

**EFFECTS OF TEMPERATURE  
AND ENVIRONMENT ON  
MECHANICAL PROPERTIES OF  
TWO CONTINUOUS CARBON-  
FIBER AUTOMOTIVE  
STRUCTURAL COMPOSITES**

**M. B. Ruggles-Wrenn**

## DOCUMENT AVAILABILITY

Reports produced after January 1, 1996, are generally available free via the U.S. Department of Energy (DOE) Information Bridge.

**Web site** <http://www.osti.gov/bridge>

Reports produced before January 1, 1996, may be purchased by members of the public from the following source.

National Technical Information Service

5285 Port Royal Road

Springfield, VA 22161

**Telephone** 703-605-6000 (1-800-553-6847)

**TDD** 703-487-4639

**Fax** 703-605-6900

**E-mail** [info@ntis.fedworld.gov](mailto:info@ntis.fedworld.gov)

**Web site** <http://www.ntis.gov/support/ordernowabout.htm>

Reports are available to DOE employees, DOE contractors, Energy Technology Data Exchange (ETDE) representatives, and International Nuclear Information System (INIS) representatives from the following source.

Office of Scientific and Technical Information

P.O. Box 62

Oak Ridge, TN 37831

**Telephone** 865-576-8401

**Fax** 865-576-5728

**E-mail** [reports@adonis.osti.gov](mailto:reports@adonis.osti.gov)

**Web site** <http://www.osti.gov/contact.html>

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

Metals and Ceramics Division

**EFFECTS OF TEMPERATURE AND ENVIRONMENT  
ON MECHANICAL PROPERTIES OF  
TWO CONTINUOUS CARBON-FIBER AUTOMOTIVE STRUCTURAL COMPOSITES**

M. B. Ruggles-Wrenn

Date Published: September 2003

Prepared by the  
OAK RIDGE NATIONAL LABORATORY  
Oak Ridge, Tennessee 37831-6285  
managed by  
UT-BATTELLE, LLC  
for the  
U.S. DEPARTMENT OF ENERGY  
under contract DE-AC05-00OR22725

This page left blank intentionally.

# CONTENTS

|  | Page |
|--|------|
| LIST OF TABLES .....                               | V    |
| ABSTRACT .....                                     | 1    |
| 1. INTRODUCTION .....                              | 1    |
| 2. MATERIAL AND SPECIMENS .....                    | 3    |
| 3. CROSSPLY CARBON-FIBER COMPOSITE .....           | 4    |
| 3.1 TENSILE PROPERTIES.....                        | 4    |
| 3.1.1 Experimental Arrangements .....              | 4    |
| 3.1.2 Room-Temperature Behavior .....              | 4    |
| 3.1.3 Effects of Temperature .....                 | 4    |
| 3.1.4 Effects of Environment.....                  | 5    |
| 3.2 COMPRESSIVE PROPERTIES .....                   | 6    |
| 3.3 SHEAR PROPERTIES .....                         | 7    |
| 3.4. UNIAXIAL AND BIAXIAL FLEXURAL PROPERTIES..... | 7    |
| 3.4.1 Uniaxial flexural properties.....            | 7    |
| 3.4.2 Biaxial flexural properties.....             | 8    |
| 4. QUASI-ISOTROPIC CARBON-FIBER COMPOSITE .....    | 9    |
| 4.1 TENSILE PROPERTIES.....                        | 9    |
| 4.1.1 Room-Temperature Behavior .....              | 9    |
| 4.1.2 Effects of Temperature .....                 | 9    |
| 4.1.3 Effects of Environment.....                  | 10   |
| 4.2 COMPRESSIVE PROPERTIES .....                   | 10   |
| 4.3 SHEAR PROPERTIES .....                         | 11   |
| 4.4 UNIAXIAL AND BIAXIAL FLEXURAL PROPERTIES.....  | 11   |
| 4.4.1 Uniaxial flexural properties.....            | 11   |
| 4.4.2 Biaxial flexural properties.....             | 12   |
| 5. SUMMARY .....                                   | 13   |
| 5.1 CROSSPLY CARBON-FIBER COMPOSITE .....          | 13   |
| 5.2 QUASI-ISOTROPIC CARBON-FIBER COMPOSITE .....   | 13   |
| REFERENCES .....                                   | 14   |

This page left blank intentionally.

## LIST OF TABLES

| Table  | Page |
|--|------|
| 1. Summary of room-temperature stiffness values for the crossply carbon-fiber composite, 0/90° fiber orientation .....   | 15   |
| 2. Summary of room-temperature stiffness values for the crossply carbon-fiber composite, ±45° fiber orientation .....  | 17   |
| 3. Summary of room-temperature tensile properties of the crossply carbon-fiber composite, 0/90° fiber orientation .....  | 18   |
| 4. Summary of room-temperature tensile properties of the crossply carbon-fiber composite, ±45° fiber orientation .....   | 19   |
| 5. Summary of plaque average tensile properties of the crossply carbon-fiber composite, 0/90° fiber orientation .....  | 21   |
| 6. Summary of plaque average tensile properties the crossply carbon-fiber composite, ±45° fiber orientation .....  | 22   |
| 7. Summary of tensile tests at various strain rates for the crossply carbon-fiber composite, 0/90° fiber orientation .....   | 23   |
| 8. Summary of tensile tests at various strain rates for the crossply carbon-fiber composite, ±45° fiber orientation .....  | 24   |
| 9. Summary of tensile tests at various temperatures for the crossply carbon-fiber composite, 0/90° fiber orientation .....   | 25   |
| 10. Summary of tensile tests at various temperatures for the crossply carbon-fiber composite, ±45° fiber orientation .....   | 27   |
| 11. Temperature multiplication factors for determining at-temperature tensile modulus and strength from room-temperature values for the crossply carbon-fiber composite, 0/90° fiber orientation ..... | 28   |
| 12. Temperature multiplication factors for determining at-temperature tensile modulus and strength from room-temperature values for the crossply carbon-fiber composite, ±45° fiber orientation .....  | 28   |
| 13. Summary of Poisson's ratio measurements at different temperatures for the crossply carbon-fiber composite, 0/90° fiber orientation .....   | 29   |
| 14. Summary of Poisson's ratio measurements at different temperatures for the crossply carbon-fiber composite, ±45° fiber orientation .....  | 29   |
| 15. Effects of prior thermal cycling on mechanical properties of the crossply carbon-fiber composite, 0/90° fiber orientation .....  | 30   |
| 16. Effects of prior thermal cycling on mechanical properties of the crossply carbon-fiber composite, ±45° fiber orientation .....   | 31   |
| 17. Effects of prior thermal cycling on apparent shear strength in short-beam shear of the crossply carbon-fiber composite, 0/90° fiber orientation .....  | 32   |
| 18. Effects of prior thermal cycling on apparent shear strength in short-beam shear of the crossply carbon-fiber composite, ±45° fiber orientation .....   | 33   |
| 19. Effects of fluid environments on apparent shear strength in short-beam shear of the crossply carbon-fiber composite, 0/90° fiber orientation .....   | 34   |
| 20. Effects of fluid environments on apparent shear strength in short-beam shear of the crossply carbon-fiber composite, ±45° fiber orientation .....  | 37   |

|     |  |    |
|-----|--|----|
| 21. | Effect of exposure in 23°C distilled water and in 70% RH air on tensile strength and stiffness of the crossply carbon-fiber composite, 0/90° fiber orientation.....                                    | 40 |
| 22. | Effect of exposure in 23°C distilled water and in 70% RH air on tensile strength and stiffness of the crossply carbon-fiber composite, ±45° fiber orientation.....                                     | 41 |
| 23. | Effect of 1000-h distilled water exposure and 1000-h distilled water exposure followed by freezing on stiffness and strength of the crossply carbon-fiber composite, 0/90° fiber orientation .....     | 42 |
| 24. | Effect of 1000-h distilled water exposure and 1000-h distilled water exposure followed by freezing on stiffness and strength of the crossply carbon-fiber composite, ±45° fiber orientation .....      | 43 |
| 25. | Effect of exposure in windshield washer fluid on tensile strength and stiffness of the crossply carbon-fiber composite, 0/90° fiber orientation .....  | 44 |
| 26. | Effect of exposure in windshield washer fluid on tensile strength and stiffness of the crossply carbon-fiber composite, ±45° fiber orientation .....   | 45 |
| 27. | Summary of room-temperature compressive tests for the crossply carbon-fiber composite.....   | 46 |
| 28. | Compressive properties of the crossply carbon-fiber composite, 0/90° fiber orientation, at different temperatures.....   | 47 |
| 29. | Compressive properties of the crossply carbon-fiber composite, ±45° fiber orientation, at different temperatures.....  | 48 |
| 30. | Temperature multiplication factors for determining at-temperature compressive modulus and strength from room-temperature values for the crossply carbon-fiber composite, 0/90° fiber orientation ..... | 49 |
| 31. | Temperature multiplication factors for determining at-temperature compressive modulus and strength from room-temperature values for the crossply carbon-fiber composite, ±45° fiber orientation .....  | 49 |
| 32. | Effects of 1000-h exposure in 23°C distilled water on room-temperature compressive properties of the crossply carbon-fiber composite.....  | 50 |
| 33. | Effect of exposure in windshield washer fluid on compressive strength of the crossply carbon-fiber composite .....   | 51 |
| 34. | Summary of room-temperature shear tests for the crossply carbon-fiber composite.....   | 52 |
| 35. | Shear properties of the crossply carbon-fiber composite, 0/90° fiber orientation, at different temperatures .....  | 53 |
| 36. | Shear properties of the crossply carbon-fiber composite, ±45° fiber orientation, at different temperatures .....   | 54 |
| 37. | Temperature multiplication factors for determining at-temperature shear modulus and strength from room-temperature values for the crossply carbon-fiber composite, 0/90° fiber orientation .....       | 55 |
| 38. | Temperature multiplication factors for determining at-temperature shear modulus and strength from room-temperature values for the crossply carbon-fiber composite, ±45° fiber orientation .....        | 55 |
| 39. | Effects of 1000-h exposure in 23°C distilled water on room-temperature shear properties of the crossply carbon-fiber composite.....  | 56 |
| 40. | Effect of exposure in windshield washer fluid on shear strength of the crossply carbon-fiber composite .....   | 57 |
| 41. | Uniaxial flexural properties of the crossply carbon-fiber composite at different temperatures.....   | 58 |



|     |   |    |
|-----|---|----|
| 42. | Effects of 1000-h exposure in 23°C distilled water on room-temperature uniaxial flexural properties of the crossply carbon-fiber composite .....                                      | 59 |
| 43. | Effect of exposure in windshield washer fluid on uniaxial flexural properties of the crossply carbon-fiber composite.....   | 60 |
| 44. | Biaxial flexural properties of the crossply carbon-fiber composite at different temperatures: $\pm 45^\circ$ fiber orientation .....  | 61 |
| 45. | Effects of environment on biaxial flexural properties of the crossply carbon-fiber composite: $\pm 45^\circ$ fiber orientation .....  | 62 |
| 46. | Summary of room-temperature stiffness values for the quasi-isotropic carbon-fiber composite .....   | 63 |
| 47. | Summary of room-temperature tensile properties for the quasi-isotropic carbon-fiber composite .....   | 66 |
| 48. | Summary of plaque average tensile properties for the quasi-isotropic carbon-fiber composite .....   | 67 |
| 49. | Summary of tensile tests at various strain rates for the quasi-isotropic carbon-fiber composite .....   | 68 |
| 50. | Summary of tensile tests at various temperatures for the quasi-isotropic carbon-fiber composite .....   | 69 |
| 51. | Temperature multiplication factors for determining at-temperature tensile modulus and strength from room-temperature values for the quasi-isotropic carbon-fiber composite .....      | 70 |
| 52. | Summary of Poisson's ratio measurements at different temperatures for the quasi-isotropic carbon-fiber composite .....  | 71 |
| 53. | Effects of prior thermal cycling on mechanical properties of the quasi-isotropic carbon-fiber composite .....   | 71 |
| 54. | Effect of exposure in 23°C distilled water on tensile strength and stiffness of the quasi-isotropic carbon-fiber composite .....  | 72 |
| 55. | Effect of exposure in 70% relative humidity air on tensile strength and stiffness of the quasi-isotropic carbon-fiber composite .....   | 74 |
| 56. | Effects of 100-h exposure in windshield washer fluid on tensile stiffness and strength of the quasi-isotropic carbon-fiber composite .....  | 75 |
| 57. | Summary of room-temperature compressive tests for the quasi-isotropic carbon-fiber composite .....  | 76 |
| 58. | Compressive properties of the quasi-isotropic carbon-fiber composite at different temperatures.....   | 77 |
| 59. | Temperature multiplication factors for determining at-temperature compressive stiffness and strength from room-temperature values for the quasi-isotropic carbon-fiber composite..... | 77 |
| 60. | Effects of 1000-h exposure in 23°C distilled water on room-temperature compressive properties of the quasi-isotropic carbon-fiber composite .....                                     | 78 |
| 61. | Effects of 100-h exposure in windshield washer fluid on room-temperature compressive strength of the quasi-isotropic carbon-fiber composite .....                                     | 78 |
| 62. | Summary of in-air room-temperature shear properties of the quasi-isotropic carbon-fiber composite .....   | 78 |
| 63. | Shear properties of the quasi-isotropic carbon-fiber composite at different temperatures.....   | 79 |

|     |  |    |
|-----|--|----|
| 64. | Temperature multiplication factors for determining at-temperature shear modulus and strength from room-temperature values for the quasi-isotropic carbon-fiber composite ..... | 79 |
| 65. | Effects of 1000-h exposure in 23°C distilled water on room-temperature shear properties of the quasi-isotropic carbon-fiber composite .....                                    | 80 |
| 66. | Effects of 100-h exposure in windshield washer fluid on room-temperature shear strength of the quasi-isotropic carbon-fiber composite .....                                    | 80 |
| 67. | Uniaxial flexural properties of the quasi-isotropic carbon-fiber composite at different temperatures .....   | 81 |
| 68. | Effects of 1000-h exposure in 23°C distilled water on uniaxial flexural properties of the quasi-isotropic carbon-fiber composite .....   | 82 |
| 69. | Effects of 100-h exposure in windshield washer fluid on uniaxial flexural properties of the quasi-isotropic carbon-fiber composite .....                                       | 83 |
| 70. | Biaxial flexural properties of the quasi-isotropic carbon-fiber composite at different temperatures.....   | 84 |
| 71. | Effects of environment on biaxial flexural properties of the quasi-isotropic carbon-fiber composite.....   | 85 |

# EFFECTS OF TEMPERATURE AND ENVIRONMENT ON MECHANICAL PROPERTIES OF TWO CONTINUOUS CARBON-FIBER AUTOMOTIVE STRUCTURAL COMPOSITES

M. B. Ruggles-Wrenn

## ABSTRACT

The Durability of Carbon-Fiber Composites Project was established at Oak Ridge National Laboratory (ORNL) by the U.S. Department of Energy to develop experimentally based, durability-driven design guidelines to assure the long-term (15-year) structural integrity of carbon-fiber-based composite systems for automotive structural applications. The project addressed characterization and modeling the durability of a progression of carbon-reinforced thermoset materials, each of which has the same urethane matrix. The primary purpose of this report is to provide the individual specimen test data. Basic mechanical property testing and results for a reference  $[\pm 45^\circ]_{3S}$  crossply composite and a quasi-isotropic,  $[0/90^\circ/\pm 45^\circ]_S$  version of the reference crossply are provided. The matrix and individual  $\pm 45^\circ$  stitch-bonded mats are the same in both cases. Although the composite utilized aerospace-grade carbon-fiber reinforcement, it was made by a rapid-molding process suitable for high-volume automotive use. Behavioral trends, effects of temperature and environment, and corresponding design knockdown factors are established for both materials. The reference crossply is highly anisotropic with two dominant fiber orientations —  $0/90^\circ$  and  $\pm 45^\circ$ . Therefore properties were developed for both orientations.

## 1. INTRODUCTION

Development of lighter weight, more fuel-efficient automobiles represents a technology area where advanced materials can be successfully applied. The fuel efficiency of automobiles can be significantly enhanced by using lightweight materials, such as polymer matrix composites, in primary structural components. However, while significant effort is being devoted to material development and processing, commercial application of composite materials lags behind due, in part, to the lack of specific design guidance and an understanding of the material performance under actual service conditions. There is a recognized need for improved structural design methods and criteria that address deformation and failure behavior of composite materials.

The Durability of Carbon-Fiber Composites Project was established at Oak Ridge National Laboratory (ORNL) by the U.S. Department of Energy to develop the experimentally based, durability-driven design guidelines necessary to assure long-term (15-year) integrity of carbon-fiber-based composite systems that can be used to produce large structural automotive components. The plan for characterizing and modeling the durability of carbon-fiber composites was to focus on the following sequence of materials, each of which has the same urethane matrix:

- reference  $[\pm 45^\circ]_{3S}$  crossply composite,
- $[0/90^\circ/\pm 45^\circ]_S$  quasi-isotropic composite, and
- chopped-fiber composite.

The present report is a companion report to ORNL/TM-2003/114 and describes basic tensile, compressive, shear, and flexure property testing and results for the reference crossply and quasi-isotropic carbon-fiber composites produced by a rapid molding process suitable for high-volume automotive applications. The two composites had the same Baydur 420 IMR urethane matrix. The quasi-isotropic composite utilizes the same  $\pm 45^\circ$  stitched-mat reinforcement as the reference crossply composite. The basic ply information from the reference crossply could thus be used as a basis for predicting and better understanding the behavior of the quasi-isotropic material.

Materials and specimen designs are presented in Chapter 2. Chapter 3 is dedicated to behavior of the crossply carbon-fiber composite. Experimental arrangements are described and tensile, compressive and shear test results are summarized for both fiber orientations. Effects of temperature and environment are assessed, corresponding design knockdown factors are established. In addition, effects of prior thermal cycling are discussed. Chapter 4 focuses on the quasi-isotropic carbon-fiber composite, giving a summary of tests and test results, as well as design knockdown factors to account for the effects of temperature and environment. Concluding remarks are made in Chapter 5.

## 2. MATERIALS AND SPECIMENS

The matrix for both materials used in this study was produced by the Bayer Corporation and identified as Baydur 420 IMR (Internal Mold Release). The basic matrix structure is a urea-urethane. The carbon-fiber laminate preforms consisted of Thornel T300 continuous fibers in tows of 6000 filaments. Stitch-bonded mats made of two unidirectional plies in a  $\pm 45^\circ$  configuration were used. Six mats,  $[\pm 45]_{3S}$ , were used for the crossply laminate. Four mats,  $[0/90, \pm 45]_S$ , were used for the quasi-isotropic laminate. The laminate thicknesses were 3.2 and 2.2 mm for the crossply and the quasi-isotropic materials, respectively. The fiber content for both carbon-fiber laminates was approximately 40 vol %.

Basic properties were established from stiffness, tensile, compressive, shear, and flexure tests. Untabbed dogbone-shaped tensile specimens were used<sup>1</sup> in all stiffness and tensile tests, which were performed according to the test method described in Ref. 1. Flat specimens with tabs were used in compression tests.<sup>1</sup> The tab material was G-11 composite, an epoxy reinforced with woven fiberglass cloth. The adhesive used for bonding the tabs to the test specimens was Hysol EA 93009NA A/B for the  $-40^\circ\text{C}$  and  $23^\circ\text{C}$  tests and XEA 9364 A/B for the  $120^\circ\text{C}$  tests. Compression tests employed an IITRI fixture (Procedure B in ASTM D 3410<sup>2</sup>). The test method was as described in Ref. 1. The V-notched beam (Iosipescu) shear specimens and shear test method were as described in Ref. 1. The uniaxial flexural strength tests were performed according to the three-point-bend test method specified in the ASTM Standard D 790.1 (Ref. 3).

In the case of the crossply laminate, two fiber orientations were considered:  $0/90^\circ$  relative to the specimen axis and  $\pm 45^\circ$ . These orientations result in two extremes of behavior. Under tensile loading, the behavior of the  $0/90^\circ$  specimens is fiber dominated, while for the  $\pm 45^\circ$  fiber orientation, the behavior is matrix dominated. In the case of the  $0/90^\circ$  fiber orientation, the tab material and adhesive used for bonding the tabs to Iosipescu shear specimens were the same as for the compression specimens. For the  $\pm 45^\circ$  fiber orientation, the tabs were cut from the same material as the specimens. The beam specimens were 25.4 mm x 76.2 mm. The loading rollers had a radius of 12.7 mm. The surface fibers in the  $0/90^\circ$  beams were at  $90^\circ$  to the beam axis, thus placing a weaker ply at the specimen surface. Poisson's ratio measurements were carried out using three specimens for each fiber orientation according to the test method described in Ref. 1.

In the case of the quasi-isotropic laminate, all tension and compression specimens were cut so that the surface fibers were at  $90^\circ$  to the specimen axis, thus placing a weaker ply at the specimen surface. All shear specimens were cut so that the surface fibers were at  $0^\circ$  to the specimen axis. The tab material and adhesive used for bonding the tabs to Iosipescu shear specimens were the same as for the compression specimens. The uniaxial flexural strength tests were performed according with the three-point-bend test method specified in the ASTM Standard D 790.1 (Ref. 3). The uniaxial flexure tests employed 12.7 mm x 76.2 mm beam specimens. The loading rollers had a radius of 4.4 mm. Half of all beam specimens were cut so that the surface fibers were longitudinal (at an angle of  $0^\circ$  relative to the beam axis). These are referred to as L beams. Remaining beam specimens were cut with transverse surface fibers, and are referred to as T beams.

### 3. CROSSPLY CARBON-FIBER COMPOSITE

#### 3.1 TENSILE PROPERTIES

##### 3.1.1 Experimental Arrangements

All tests were performed in an air environment. A servocontrolled MTS axial-torsion mechanical testing machine together with an MTS digital TestStar Materials Testing Workstation was used for computerized testing and data acquisition. The load (engineering stress), strain, and displacement were measured and recorded; the digitized test data were stored on both hard and floppy disks. The data acquisition intervals were established on the basis of load, i.e. a data point was recorded whenever the load changed by 44.5 N. After the test the digitized data can be recalled for processing and interpretation. The entire history is available for analysis.

Specimens were mounted in mechanical wedge grips. Strain measurement was accomplished with an MTS 632.17E-20 averaging extensometer of 25.4-mm gage length. For the 0/90° specimens, elastic modulus,  $E$ , was measured in three load-controlled cycles between load levels of 2960 (corresponding to  $\approx 10\%$  of the UTS) and 6630 N (corresponding to  $\approx 22\%$  of the UTS) with a frequency of 0.1 Hz. In the case of the  $\pm 45^\circ$  specimens, the load controlled cycles were between 445 N (corresponding to  $\approx 5\%$  of the UTS) and 1447 N (corresponding to  $\approx 15\%$  of the UTS). The recorded elastic modulus was established as the average value obtained during cycling. Tensile tests to failure were conducted in displacement control at a rate of 0.025 mm/s.

##### 3.1.2 Room-Temperature Behavior

In-air room-temperature tensile stiffness values were established from 243 stiffness tests for the 0/90° fiber orientation and from 115 stiffness tests for  $\pm 45^\circ$  fiber orientation. Results of stiffness tests are summarized in Tables 1 and 2 for the 0/90° and for the  $\pm 45^\circ$  fiber orientations, respectively. In addition to the values of elastic modulus,  $E$ , Tables 1 and 2 include corresponding averages, standard deviations, and coefficients of variation.

Results of 91 tensile tests for the 0/90° fiber orientation are summarized in Table 3. Presented in Table 4 are results of 116 tensile tests for the  $\pm 45^\circ$  fiber orientation. The ultimate tensile strength, UTS, and failure strain,  $\epsilon_f$ , are shown in Tables 3 and 4 together with the overall average,  $A$ , standard deviation,  $S$ , and coefficient of variation,  $C_v$ , for each of the properties determined.

Stiffness and tensile test results are recapitulated in Tables 5 and 6, for the 0/90° and the  $\pm 45^\circ$  fiber orientations, respectively. Shown in Tables 5 and 6 are the number of stiffness and tensile tests conducted on specimens from each particular plaque and the plaque averages of the tensile properties  $E$ , UTS, and  $\epsilon_f$ . Plaques are referred to using the ORNL nomenclature. Tables 5 and 6 permit an assessment of plaque-to-plaque variations in tensile properties. Overall averages of the tensile properties are included at the bottom of Tables 5 and 6.

The effect of strain rate on tensile behavior was investigated in thirty-two tests conducted at the following constant strain rates:  $10^{-6}$ ,  $10^{-4}$ ,  $10^{-2}$ , and  $10 \text{ s}^{-1}$ . Four tests were performed at each strain rate for each fiber orientation. Results are summarized in Tables 7 and 8, for the 0/90° and the  $\pm 45^\circ$  fiber orientations, respectively.

##### 3.1.3 Effects of Temperature

Effects of temperature on tensile properties of the crossply carbon-fiber composite, 0/90° fiber orientation, were assessed in thirty-three tensile tests on specimens from plaques C1 and C5 (6 tests at  $-40^\circ\text{C}$  and 9 tests at each of the following temperatures: 23, 50, and  $120^\circ\text{C}$ ). For the

$\pm 45^\circ$  fiber orientation, the temperature effects were assessed in thirty tensile tests on specimens from plaque C11 (12 tests at  $70^\circ\text{C}$  and 6 tests at each of the following temperatures:  $-40$ ,  $23$ , and  $120^\circ\text{C}$ ). Results are summarized in Tables 9 and 10, for the  $0/90^\circ$  and the  $\pm 45^\circ$  fiber orientations, respectively. Virgin (room-temperature) stiffness, at-temperature stiffness, UTS, and failure strain are shown in Tables 9 and 10 together with the stiffness and strength temperature factors for each specimen. The stiffness temperature factor is defined as the ratio of at-temperature stiffness for a particular specimen to the virgin room-temperature stiffness. The strength temperature factor is defined as the ratio of the at-temperature UTS for a particular specimen to the average UTS obtained at room-temperature for specimens from the same plaque.

Results in Tables 9 and 10 were used to derive temperature multiplication factors to determine at-temperature stiffness and strength from room-temperature values. The factors are presented in Tables 11 and 12, for the  $0/90^\circ$  and the  $\pm 45^\circ$  fiber orientations, respectively. The detailed derivation of the temperature multiplication factors can be found in Ref. 4.

For the  $0/90^\circ$  specimens, Poisson's ratio measurements were carried out by subjecting three tensile specimens to five load-controlled cycles between load levels of 2960 (corresponding to  $\approx 10\%$  of the UTS) and 6630 N (corresponding to  $\approx 22\%$  of the UTS) with a frequency of 0.1 Hz. In the case of the  $\pm 45^\circ$  specimens, the load-controlled cycles were between 445 N (corresponding to  $\approx 5\%$  of the UTS) and 1447 N (corresponding to  $\approx 15\%$  of the UTS). Each specimen was tested at  $-40$ ,  $23$ ,  $70$ , and  $120^\circ\text{C}$ . Using very low loads ensures that damage was not introduced at each temperature. Poisson's ratio values are summarized in Tables 13 and 14, for the  $0/90^\circ$  and the  $\pm 45^\circ$  fiber orientations, respectively.

The effects of prior thermal cycling on basic properties of the crossply carbon-fiber composite were investigated in six tensile and six compressive tests for each fiber orientation. In addition, short-beam shear specimens with a 3- by 6-mm cross-section (six for each fiber orientation) were included in this test series. The short-beam shear specimens were tested in three-point bending with a span of 12.5 mm. Prior to testing, specimens were subjected to 20 thermal cycles. A thermal cycle between  $-40$  and  $120^\circ\text{C}$  (shown in Ref. 4) was chosen to reflect the automotive design temperature range. Tension and compression results are summarized in Tables 15 and 16 for the  $0/90^\circ$  and the  $\pm 45^\circ$  fiber orientations, respectively. Results of the short-beam shear tests are presented in Tables 17 and 18 for the  $0/90^\circ$  and the  $\pm 45^\circ$  fiber orientations, respectively.

### **3.1.4 Effects of Environment**

Environmental screening tests were performed to determine which automotive fluids have a degrading effect on strength. Short-beam shear specimens, having the highest edge-to-face area ratio, were used in this study. All specimens were cut from the same plaque. The  $0/90$  specimens had  $0^\circ$  fibers on the surface. Details of the nine automotive fluids used in the screening can be found in Ref. 4. Twelve specimens were pre-exposed in each fluid, six for each fiber orientation. Exposure time for all fluids except battery acid was 1000 h. In the case of battery acid, exposure time was reduced to 115 h. Short-beam shear specimens were tested in accordance with the ASTM Standard D 2344<sup>5</sup>. Results are summarized in Tables 19 and 20 for the  $0/90^\circ$  and the  $\pm 45^\circ$  fiber orientations, respectively. Note that results obtained for the unexposed short-beam shear specimens are given in Tables 17 and 18 above.

Effects of moisture on tensile properties of the crossply carbon-fiber composite were investigated with the purpose of establishing correlations between exposure time and weight change, and subsequently, strength and stiffness. For each fiber orientation, six specimens were exposed in room-temperature distilled water and six specimens, in 70% relative humidity (RH) air. All specimens were initially in the "as-received" condition. Effects of exposure in  $23^\circ\text{C}$  distilled water and in 70% RH air on tensile properties are summarized in Tables 21 and 22 for the  $0/90^\circ$  and the  $\pm 45^\circ$  fiber orientations, respectively. Included in Tables 21 and 22 are the virgin

stiffness, post-exposure stiffness and strength, as well as the values of percent change in strength and stiffness for given exposure times. The change in stiffness is calculated with reference to the virgin stiffness of each individual specimen. The change in strength is calculated with reference to the plaque average strength. A detailed discussion of moisture sorption and correlations between exposure time, weight change, and property changes can be found in Ref. 4.

In addition to these conditions, the effects of exposure to freezing temperatures on stiffness and strength of the material when saturated or nearly saturated with water were considered. Twelve tensile specimens for each fiber orientation were soaked in room-temperature distilled water for 1000 h. Six of the twelve specimens were tested after exposure. The remaining six specimens were exposed overnight to a temperature of  $-15^{\circ}\text{C}$  and then tested. Changes in stiffness and strength due to exposure to distilled water, as well as to the water exposure followed by subfreezing overnight, were assessed and compared. As before, changes in stiffness were calculated with reference to the virgin stiffness for each specimen, while changes in strength were referenced to the plaque average strength. Results are summarized in Tables 23 and 24 for the  $0/90^{\circ}$  and the  $\pm 45^{\circ}$  fiber orientations, respectively. Note that all  $0/90^{\circ}$  specimens came from a single plaque (C-15), as did the  $\pm 45^{\circ}$  specimens (C-17).

The effects of exposure in windshield washer fluid (30% distilled water and 70% methanol) were investigated. Windshield washer fluid was selected as a practical exposure condition, because methanol in windshield washer fluid is a “lighter molecule”. Exposure times were 50, 100, and 1000 h. Results are summarized in Tables 25 and 26 for the  $0/90^{\circ}$  and the  $\pm 45^{\circ}$  fiber orientations, respectively. Virgin stiffness, post-exposure stiffness, UTS and failure strain are given in Tables 25 and 26 for each specimen. Also included in Tables 25 and 26 are environmental knockdown factors for design. Stiffness design factor is defined as the ratio of post-exposure stiffness to virgin stiffness of that particular specimen. Strength design factor is calculated as the ratio of the post-exposure UTS to the average UTS obtained in tensile tests on unexposed specimens from the same plaque.

### 3.2 COMPRESSIVE PROPERTIES

All tests were performed at room temperature in an air environment. Specimens were mounted in an IITRI Compression Test Fixture according to the ASTM Standard D 3410<sup>3</sup>. Compressive tests to failure were conducted in displacement control at a rate of 0.025 mm/s. Strain measurement was accomplished with two strain gages mounted in the gage section of the specimen, one strain gage on each side of the specimen. In most tests the two strain gages produced strain measurements that were approximately the same. The two strain measurements were averaged and the average strains were used for reporting data. The data acquisition intervals were established on the basis of load, i.e. a data point was recorded whenever the load changed by 44.5 N. For the  $0/90^{\circ}$  specimens, compressive stiffness,  $E_c$ , was calculated using linear regression for the initial stress-strain slope between the loads of 2960 and 6630 N. In the case of the  $\pm 45^{\circ}$  the load interval between 445 and 1447 N was used in calculations.

Eighteen  $0/90^{\circ}$  and six  $\pm 45^{\circ}$  compression specimens were tested at room temperature. Test results are summarized in Table 27, where compressive stiffness,  $E_c$  and ultimate compressive strength (UCS) are given together with failure strain for each specimen. The effect of temperature on compressive properties of the  $0/90^{\circ}$  fiber orientation was investigated in eight tests each at  $-40$ ,  $50$ , and  $120^{\circ}\text{C}$ . In the case of the  $\pm 45^{\circ}$  fiber orientation, effects of temperature were assessed in six compression tests each at  $-40$ ,  $23$ ,  $70$ , and  $120^{\circ}\text{C}$ . Test results are summarized in Tables 28 and 29 for the  $0/90^{\circ}$  and  $\pm 45^{\circ}$  fiber orientations, respectively. Results in Tables 28 and 29 were used to derive temperature multiplication factors to determine at-temperature compressive stiffness and strength from room-temperature values (See Ref 4). The factors are presented in Tables 30 and 31 for the  $0/90^{\circ}$  and  $\pm 45^{\circ}$  fiber orientations, respectively.



Effects of 1000-h exposure in 23°C distilled water on compressive properties of the crossply composite were investigated using six pre-exposed specimens each for the 0/90° and ±45° fiber orientations. Results are summarized in Table 32, where compressive stiffness, UCS and failure strain are given together with knockdown design factors for each specimen. The stiffness (strength) design factor is defined as the ratio of the post-exposure stiffness (strength) to the average stiffness (strength) obtained in compression tests on unexposed specimens from the same plaque.

Effects of exposure to windshield washer fluid on compressive strength of the crossply carbon-fiber composite were investigated using twelve pre-exposed specimens (six pre-exposed for 50 h and six for 100 h) each for the 0/90° and ±45° fiber orientations. Results are summarized in Table 33. Note that in the case of windshield washer fluid, compressive stiffness values were not measured. Application of strain gages, required for compressive stiffness determinations, would have resulted in excessive loss of the absorbed methanol due to evaporation during gage installation.

### **3.3 SHEAR PROPERTIES**

In-air room-temperature shear properties of the crossply carbon-fiber composite were established based on twenty-one Iosipescu shear tests for the 0/90° fiber orientation, and on six tests for the ±45° fiber orientation. Test results are summarized in Table 34.

For each fiber orientation, the effect of temperature on shear properties was investigated in six tests each at -40, 70, and 120°C. Test results are summarized in Tables 35 and 36 for the 0/90° and ±45° fiber orientations, respectively. Results in Tables 35 and 36 were used to derive temperature multiplication factors to determine at-temperature stiffness and strength from room-temperature values (See Ref 4). The factors are presented in Tables 37 and 38 for 0/90° and ±45° fiber orientations, respectively.

Effects of 1000-h exposure in 23°C distilled water on shear properties of the crossply composite were investigated using six pre-exposed specimens each for the 0/90° and ±45° fiber orientations. Results are summarized in Table 39, where shear modulus, shear strength, and knockdown design factors are presented for each specimen. The stiffness (strength) design factor is defined as the ratio of the post-exposure stiffness (strength) to the average stiffness (strength) obtained in compression tests on unexposed specimens from the same plaque.

Effects of exposure to windshield washer fluid on shear strength of the crossply carbon-fiber composite were investigated using twelve pre-exposed specimens (six pre-exposed for 50 h and six for 100 h) each for the 0/90° and ±45° fiber orientations. Results are summarized in Table 40. Note that in the case of windshield washer fluid, shear modulus values were not measured. Application of strain gages, required for shear specimens, would have resulted in excessive loss of the absorbed methanol due to evaporation during gage installation.

### **3.4 UNIAXIAL AND BIAXIAL FLEXURAL PROPERTIES**

#### **3.4.1 Uniaxial flexural properties**

The uniaxial flexural strength tests were performed in accordance with the three-point bend test method specified in ASTM Standard D 790<sup>5</sup>. The specimen width was 25.4 mm, the overall specimen length was 76.2 mm, and the support span was 50.8 mm (see Ref. 4). The loading rollers had a radius of 12.7 mm.

For each fiber orientation, uniaxial flexure properties were established based on six tests each at 23 and 120°C. Results are presented in Table 41. The strength values are reported in terms of the modulus of rupture (MOR), which is the maximum bending stress at rupture calculated using simple elastic beam theory for an isotropic, homogeneous material. Because the MOR

calculations ignore the composite inhomogeneity, results are somewhat qualitative, but nonetheless useful for establishing environmental and temperature multiplication factors. Likewise the "modulus of elasticity" values tabulated are just apparent values based on the assumption that the composite is homogeneous, isotropic, and elastic.

Effects of 1000-h exposure in 23°C distilled water on uniaxial flexure properties of the crossply composite were investigated using six pre-exposed specimens each for the 0/90° and ±45° fiber orientations. Results are summarized in Table 42, where MOR and a corresponding knockdown design factor are given for each specimen. Effects of exposure to windshield washer fluid on uniaxial flexural properties of the crossply carbon-fiber composite were investigated using twelve pre-exposed specimens (six pre-exposed for 50 h and six for 100 h) each for the 0/90° and ±45° fiber orientations. Results are summarized in Table 43.

### **3.4.2 Biaxial flexural properties**

The test specimen together with the support and loading arrangement used for biaxial flexural tests were as described in Chap. 8 of Ref. 4. The specimen outside diameter was 94 mm, and the nominal thickness was 3.2 mm. The load-ring diameter was 38.1 mm, while the support-ring diameter was 88.9 mm. Six specimens were tested each at room temperature, and at 120°C. Results are summarized in Table 44 for the ±45° composite fiber orientation. Biaxial flexure results are presented in terms of the failure load and used in this way to establish temperature multiplication factors, which are defined as the ratios of the at-temperature failure load to the average room-temperature failure load.

Effects of 1000-h exposure in 23°C distilled water and of 100-h exposure in windshield washer fluid on biaxial flexure properties of the crossply composite were investigated using six pre-exposed specimens for each condition. Results are summarized in Table 45 for the ±45° composite fiber orientation, where maximum load and a corresponding knockdown design factor are given for each specimen.

## 4. QUASI-ISOTROPIC CARBON-FIBER COMPOSITE

### 4.1 TENSILE PROPERTIES

#### 4.1.1 Room-Temperature Behavior

Experimental arrangements were as described in Sect. 3.1.1. Elastic modulus,  $E$ , was measured in three load-controlled cycles between load levels of 445 N (corresponding to  $\approx 3\%$  of the UTS) and 2224 N (corresponding to  $\approx 15\%$  of the UTS) with a frequency of 0.1 Hz. Results of stiffness and tensile tests are summarized in Tables 46 and 47. Values of elastic modulus,  $E$ , obtained in 456 stiffness tests are presented in Table 46. The ultimate tensile strength, UTS, and failure strain,  $\epsilon_f$ , produced in 86 tensile tests to failure are summarized in Table 47. Also given in Tables 46 and 47 are the overall average,  $A$ , standard deviation,  $S$ , and coefficient of variation,  $C_v$ , for each of the material properties determined.

Stiffness and tensile test results are recapitulated in Table 48, where the number of stiffness and tensile tests conducted on specimens from each particular plaque and the plaque averages of the tensile properties  $E$ , UTS, and  $\epsilon_f$ , are given. Plaques are referred to using the ORNL nomenclature. Table 48 permits an assessment of plaque-to-plaque variations in tensile properties. Overall averages of the tensile properties are included at the bottom of Table 48.

The effect of strain rate on tensile behavior was investigated in four tests conducted at each of the following constant strain rates:  $10^{-6}$ ,  $10^{-4}$ ,  $10^{-2}$ , and  $10 \text{ s}^{-1}$ . Results are summarized in Table 49.

#### 4.1.2 Effects of Temperature

Effects of temperature on tensile properties of the quasi-isotropic carbon-fiber composite were assessed in six tests at each of the following temperatures:  $-40$ ,  $23$ ,  $50$ ,  $70$ , and  $120^\circ\text{C}$ , and in five tests at  $-10^\circ\text{C}$ . All 35 tests in the temperature study were conducted on specimens from a single plaque Q11. Results are summarized in Table 50, where the virgin (room-temperature) stiffness is shown together with the at-temperature stiffness, UTS, and failure strain. Also given in Table 50 are stiffness and strength temperature factors for each specimen. Stiffness temperature factor is defined as the ratio of at-temperature stiffness for a particular specimen to the room-temperature stiffness. Strength temperature factor is defined as the ratio of the at-temperature UTS for a particular specimen to the average UTS obtained at room-temperature for specimens from the same plaque. Results in Table 50 were used to derive temperature multiplication factors to determine at-temperature stiffness and strength from room-temperature values. The factors are presented in Table 51. The detailed derivation of the temperature multiplication factors can be found in Ref. 6.

Poisson's ratio measurements were carried out by subjecting five tensile specimens to 5 load-controlled cycles between 445 N (corresponding to  $\approx 3\%$  of the room-temperature UTS) and 2224 N (corresponding to  $\approx 15\%$  of the room-temperature UTS) at a frequency of 0.1 Hz. Each specimen was tested at  $-40$ ,  $23$ ,  $70$ , and  $120^\circ\text{C}$ . Using very low loads ensures that damage was not introduced at each temperature. Poisson's ratio values summarized in Table 52.

The effects of prior thermal cycling on basic properties of the quasi-isotropic carbon-fiber composite were investigated in six tensile, four compressive, and four shear tests. Prior to testing, specimens were subjected to 26 thermal cycles. A thermal cycle between  $-40$  and  $120^\circ\text{C}$  (shown in Ref. 6) was chosen to reflect the automotive design temperature range. Results are summarized in Table 53. Results in Table 53 demonstrate that thermal cycling has no significant effect on fiber-dominated properties.

#### 4.1.3 Effects of Environment

Effects of moisture on tensile properties of the quasi-isotropic carbon-fiber composite were investigated with the purpose of establishing correlations between exposure time and weight change, and subsequently, strength and stiffness. One group of specimens was exposed in 23°C distilled water. Another group was exposed in 70% relative humidity (RH) air. All specimens were kept in 40% RH air for one week prior to exposure. Effects of exposure in 23°C distilled water and in 70% RH air on tensile properties are summarized in Tables 54 and 55, respectively. Included in Tables 54 and 55 are the virgin stiffness, post-exposure stiffness and strength, as well as the values of percent change in strength and stiffness for given exposure times. The change in stiffness is calculated with reference to the virgin stiffness of each individual specimen. The change in strength is calculated with reference to the plaque average strength. A detailed discussion of moisture sorption and correlations between exposure time, weight change, and property changes is given in Ref. 6.

The effects of exposure in windshield washer fluid (30% distilled water and 70% methanol) on tensile properties were investigated. Windshield washer fluid was selected as a practical exposure condition because methanol in windshield washer fluid is a “lighter molecule”. Exposure time was 100 h. Test results are summarized in Table 56, where virgin stiffness, post-exposure stiffness and UTS are given for each specimen. Also included in Table 56 are environmental knockdown factors for design. Stiffness design factor is defined as the ratio of post-exposure stiffness to virgin stiffness of that particular specimen. Strength design factor is calculated as the ratio of the post-exposure UTS to the average UTS obtained in tensile tests on unexposed specimens from the same plaque.

## 4.2 COMPRESSIVE PROPERTIES

All tests were performed at room temperature in an air environment. Test procedure was as described in Sect. 3.2. Compressive stiffness,  $E_c$ , was calculated using linear regression for the stress-strain slope between the loads of 445 and 2224 N. Forty specimens from 9 different plaques were tested at 23°C. Test results are summarized in Table 57.

The effect of temperature on compressive properties of the quasi-isotropic carbon-fiber composite was investigated in five tests each at -40, 70, and 120°C. All compression specimens in the temperature-dependence study came from plaque Q18. Test results are summarized in Table 58. Results in Table 58 were used to derive temperature multiplication factors to determine at-temperature compressive stiffness and strength from room-temperature values (See Ref 4). The factors are presented in Table 59.

Effects of 1000-h exposure in 23°C distilled water on compressive properties of the quasi-isotropic composite were investigated using six baseline and five pre-exposed specimens from plaque Q18. Results for the pre-exposed specimens are summarized in Table 60, where compressive stiffness, UCS and knockdown design factors are presented for each specimen. The stiffness (strength) design factor is defined as the ratio of the post-exposure stiffness (strength) to the average stiffness (strength) obtained in compression tests on unexposed specimens from the same plaque.

Effects of 100-h exposure to windshield washer fluid on compressive strength of the quasi-isotropic composite were investigated using six baseline and six pre-exposed specimens from plaque Q18. Results are summarized in Table 61. Note that in the case of windshield washer fluid, compressive stiffness values were not measured. Application of strain gages, required for compressive specimens, would have resulted in excessive loss of the absorbed methanol due to evaporation during gage installation.

### 4.3 SHEAR PROPERTIES

In-air room-temperature shear properties of the quasi-isotropic carbon-fiber composite were established based on eight Iosipescu shear tests on specimens from a single plaque. Test results are summarized in Table 62.

The effect of temperature on shear properties of the quasi-isotropic carbon-fiber composite was investigated in five tests each at 70 and 120°C and in four tests at -40°C. All specimens came from plaque Q18. Test results summarized in Table 63. Results in Table 63 were used to derive temperature multiplication factors to determine at-temperature stiffness and strength from room-temperature values (See Ref 4). The factors are presented in Table 64.

Effects of 1000-h exposure in 23°C distilled water on shear properties of the quasi-isotropic composite were investigated using six pre-exposed specimens from plaque Q18. Results are summarized in Table 65, where shear modulus, shear strength, and strength factors are presented for each specimen. The stiffness (strength) design factor is defined as the ratio of the post-exposure stiffness (strength) to the average stiffness (strength) obtained in shear tests on unexposed specimens from the same plaque.

Effects of 100-h exposure in windshield washer fluid on shear strength of the 3-mm-thick composite were investigated using six pre-exposed specimens from plaque Q18. Results are summarized in Table 66. Note that in the case of windshield washer fluid, shear stiffness values were not measured. Application of strain gages, required for compressive and shear specimens, would have resulted in excessive loss of the absorbed methanol due to evaporation during gage installation.

### 4.4 UNIAXIAL AND BIAXIAL FLEXURAL PROPERTIES

#### 4.4.1 Uniaxial flexural properties

The uniaxial flexural strength tests were performed in accordance with the three-point bend test method specified in ASTM Standard D 790<sup>5</sup>. The specimen width was 12.7 mm, the overall specimen length was 76.2 mm, and the support span was 50 mm (see Ref. 6). The loading rollers had a radius of 4.4 mm.

Seventy-two specimens were tested. All came from a single plaque, Q19. The UTS for this plaque was determined to be 346 MPa. Thirty-six specimens were cut so that the surface fibers were longitudinal (at an angle of 0° relative to the beam axis). These are referred to as L beams. The other 36 beams were cut so that surface fibers were transverse. They are referred to as T beams.

The strength values are reported in terms of the modulus of rupture (MOR), which is the maximum bending stress at rupture calculated using simple elastic beam theory for an isotropic, homogeneous material. Because the MOR calculations ignore the composite inhomogeneity, results are somewhat qualitative, but nonetheless useful for establishing environmental and temperature multiplication factors.

The MOR values at -40, 23, 70, and 120°C were established based on 6 tests on L beams and 6 tests on T beams at each temperature (a total of 48 tests). Results are presented in Table 67. Temperature multiplication factors (defined as the ratio of at-temperature MOR to the room-temperature MOR value) present the MOR at each temperature in terms of the room-temperature baseline value.

The effects of environment on uniaxial flexure properties of quasi-isotropic carbon-fiber composite were assessed using the standard exposures in 23°C distilled water and windshield washer fluid. For each standard exposure, six L beams and six T beams were tested. Test results and the resulting fluid strength-multiplication factors are presented in Tables 68 and 69 for exposures in distilled water and windshield washer fluid, respectively.

#### **4.4.2 Biaxial flexural properties**

The test specimen together with the support and loading arrangement used for biaxial flexural tests were as described in Chap. 8 of Ref. 6. The specimen outside diameter was 94 mm. The load-ring diameter was 38.1 mm, while the support-ring diameter was 88.9 mm. Six specimens were tested at room temperature, and six at 120°C. Results are summarized in Table 70. Biaxial flexure results are presented in terms of the failure load and used in this way to establish temperature multiplication factors, which are defined as the ratios of the at-temperature failure load to the average room-temperature failure load.

To explore fluid effects, six specimens presoaked for 100 h in windshield washer fluid and five specimens presoaked for 1000 h in room-temperature distilled water were also tested. All tests were conducted in the laboratory air environment. Results are summarized in Table 71.

## 5. SUMMARY

### 5.1 CROSSPLY CARBON-FIBER COMPOSITE

- The crossply carbon-fiber composite is highly anisotropic with a fiber-dominated 0/90° orientation and a matrix-dominated  $\pm 45^\circ$  orientation. The room-temperature 0/90° stiffness is more than four times the corresponding  $\pm 45^\circ$  value. This difference increases to almost seven times at 120°C.
- For the 0/90° fiber orientation, the room-temperature compressive strength, which is matrix-dominated, is only about 0.90 of the tensile strength, which is strongly fiber dominated. This difference increases with increasing temperature.
- For the  $\pm 45^\circ$  fiber orientation, the compressive strength is greater than the tensile strength over the temperature range, except near 120°C, where it drops below the tensile strength by about 1.2%.
- Basic properties at different temperatures were established for both fiber orientations. Temperature factors for determining baseline properties at different temperature from room-temperature values were provided.
- The  $\pm 45^\circ$  strength and stiffness increase with increasing strain rate. The 0/90° strength and stiffness appear to be relatively independent of strain rate.
- Effects of exposure in distilled water and windshield washer fluid were investigated. A stiffness reduction factor of 0.93 covers degrading effects for the two standard bounding fluid exposures, 1000 h in room-temperature distilled water and 100 h in windshield washer fluid.
- Uniaxial and biaxial flexure properties were established, effects of temperature and environment on flexure were assessed.

### 5.2 QUASI-ISOTROPIC CARBON-FIBER COMPOSITE

- Room-temperature stiffness values in tension and compression are comparable.
- Room-temperature tensile strength is approximately 1.5 times compressive strength. The low compressive strength is most likely due to specimen geometry. Thin compressive specimens are likely to fail in a buckling mode at a lower stress.
- Basic properties at different temperatures were established. Temperature factors for determining baseline properties at different temperature from room-temperature values were provided.
- Strain rate effects were found to be relatively small, except at the fastest rate examined.
- Prior thermal cycling was found to have a significant effect on matrix-dominated properties.
- The study of fluid effects revealed that the moisture absorption process reaches saturation at about 3000 h for both room-temperature distilled water and for 70% RH air.
- A single reduction factor of 0.94 can be used to bound the effects of both standard exposures (1000 h in room-temperature distilled water and 100 h in windshield washer fluid) on stiffness and strength.
- Uniaxial and biaxial flexure tests were conducted. Effects of temperature and environment on uniaxial and biaxial flexure were explored.

## REFERENCES

1. J. M. Corum, R. L. Battiste, W. Ren, and M. B. Ruggles, *Recommended Minimum Test Requirements and Test Methods for Assessing Durability of Random-Glass-Fiber Composites*, ORNL-6953, Oak Ridge National Laboratory, Oak Ridge, Tenn., 1999.
2. ASTM Standard D3410-87, *Standard Test Method for Compressive Properties of Unidirectional or Crossply Fiber-Resin Composites*, American Society for Testing and Materials.
3. ASTM Standard D 790, *Test Methods for Flexural Properties of Unreinforced and Reinforced Plastics and Electrical Insulating Materials*, American Society for Testing and Materials.
4. J. M. Corum, R. L. Battiste, S. Deng, K. C. Liu, M. B. Ruggles, and Y. J. Weitsman, *Durability-Based Design Properties of Reference Crossply Carbon-Fiber Composite*, ORNL/TM-2000/322, Oak Ridge National Laboratory, Oak Ridge, Tenn., 2000.
5. ASTM Standard D 2344, *Test Methods for Apparent Interlaminar Shear Strength of Parallel Fiber Composites by Short Beam Method*, American Society for Testing and Materials.
6. J. M. Corum, R. L. Battiste, S. Deng, M. B. Ruggles-Wrenn, and Y. J. Weitsman, *Durability-Based Design Criteria for a Quasi-Isotropic Carbon-Fiber Automotive Composite*, ORNL/TM-2002/39, Oak Ridge National Laboratory, Oak Ridge, Tenn., 2002.



**Table 1. Summary of room-temperature stiffness values for the crossply carbon-fiber composite, 0/90° fiber orientation**

| <b>Specimen number</b> | <b>Stiffness (GPa)</b> | <b>Specimen number</b> | <b>Stiffness (GPa)</b> | <b>Specimen number</b> | <b>Stiffness (GPa)</b> | <b>Specimen number</b> | <b>Stiffness (GPa)</b> |
|------------------------|------------------------|------------------------|------------------------|------------------------|------------------------|------------------------|------------------------|
| C1-1                   | 48.2                   | C2-11                  | 49.0                   | C3-22                  | 42.2                   | C4-33                  | 41.4                   |
| C1-2                   | 51.0                   | C2-12                  | 48.1                   | C3-23                  | 42.2                   | C4-34                  | 40.1                   |
| C1-3                   | 44.7                   | C2-13                  | 47.3                   | C3-24                  | 41.1                   | C4-35                  | 39.0                   |
| C1-4                   | 47.2                   | C2-14                  | 46.7                   | C3-25                  | 42.8                   | C4-36                  | 39.5                   |
| C1-5                   | 44.6                   | C2-15                  | 44.9                   | C3-26                  | 42.9                   | C5-1                   | 47.0                   |
| C1-6                   | 44.3                   | C2-16                  | 46.9                   | C3-27                  | 41.8                   | C5-2                   | 46.8                   |
| C1-7                   | 45.0                   | C2-17                  | 49.4                   | C3-28                  | 39.4                   | C5-3                   | 41.9                   |
| C1-8                   | 44.3                   | C2-18                  | 49.0                   | C3-29                  | 43.8                   | C5-4                   | 44.3                   |
| C1-9                   | 49.6                   | C2-19                  | 45.3                   | C3-30                  | 40.2                   | C5-5                   | 45.4                   |
| C1-10                  | 46.9                   | C2-20                  | 44.5                   | C3-31                  | 42.6                   | C5-6                   | 46.8                   |
| C1-11                  | 46.4                   | C2-21                  | 44.6                   | C3-32                  | 43.7                   | C5-7                   | 44.1                   |
| C1-12                  | 47.8                   | C2-22                  | 47.4                   | C3-33                  | 46.1                   | C5-8                   | 46.0                   |
| C1-13                  | 44.1                   | C2-23                  | 44.3                   | C3-34                  | 41.9                   | C5-9                   | 46.5                   |
| C1-14                  | 47.0                   | C2-24                  | 46.3                   | C3-35                  | 42.7                   | C5-10                  | 43.6                   |
| C1-15                  | 43.6                   | C2-25                  | 44.1                   | C3-36                  | 38.9                   | C5-11                  | 45.4                   |
| C1-16                  | 48.7                   | C2-26                  | 44.2                   | C4-1                   | 44.9                   | C5-12                  | 47.3                   |
| C1-17                  | 46.3                   | C2-27                  | 42.2                   | C4-2                   | 43.8                   | C5-13                  | 48.2                   |
| C1-18                  | 44.2                   | C2-28                  | 42.0                   | C4-3                   | 44.9                   | C5-14                  | 47.2                   |
| C1-19                  | 42.5                   | C2-29                  | 43.3                   | C4-4                   | 36.8                   | C5-15                  | 45.4                   |
| C1-20                  | 42.3                   | C2-30                  | 45.8                   | C4-5                   | 46.7                   | C5-16                  | 45.6                   |
| C1-21                  | 44.5                   | C2-31                  | 48.8                   | C4-6                   | 45.1                   | C5-17                  | 44.1                   |
| C1-22                  | 45.1                   | C2-32                  | 48.7                   | C4-7                   | 43.1                   | C5-18                  | 42.7                   |
| C1-23                  | 45.2                   | C2-33                  | 44.9                   | C4-8                   | 42.0                   | C5-19                  | 43.9                   |
| C1-24                  | 44.4                   | C2-34                  | 43.7                   | C4-9                   | 45.2                   | C5-20                  | 43.8                   |
| C1-25                  | 44.7                   | C2-35                  | 45.6                   | C4-10                  | 45.4                   | C5-21                  | 44.4                   |
| C1-26                  | 45.2                   | C2-36                  | 42.3                   | C4-11                  | 44.6                   | C5-22                  | 43.5                   |
| C1-27                  | 42.3                   | C3-1                   | 46.7                   | C4-12                  | 46.4                   | C5-23                  | 38.7                   |
| C1-28                  | 39.7                   | C3-2                   | 44.3                   | C4-13                  | 46.3                   | C5-24                  | 41.6                   |
| C1-29                  | 46.6                   | C3-3                   | 41.8                   | C4-14                  | 45.3                   | C5-25                  | 43.1                   |
| C1-30                  | 48.0                   | C3-4                   | 44.3                   | C4-15                  | 44.9                   | C5-26                  | 44.5                   |
| C1-31                  | 42.6                   | C3-5                   | 47.2                   | C4-16                  | 44.8                   | C5-27                  | 42.3                   |
| C1-32                  | 42.8                   | C3-6                   | 45.4                   | C4-17                  | 43.2                   | C5-28                  | 40.3                   |
| C1-33                  | 42.2                   | C3-7                   | 42.5                   | C4-18                  | 45.0                   | C5-29                  | 43.0                   |
| C1-34                  | 39.9                   | C3-8                   | 43.1                   | C4-19                  | 43.0                   | C5-30                  | 42.9                   |
| C1-35                  | 40.5                   | C3-9                   | 45.5                   | C4-20                  | 41.8                   | C5-31                  | 42.6                   |
| C1-36                  | 42.5                   | C3-10                  | 45.7                   | C4-21                  | 41.9                   | C5-32                  | 41.2                   |
| C1-D-28                | 40.8                   | C3-11                  | 46.3                   | C4-22                  | 37.9                   | C5-33                  | 42.3                   |
| C2-1                   | 52.5                   | C3-12                  | 50.1                   | C4-23                  | 40.0                   | C5-34                  | 43.3                   |
| C2-2                   | 48.2                   | C3-13                  | 48.8                   | C4-24                  | 40.0                   | C5-35                  | 42.4                   |
| C2-3                   | 50.3                   | C3-14                  | 47.2                   | C4-25                  | 40.6                   | C5-36                  | 40.3                   |
| C2-4                   | 48.5                   | C3-15                  | 43.9                   | C4-26                  | 44.0                   | C12-1                  | 46.2                   |
| C2-5                   | 45.7                   | C3-16                  | 46.4                   | C4-27                  | 41.6                   | C12-19                 | 41.3                   |
| C2-6                   | 47.8                   | C3-17                  | 43.1                   | C4-28                  | 39.0                   | C12-29                 | 44.4                   |
| C2-7                   | 42.5                   | C3-18                  | 46.1                   | C4-29                  | 43.0                   | C12-36                 | 40.9                   |
| C2-8                   | 44.4                   | C3-19                  | 43.5                   | C4-30                  | 40.7                   | C13-1                  | 41.7                   |
| C2-9                   | 46.4                   | C3-20                  | 43.7                   | C4-31                  | 36.5                   | C13-9                  | 45.6                   |
| C2-10                  | 49.2                   | C3-21                  | 39.5                   | C4-32                  | 38.8                   | C13-19                 | 36.5                   |

**Table 1. Summary of room-temperature stiffness values for the crossply carbon-fiber composite, 0/90° fiber orientation**

| <b>Specimen number</b> | <b>Stiffness (GPa)</b> | <b>Specimen number</b> | <b>Stiffness (GPa)</b> | <b>Specimen number</b> | <b>Stiffness (GPa)</b> | <b>Specimen number</b> | <b>Stiffness (GPa)</b> |
|------------------------|------------------------|------------------------|------------------------|------------------------|------------------------|------------------------|------------------------|
| C13-36                 | 37.5                   | C19-19                 | 49.1                   | C25-2                  | 50.5                   | C48-5                  | 48.8                   |
| C15-1                  | 49.3                   | C19-36                 | 43.2                   | C25-3                  | 51.5                   | C52-13                 | 44.9                   |
| C15-9                  | 46.4                   | C21-1                  | 48.7                   | C27-2                  | 52.5                   | C52-15                 | 49.2                   |
| C15-12                 | 49.0                   | C21-9                  | 50.3                   | C27-3                  | 51.2                   | C52-17                 | 49.7                   |
| C15-15                 | 56.8                   | C21-19                 | 50.0                   | C27-4                  | 47.5                   | C52-19                 | 44.5                   |
| C15-19                 | 46.3                   | C21-36                 | 53.7                   | C27-5                  | 50.0                   | C52-21                 | 47.2                   |
| C15-27                 | 51.2                   | C22-1                  | 49.3                   | C28-2                  | 50.4                   | C56-1                  | 44.1                   |
| C15-31                 | 49.3                   | C22-9                  | 50.3                   | C28-3                  | 50.2                   | C56-9                  | 46.7                   |
| C15-36                 | 42.7                   | C22-19                 | 49.8                   | C28-4                  | 51.4                   | C56-19                 | 49.6                   |
| C18-1                  | 46.0                   | C22-36                 | 44.5                   | C28-5                  | 51.2                   | C56-36                 | 48.7                   |
| C18-9                  | 49.2                   | C23-1                  | 47.0                   | C46-2                  | 51.0                   |                        |                        |
| C18-19                 | 42.0                   | C23-9                  | 49.2                   | C46-3                  | 48.7                   | <b>Average</b>         | 45.2                   |
| C18-36                 | 41.1                   | C23-19                 | 48.5                   | C46-4                  | 52.3                   | <b>SD</b>              | 3.76                   |
| C19-1                  | 68.7                   | C23-36                 | 48.9                   | C46-5                  | 45.8                   | <b>COV(%)</b>          | 8.33                   |
| C19-9                  | 46.8                   | C25-1                  | 48.3                   | C48-4                  | 50.5                   |                        |                        |

**Table 2. Summary of room-temperature stiffness values for the crossply carbon-fiber composite,  $\pm 45^\circ$  fiber orientation**

| <b>Specimen number</b> | <b>Stiffness (GPa)</b> | <b>Specimen number</b> | <b>Stiffness (GPa)</b> | <b>Specimen number</b> | <b>Stiffness (GPa)</b> |
|------------------------|------------------------|------------------------|------------------------|------------------------|------------------------|
| C6-6                   | 11.3                   | C32-7                  | 11.0                   | C44-3                  | 10.8                   |
| C6-29                  | 10.4                   | C33-1                  | 10.5                   | C44-5                  | 10.7                   |
| C6-53                  | 10.5                   | C33-3                  | 9.85                   | C44-7                  | 10.6                   |
| C9-3                   | 11.0                   | C33-5                  | 9.89                   | C45-1                  | 12.6                   |
| C9-29                  | 9.74                   | C33-7                  | 10.8                   | C45-3                  | 12.0                   |
| C9-56                  | 10.0                   | C34-1                  | 10.3                   | C45-5                  | 12.1                   |
| C9-58                  | 10.5                   | C34-3                  | 10.7                   | C45-7                  | 12.6                   |
| C11-3                  | 10.9                   | C34-5                  | 10.1                   | C46-1                  | 12.1                   |
| C11-18                 | 10.5                   | C34-7                  | 11.6                   | C46-6                  | 13.0                   |
| C11-29                 | 10.2                   | C35-1                  | 10.4                   | C46-7                  | 13.4                   |
| C11-30                 | 10.1                   | C35-3                  | 9.94                   | C46-8                  | 12.6                   |
| C11-41                 | 9.69                   | C35-5                  | 10.3                   | C48-1                  | 12.4                   |
| C11-56                 | 9.40                   | C35-7                  | 10.5                   | C48-2                  | 13.1                   |
| C14-3                  | 10.5                   | C36-1                  | 10.5                   | C48-3                  | 12.5                   |
| C14-6                  | 12.3                   | C36-3                  | 10.3                   | C52-1                  | 12.3                   |
| C14-15                 | 12.4                   | C36-5                  | 10.7                   | C52-3                  | 10.8                   |
| C14-29                 | 11.0                   | C36-7                  | 10.4                   | C52-5                  | 10.7                   |
| C14-44                 | 10.4                   | C37-1                  | 10.9                   | C52-7                  | 10.8                   |
| C14-56                 | 10.1                   | C37-3                  | 10.3                   | C52-9                  | 11.0                   |
| C16-3                  | 11.4                   | C37-5                  | 10.3                   | C52-11                 | 11.4                   |
| C16-29                 | 10.4                   | C37-7                  | 10.6                   | C57-3                  | 12.1                   |
| C16-56                 | 9.51                   | C38-1                  | 10.8                   | C57-29                 | 11.3                   |
| C17-3                  | 11.2                   | C38-3                  | 10.3                   | C57-56                 | 11.1                   |
| C17-29                 | 10.2                   | C38-5                  | 10.4                   |                        |                        |
| C17-56                 | 9.17                   | C38-7                  | 10.0                   | <b>Average</b>         | 11.3                   |
| C20-3                  | 13.8                   | C39-1                  | 11.4                   | <b>SD</b>              | 1.44                   |
| C20-29                 | 13.2                   | C39-3                  | 10.4                   | <b>COV(%)</b>          | 12.7                   |
| C20-56                 | 12.1                   | C39-5                  | 10.1                   |                        |                        |
| C24-3                  | 13.0                   | C39-7                  | 9.91                   |                        |                        |
| C24-29                 | 12.1                   | C40-1                  | 11.1                   |                        |                        |
| C24-56                 | 13.0                   | C40-3                  | 11.0                   |                        |                        |
| C26-3                  | 16.5                   | C40-5                  | 10.4                   |                        |                        |
| C26-56                 | 15.3                   | C40-7                  | 10.1                   |                        |                        |
| C27-1                  | 14.1                   | C41-1                  | 10.6                   |                        |                        |
| C27-6                  | 13.5                   | C41-3                  | 10.5                   |                        |                        |
| C27-7                  | 14.3                   | C41-5                  | 10.2                   |                        |                        |
| C27-8                  | 14.3                   | C41-7                  | 10.5                   |                        |                        |
| C28-6                  | 14.1                   | C42-1                  | 10.2                   |                        |                        |
| C28-7                  | 14.2                   | C42-3                  | 9.93                   |                        |                        |
| C28-8                  | 14.3                   | C42-5                  | 10.1                   |                        |                        |
| C31-1                  | 13.7                   | C42-7                  | 9.89                   |                        |                        |
| C31-2                  | 13.4                   | C43-1                  | 10.5                   |                        |                        |
| C31-6                  | 14.3                   | C43-3                  | 10.2                   |                        |                        |
| C32-1                  | 11.6                   | C43-5                  | 9.69                   |                        |                        |
| C32-3                  | 11.1                   | C43-7                  | 9.98                   |                        |                        |
| C32-5                  | 10.8                   | C44-1                  | 10.8                   |                        |                        |

**Table 3. Summary of room-temperature tensile properties of the crossply carbon-fiber composite, 0/90° fiber orientation**

| <b>Specimen number</b> | <b>UTS (MPa)</b> | <b>Failure strain (%)</b> | <b>Specimen number</b> | <b>UTS (MPa)</b> | <b>Failure strain (%)</b> |
|------------------------|------------------|---------------------------|------------------------|------------------|---------------------------|
| C1-9                   | 575              | 1.19                      | C56-1                  | 369              | -                         |
| C1-19                  | 462              | 0.95                      | C15-15                 | 478              | -                         |
| C1-36                  | 474              | 1.01                      | C15-19                 | 455              | 0.99                      |
| C1-11                  | 552              | 1.19                      | C15-27                 | 419              | -                         |
| C1-15                  | 551              | 1.17                      | C15-31                 | 465              | -                         |
| C1-31                  | 481              | 1.10                      | C15-36                 | 494              | 1.12                      |
| C1-21                  | 438              | 0.98                      | C18-1                  | 510              | 1.14                      |
| C1-22                  | 471              | 1.01                      | C18-9                  | 498              | 1.00                      |
| C1-25                  | 481              | 1.10                      | C18-19                 | 404              | 0.99                      |
| C1-27                  | 479              | 1.14                      | C18-36                 | 391              | 0.96                      |
| C2-1                   | 433              | 0.77                      | C19-1                  | 476              | 0.99                      |
| C2-9                   | 544              | 1.06                      | C19-9                  | 470              | 0.93                      |
| C2-19                  | 559              | 1.07                      | C19-19                 | 495              | 0.98                      |
| C2-36                  | 522              | 1.10                      | C19-36                 | 461              | 1.09                      |
| C3-1                   | 346              | 0.67                      | C21-1                  | 394              | 0.95                      |
| C3-9                   | 556              | 1.14                      | C21-9                  | 481              | 1.08                      |
| C3-19                  | 529              | 1.10                      | C21-19                 | 430              | 0.80                      |
| C3-36                  | 511              | 1.21                      | C21-36                 | 470              | 0.94                      |
| C4-1                   | 576              | 1.19                      | C22-1                  | 459              | 0.86                      |
| C4-9                   | 450              | 0.87                      | C22-9                  | 436              | 0.85                      |
| C4-19                  | 414              | 0.88                      | C22-19                 | 469              | 0.88                      |
| C4-36                  | 468              | 1.07                      | C22-36                 | 469              | 0.89                      |
| C5-1                   | 410              | 0.81                      | C23-1                  | 360              | 0.84                      |
| C5-9                   | 553              | 1.11                      | C23-9                  | 446              | 0.87                      |
| C5-19                  | 557              | 1.16                      | C23-19                 | 402              | 0.80                      |
| C5-36                  | 463              | 1.02                      | C23-36                 | 389              | 0.73                      |
| C5-2                   | 536              | 1.02                      | C25-1                  | 435              | 0.90                      |
| C5-3                   | 480              | 1.00                      | C25-2                  | 480              | 0.94                      |
| C5-8                   | 485              | 0.97                      | C25-3                  | 469              | 0.92                      |
| C12-1                  | 381              | 0.97                      | C27-2                  | 458              | 1.06                      |
| C12-19                 | 378              | 0.90                      | C27-3                  | 489              | 0.92                      |
| C12-29                 | 449              | 1.07                      | C27-4                  | 482              | 1.14                      |
| C12-36                 | 424              | 1.19                      | C27-5                  | 477              | 0.95                      |
| C13-1                  | 434              | 1.01                      | C28-2                  | 503              | 1.08                      |
| C13-9                  | 492              | 1.11                      | C28-3                  | 504              | 1.06                      |
| C13-19                 | 418              | 1.12                      | C28-4                  | 504              | 1.08                      |
| C13-36                 | 412              | 1.18                      | C28-5                  | 505              | 0.96                      |
| C15-1                  | 446              | 0.86                      | C46-2                  | 467              | -                         |
| C15-9                  | 494              | 0.99                      | C46-3                  | 478              | -                         |
| C15-12                 | 470              | -                         | C46-4                  | 484              | -                         |
| C48-4                  | 545              | -                         | C46-5                  | 475              | -                         |
| C48-5                  | 490              | -                         | C56-9                  | 440              | -                         |
| C52-13                 | 510              | -                         | C56-19                 | 441              | -                         |
| C52-15                 | 587              | -                         | C56-36                 | 385              | -                         |
| C52-17                 | 572              | -                         | <b>Average</b>         | 471              | 1.00                      |
| C52-19                 | 483              | -                         | <b>SD</b>              | 52.1             | 0.12                      |
| C52-21                 | 460              | -                         | <b>COV(%)</b>          | 11.1             | 12.3                      |

**Table 4. Summary of room-temperature tensile properties of the crossply carbon-fiber composite,  $\pm 45^\circ$  fiber orientation**

| <b>Specimen number</b> | <b>UTS (MPa)</b> | <b>Failure strain (%)</b> | <b>Specimen number</b> | <b>UTS (MPa)</b> | <b>Failure strain (%)</b> |
|------------------------|------------------|---------------------------|------------------------|------------------|---------------------------|
| C6-6                   | 132              | 15.0                      | C33-1                  | 143              | 6.60                      |
| C6-29                  | 132              | 14.4                      | C33-3                  | 154              | 9.92                      |
| C6-53                  | 133              | 10.6                      | C33-5                  | 148              | 9.00                      |
| C9-3                   | 141              | 10.0                      | C33-7                  | 166              | 9.41                      |
| C9-29                  | 148              | 10.0                      | C34-1                  | 125              | 7.45                      |
| C9-56                  | 129              | 10.6                      | C34-3                  | 142              | 9.38                      |
| C9-58                  | 135              | 12.0                      | C34-5                  | 130              | 13.4                      |
| C11-3                  | 124              | 12.9                      | C34-7                  | 163              | 10.4                      |
| C11-18                 | 127              | 14.2                      | C35-1                  | 149              | 13.3                      |
| C11-29                 | 134              | 15.0                      | C35-3                  | 157              | 8.96                      |
| C11-30                 | 132              | 9.51                      | C35-5                  | 166              | 10.8                      |
| C11-41                 | 120              | 15.0                      | C35-7                  | 159              | 6.08                      |
| C11-56                 | 121              | 11.0                      | C36-1                  | 158              | 11.7                      |
| C14-3                  | 131              | -                         | C36-3                  | 154              | 10.5                      |
| C14-6                  | 139              | -                         | C36-5                  | 168              | 11.7                      |
| C14-15                 | 139              | -                         | C36-7                  | 158              | 8.03                      |
| C14-29                 | 139              | -                         | C37-1                  | 148              | 11.1                      |
| C14-44                 | 123              | -                         | C37-3                  | 150              | 7.73                      |
| C14-56                 | 123              | -                         | C37-5                  | 148              | 12.3                      |
| C16-3                  | 117              | -                         | C37-7                  | 150              | 7.83                      |
| C16-29                 | 109              | -                         | C38-1                  | 164              | 11.1                      |
| C16-56                 | 110              | -                         | C38-3                  | 155              | 10.6                      |
| C17-3                  | 116              | -                         | C38-5                  | 147              | 10.7                      |
| C17-29                 | 107              | -                         | C38-7                  | 156              | 9.32                      |
| C17-56                 | 100              | -                         | C39-1                  | 162              | 9.93                      |
| C20-3                  | 127              | -                         | C39-3                  | 153              | 7.51                      |
| C20-29                 | 127              | -                         | C39-5                  | 160              | 8.76                      |
| C20-56                 | 126              | -                         | C39-7                  | 145              | 8.14                      |
| C24-3                  | 162              | 5.43                      | C40-1                  | 161              | 10.6                      |
| C24-29                 | 157              | 6.36                      | C40-3                  | 172              | 7.20                      |
| C24-56                 | 164              | 6.33                      | C40-5                  | 162              | 11.5                      |
| C26-3                  | 171              | -                         | C40-7                  | 157              | 8.98                      |
| C26-56                 | 175              | -                         | C41-1                  | 167              | 11.1                      |
| C27-1                  | 162              | -                         | C41-3                  | 161              | 11.1                      |
| C27-6                  | 157              | -                         | C41-5                  | 158              | 9.18                      |
| C27-7                  | 144              | -                         | C41-7                  | 166              | 8.36                      |
| C27-8                  | 149              | -                         | C42-1                  | 160              | 11.5                      |
| C28-6                  | 154              | -                         | C42-3                  | 155              | 9.33                      |
| C28-7                  | 152              | -                         | C42-5                  | 158              | 9.48                      |
| C28-8                  | 147              | -                         | C42-7                  | 162              | 8.92                      |
| C31-1                  | 150              | -                         | C43-1                  | 160              | 11.3                      |
| C31-2                  | 144              | -                         | C43-3                  | 160              | 8.87                      |
| C31-6                  | 152              | -                         | C43-5                  | 159              | 9.43                      |
| C32-1                  | 172              | 10.8                      | C43-7                  | 152              | 7.59                      |
| C32-3                  | 168              | 9.75                      | C44-1                  | 164              | 11.4                      |
| C32-5                  | 164              | 8.12                      | C44-3                  | 159              | 10.6                      |
| C32-7                  | 156              | 8.31                      | C44-5                  | 168              | 12.2                      |

**Table 4. Continued. Summary of room-temperature tensile properties of the crossply carbon-fiber composite,  $\pm 45^\circ$  fiber orientation**

| <b>Specimen number</b> | <b>UTS (MPa)</b> | <b>Failure strain (%)</b> |
|------------------------|------------------|---------------------------|
| C44-7                  | 163              | 8.92                      |
| C45-1                  | 145              | 5.20                      |
| C45-3                  | 149              | 4.73                      |
| C45-5                  | 157              | 4.56                      |
| C45-7                  | 153              | 5.37                      |
| C46-1                  | 150              | -                         |
| C46-6                  | 156              | -                         |
| C46-7                  | 164              | -                         |
| C46-8                  | 152              | -                         |
| C48-1                  | 152              | -                         |
| C48-2                  | 161              | -                         |
| C48-3                  | 161              | -                         |
| C52-1                  | 156              | -                         |
| C52-3                  | 163              | -                         |
| C52-5                  | 170              | -                         |
| C52-7                  | 170              | -                         |
| C52-9                  | 168              | -                         |
| C52-11                 | 165              | -                         |
| C57-3                  | 161              | -                         |
| C57-29                 | 155              | -                         |
| C57-56                 | 162              | -                         |
| <b>Average</b>         | 150              | 9.78                      |
| <b>SD</b>              | 16.2             | 2.43                      |
| <b>COV(%)</b>          | 10.8             | 24.8                      |

**Table 5. Summary of plaque average tensile properties of the crossply carbon-fiber composite, 0/90° fiber orientation**

| <b>Plaque number</b>   | <b>Number of stiffness tests</b> | <b>E<sub>avg</sub> (GPa)</b> | <b>Number of tensile tests</b> | <b>UTS<sub>avg</sub> (MPa)</b> | <b>ε<sub>f avg</sub> (%)</b> |
|------------------------|----------------------------------|------------------------------|--------------------------------|--------------------------------|------------------------------|
| C1                     | 37                               | 44.7                         | 10                             | 496                            | 1.07                         |
| C2                     | 36                               | 46.2                         | 4                              | 514                            | 1.00                         |
| C3                     | 36                               | 43.8                         | 4                              | 485                            | 1.03                         |
| C4                     | 36                               | 42.4                         | 4                              | 477                            | 1.00                         |
| C5                     | 36                               | 43.9                         | 7                              | 498                            | 1.01                         |
| C12                    | 4                                | 43.2                         | 4                              | 408                            | 1.03                         |
| C13                    | 4                                | 40.3                         | 4                              | 439                            | 1.11                         |
| C15                    | 8                                | 48.9                         | 8                              | 465                            | 0.99                         |
| C18                    | 4                                | 44.6                         | 4                              | 451                            | 1.02                         |
| C19                    | 4                                | 51.9                         | 4                              | 475                            | 1.00                         |
| C21                    | 4                                | 50.7                         | 4                              | 444                            | 0.94                         |
| C22                    | 4                                | 48.5                         | 4                              | 458                            | 0.87                         |
| C23                    | 4                                | 48.4                         | 4                              | 399                            | 0.81                         |
| C25                    | 3                                | 50.1                         | 3                              | 461                            | 0.92                         |
| C27                    | 4                                | 50.3                         | 4                              | 476                            | 1.02                         |
| C28                    | 4                                | 50.8                         | 4                              | 504                            | 1.05                         |
| C46                    | 4                                | 49.5                         | 4                              | 476                            | -                            |
| C48                    | 2                                | 49.7                         | 2                              | 518                            | -                            |
| C52                    | 5                                | 47.1                         | 5                              | 522                            | -                            |
| C56                    | 4                                | 47.3                         | 4                              | 409                            | -                            |
| <b>Number of tests</b> | 243                              |                              | 91                             |                                |                              |
| <b>Average</b>         |                                  | 45.2                         |                                | 471                            | 1.00                         |
| <b>SD</b>              |                                  | 3.76                         |                                | 52.1                           | 0.12                         |
| <b>COV %</b>           |                                  | 8.33                         |                                | 11.1                           | 12.3                         |

**Table 6. Summary of plaque average tensile properties the crossply carbon-fiber composite,  $\pm 45^\circ$  fiber orientation**

| Plaque number          | Number of stiffness tests | $E_{avg}$ (GPa) | Number of tensile tests | $UTS_{avg}$ (MPa) | $\epsilon_{f avg}$ (%) |
|------------------------|---------------------------|-----------------|-------------------------|-------------------|------------------------|
| C6                     | 3                         | 10.7            | 3                       | 132               | 13.3                   |
| C9                     | 4                         | 10.3            | 4                       | 139               | 10.7                   |
| C11                    | 6                         | 10.1            | 6                       | 126               | 12.9                   |
| C14                    | 6                         | 11.1            | 6                       | 133               | -                      |
| C16                    | 3                         | 10.4            | 3                       | 112               | -                      |
| C17                    | 3                         | 10.2            | 3                       | 107               | -                      |
| C20                    | 3                         | 13.1            | 3                       | 127               | -                      |
| C24                    | 3                         | 12.7            | 3                       | 161               | 6.04                   |
| C26                    | 2                         | 15.9            | 2                       | 173               | -                      |
| C27                    | 4                         | 14.1            | 4                       | 153               | -                      |
| C28                    | 3                         | 14.2            | 3                       | 151               | -                      |
| C31                    | 3                         | 13.8            | 3                       | 149               | -                      |
| C32                    | 4                         | 11.1            | 4                       | 165               | 9.24                   |
| C33                    | 4                         | 10.2            | 4                       | 153               | 8.73                   |
| C34                    | 4                         | 10.7            | 4                       | 140               | 10.2                   |
| C35                    | 4                         | 10.3            | 4                       | 158               | 9.79                   |
| C36                    | 4                         | 10.5            | 4                       | 160               | 10.5                   |
| C37                    | 4                         | 10.5            | 4                       | 149               | 9.73                   |
| C38                    | 4                         | 10.4            | 4                       | 156               | 10.4                   |
| C39                    | 4                         | 10.4            | 4                       | 155               | 8.59                   |
| C40                    | 4                         | 10.6            | 4                       | 163               | 9.57                   |
| C41                    | 4                         | 10.4            | 4                       | 163               | 9.94                   |
| C42                    | 4                         | 10.0            | 4                       | 159               | 9.81                   |
| C43                    | 4                         | 10.1            | 4                       | 158               | 9.30                   |
| C44                    | 4                         | 10.7            | 4                       | 163               | 10.8                   |
| C45                    | 4                         | 12.3            | 4                       | 151               | -                      |
| C46                    | 4                         | 12.8            | 4                       | 155               | -                      |
| C48                    | 3                         | 12.7            | 3                       | 158               | -                      |
| C52                    | 6                         | 11.2            | 6                       | 165               | -                      |
| C57                    | 3                         | 11.5            | 3                       | 159               | -                      |
| <b>Number of tests</b> | 115                       |                 | 115                     |                   |                        |
| <b>Average</b>         |                           | 11.3            |                         | 149               | 9.78                   |
| <b>SD</b>              |                           | 1.49            |                         | 16.3              | 2.43                   |
| <b>COV %</b>           |                           | 13.1            |                         | 10.9              | 24.8                   |



**Table 7. Summary of tensile tests at various strain rates for the crossply carbon-fiber composite, 0/90° fiber orientation**

| <b>Specimen number</b>                                   | <b>Stiffness (GPa)</b> | <b>UTS (MPa)</b> |
|--|------------------------|------------------|
| <b>Strain rate = <math>10^{-6} \text{ s}^{-1}</math></b> |                        |                  |
| C56-8  | 43.2                   | 388              |
| C56-13   | 45.1                   | 416              |
| C56-28   | 42.6                   | 453              |
| C56-35   | 49.4                   | 459              |
| <b>Average</b>   | 45.1                   | 429              |
| <b>SD</b>  | 3.10                   | 33.1             |
| <b>COV (%)</b>   | 6.87                   | 7.71             |
| <b>Strain rate = <math>10^{-4} \text{ s}^{-1}</math></b> |                        |                  |
| C56-7  | 41.6                   | 407              |
| C56-12   | 48.3                   | 426              |
| C56-27   | 46.4                   | 358              |
| C56-34   | 50.6                   | 426              |
| <b>Average</b>   | 46.7                   | 404              |
| <b>SD</b>  | 3.84                   | 32.3             |
| <b>COV (%)</b>   | 8.22                   | 7.99             |
| <b>Strain rate = <math>10^{-2} \text{ s}^{-1}</math></b> |                        |                  |
| C56-6  | 47.2                   | 351              |
| C56-11   | 49.7                   | 441              |
| C56-26   | 44.9                   | 481              |
| C56-33   | 50.5                   | 462              |
| <b>Average</b>   | 48.1                   | 434              |
| <b>SD</b>  | 2.54                   | 57.9             |
| <b>COV (%)</b>   | 5.29                   | 13.3             |
| <b>Strain rate = <math>10 \text{ s}^{-1}</math></b>      |                        |                  |
| C56-5  | 49.8                   | 355              |
| C56-10   | 48.7                   | 393              |
| C56-25   | 47.1                   | 357              |
| C56-32   | 47.0                   | 412              |
| <b>Average</b>   | 48.1                   | 379              |
| <b>SD</b>  | 1.36                   | 28.0             |
| <b>COV (%)</b>   | 2.83                   | 7.39             |

**Table 8. Summary of tensile tests at various strain rates for the crossply carbon-fiber composite,  $\pm 45^\circ$  fiber orientation**

| <b>Specimen number</b>                                   | <b>Stiffness (GPa)</b> | <b>UTS (MPa)</b> |
|--|------------------------|------------------|
| <b>Strain rate = <math>10^{-6} \text{ s}^{-1}</math></b> |                        |                  |
| C57-8  | 9.93                   | 139              |
| C57-20   | 10.2                   | 135              |
| C57-24   | 9.38                   | 145              |
| C57-55   | 9.86                   | 138              |
| <b>Average</b>   | 9.85                   | 139              |
| <b>SD</b>  | 0.34                   | 4.23             |
| <b>COV (%)</b>   | 3.50                   | 3.05             |
| <b>Strain rate = <math>10^{-4} \text{ s}^{-1}</math></b> |                        |                  |
| C57-7  | 10.4                   | 154              |
| C57-19   | 11.9                   | 149              |
| C57-54   | 9.52                   | 145              |
| C57-23   | 9.80                   | 149              |
| <b>Average</b>   | 10.4                   | 149              |
| <b>SD</b>  | 1.08                   | 3.46             |
| <b>COV (%)</b>   | 10.4                   | 2.32             |
| <b>Strain rate = <math>10^{-2} \text{ s}^{-1}</math></b> |                        |                  |
| C57-6  | 12.3                   | 170              |
| C57-18   | 10.7                   | 165              |
| C57-53   | 8.83                   | 162              |
| C57-22   | 10.9                   | 156              |
| <b>Average</b>   | 10.7                   | 163              |
| <b>SD</b>  | 1.42                   | 5.89             |
| <b>COV (%)</b>   | 13.3                   | 3.61             |
| <b>Strain rate = <math>10 \text{ s}^{-1}</math></b>      |                        |                  |
| C57-5  | 10.3                   | 191              |
| C57-17   | 11.4                   | 166              |
| C57-52   | 10.4                   | 192              |
| C57-21   | 9.72                   | 173              |
| <b>Average</b>   | 10.5                   | 177              |
| <b>SD</b>  | 0.87                   | 13.6             |
| <b>COV (%)</b>   | 8.24                   | 7.67             |

**Table 9. Summary of tensile tests at various temperatures for the crossply carbon-fiber composite, 0/90° fiber orientation**

| <b>Specimen number</b> | <b>Virgin stiffness (GPa)</b> | <b>Stiffness (GPa)</b> | <b>UTS (MPa)</b> | <b>Failure strain (%)</b> | <b>Stiffness factor</b> | <b>Strength factor</b> |
|------------------------|-------------------------------|------------------------|------------------|---------------------------|-------------------------|------------------------|
| <b>-40°C</b>           |                               |                        |                  |                           |                         |                        |
| C1-6                   | 44.3                          | 44.3                   | 521              | 1.12                      | 1.00                    | 1.05                   |
| C1-10                  | 47.0                          | 46.6                   | 549              | 1.11                      | 0.99                    | 1.11                   |
| C1-17                  | 46.3                          | 46.4                   | 544              | 1.18                      | 1.00                    | 1.10                   |
| C1-20                  | 42.3                          | 42.4                   | 477              | 1.09                      | 1.00                    | 0.96                   |
| C1-26                  | 45.2                          | 45.4                   | 472              | 1.00                      | 1.00                    | 0.95                   |
| C1-32                  | 42.8                          | 42.9                   | 483              | 1.10                      | 1.00                    | 0.97                   |
| <b>Average</b>         | 44.7                          | 44.7                   | 508              | 1.10                      | 1.00                    | 1.02                   |
| <b>SD</b>              | 1.88                          | 1.77                   | 34.7             | 0.06                      |                         |                        |
| <b>COV (%)</b>         | 4.20                          | 3.96                   | 6.84             | 5.30                      |                         |                        |
| <b>23°C</b>            |                               |                        |                  |                           |                         |                        |
| C1-9                   | 49.6                          | 49.6                   | 575              | 1.19                      | 1.00                    | 1.00                   |
| C1-19                  | 42.5                          | 42.5                   | 462              | 0.95                      | 1.00                    | 1.00                   |
| C1-36                  | 42.5                          | 42.5                   | 474              | 1.01                      | 1.00                    | 1.00                   |
| C1-11                  | 46.4                          | 46.4                   | 552              | 1.19                      | 1.00                    | 1.00                   |
| C1-15                  | 43.6                          | 43.6                   | 551              | 1.17                      | 1.00                    | 1.00                   |
| C1-31                  | 42.6                          | 42.6                   | 481              | 1.10                      | 1.00                    | 1.00                   |
| C5-2                   | 49.6                          | 49.6                   | 536              | 1.02                      | 1.00                    | 1.00                   |
| C5-3                   | 46.1                          | 46.1                   | 480              | 1.00                      | 1.00                    | 1.00                   |
| C5-8                   | 47.5                          | 47.5                   | 485              | 0.97                      | 1.00                    | 1.00                   |
| <b>Average</b>         | 45.6                          | 45.6                   | 511              | 1.07                      | 1.00                    | 1.00                   |
| <b>SD</b>              | 2.93                          | 2.93                   | 42.3             | 0.10                      |                         |                        |
| <b>COV (%)</b>         | 6.43                          | 6.43                   | 8.28             | 9.08                      |                         |                        |
| <b>50°C</b>            |                               |                        |                  |                           |                         |                        |
| C1-3                   | 44.7                          | 44.3                   | 506              | 1.09                      | 0.99                    | 1.02                   |
| C1-8                   | 44.3                          | 43.4                   | 484              | 1.05                      | 0.98                    | 0.98                   |
| C1-13                  | 44.1                          | 43.6                   | 498              | 1.10                      | 0.99                    | 1.00                   |
| C1-16                  | 48.7                          | 48.3                   | 525              | 1.07                      | 0.99                    | 1.06                   |
| C1-24                  | 44.4                          | 43.0                   | 491              | 1.24                      | 0.97                    | 0.99                   |
| C1-30                  | 48.0                          | 47.4                   | 515              | 1.14                      | 0.99                    | 1.04                   |
| C5-4                   | 50.9                          | 50.2                   | 503              | 0.96                      | 0.99                    | 1.01                   |
| C5-5                   | 47.0                          | 47.4                   | 454              | 0.92                      | 1.01                    | 0.91                   |
| C5-10                  | 47.4                          | 47.2                   | 476              | 0.98                      | 1.00                    | 0.96                   |
| <b>Average</b>         | 46.6                          | 46.1                   | 495              | 1.06                      | 0.99                    | 1.00                   |
| <b>SD</b>              | 2.39                          | 2.56                   | 21.4             | 0.10                      |                         |                        |
| <b>COV (%)</b>         | 5.12                          | 5.57                   | 4.33             | 9.27                      |                         |                        |

**Table 9. Continued. Summary of tensile tests at various temperatures for the crossply carbon-fiber composite, 0/90° fiber orientation**

| <b>Specimen number</b> | <b>Virgin stiffness (GPa)</b> | <b>Stiffness (GPa)</b> | <b>UTS (MPa)</b> | <b>Failure strain (%)</b> | <b>Stiffness factor</b> | <b>Strength factor</b> |
|------------------------|-------------------------------|------------------------|------------------|---------------------------|-------------------------|------------------------|
| <b>120°C</b>           |                               |                        |                  |                           |                         |                        |
| C1-4                   | 47.2                          | 40.7                   | 414              | 1.00                      | 0.86                    | 0.83                   |
| C1-12                  | 47.8                          | 43.5                   | 479              | 1.08                      | 0.91                    | 0.97                   |
| C1-18                  | 44.2                          | 36.4                   | 376              | 1.07                      | 0.82                    | 0.76                   |
| C1-23                  | 45.2                          | 40.1                   | 433              | 1.13                      | 0.89                    | 0.87                   |
| C1-29                  | 46.7                          | 41.3                   | 405              | 1.00                      | 0.88                    | 0.82                   |
| C1-34                  | 39.9                          | 36.9                   | 403              | 1.08                      | 0.92                    | 0.81                   |
| C5-7                   | 50.2                          | 47.1                   | 370              | 0.76                      | 0.94                    | 0.74                   |
| C5-8                   | 48.9                          | 44.3                   | 377              | 0.82                      | 0.91                    | 0.76                   |
| C5-11                  | 51.2                          | 47.5                   | 425              | 0.88                      | 0.93                    | 0.85                   |
| <b>Average</b>         | 46.8                          | 42.0                   | 409              | 0.98                      | 0.90                    | 0.82                   |
| <b>SD</b>              | 3.42                          | 3.98                   | 34.4             | 0.13                      |                         |                        |
| <b>COV (%)</b>         | 7.30                          | 9.49                   | 8.40             | 13.3                      |                         |                        |

**Table 10. Summary of tensile tests at various temperatures for the crossply carbon-fiber composite,  $\pm 45^\circ$  fiber orientation**

| <b>Specimen number</b> | <b>Virgin stiffness (GPa)</b> | <b>Stiffness (GPa)</b> | <b>UTS (MPa)</b> | <b>Failure strain (%)</b> | <b>Stiffness factor</b> | <b>Strength factor</b> |
|------------------------|-------------------------------|------------------------|------------------|---------------------------|-------------------------|------------------------|
| <b>-40°C</b>           |                               |                        |                  |                           |                         |                        |
| C11-5                  | 11.5                          | 14.5                   | 154              | 3.34                      | 1.27                    | 1.23                   |
| C11-16                 | 10.5                          | 13.9                   | 164              | 4.05                      | 1.32                    | 1.30                   |
| C11-26                 | 10.5                          | 13.5                   | 156              | 4.00                      | 1.29                    | 1.24                   |
| C11-33                 | 10.4                          | 13.7                   | 167              | 4.95                      | 1.32                    | 1.32                   |
| C11-43                 | 9.53                          | 11.7                   | 161              | 4.43                      | 1.23                    | 1.28                   |
| C11-54                 | 10.0                          | 12.5                   | 156              | 4.41                      | 1.25                    | 1.23                   |
| <b>Average</b>         | 10.4                          | 13.3                   | 160              | 4.20                      | 1.28                    | 1.27                   |
| <b>SD</b>              | 0.64                          | 1.02                   | 5.12             | 0.54                      |                         |                        |
| <b>COV (%)</b>         | 6.14                          | 7.64                   | 3.21             | 12.9                      |                         |                        |
| <b>23°C</b>            |                               |                        |                  |                           |                         |                        |
| C11-3                  | 10.9                          | 10.9                   | 124              | 12.9                      | 1.00                    | 1.00                   |
| C11-18                 | 10.5                          | 10.5                   | 127              | 14.2                      | 1.00                    | 1.00                   |
| C11-29                 | 10.2                          | 10.2                   | 134              | 15.0                      | 1.00                    | 1.00                   |
| C11-30                 | 10.1                          | 10.1                   | 132              | 9.51                      | 1.00                    | 1.00                   |
| C11-41                 | 9.69                          | 9.69                   | 120              | 15.0                      | 1.00                    | 1.00                   |
| C11-56                 | 9.40                          | 9.40                   | 121              | 11.0                      | 1.00                    | 1.00                   |
| <b>Average</b>         | 10.1                          | 10.1                   | 126              | 12.9                      | 1.00                    | 1.00                   |
| <b>SD</b>              | 0.56                          | 0.56                   | 5.76             | 2.28                      |                         |                        |
| <b>COV (%)</b>         | 5.49                          | 5.49                   | 4.56             | 17.6                      |                         |                        |
| <b>70°C</b>            |                               |                        |                  |                           |                         |                        |
| C11-4                  | 11.1                          | 9.65                   | 102              | 13.7                      | 0.87                    | 0.81                   |
| C11-17                 | 10.7                          | 9.51                   | 104              | -                         | 0.89                    | 0.83                   |
| C11-28                 | 10.5                          | 8.89                   | 108              | -                         | 0.85                    | 0.85                   |
| C11-31                 | 10.3                          | 8.96                   | 105              | -                         | 0.87                    | 0.83                   |
| C11-42                 | 9.30                          | 8.14                   | 107              | -                         | 0.87                    | 0.85                   |
| C11-55                 | 9.88                          | 8.20                   | 103              | -                         | 0.83                    | 0.82                   |
| C11-8                  | 11.3                          | 9.9                    | 110              | 13.9                      | 0.88                    | 0.87                   |
| C11-14                 | 10.9                          | 9.65                   | 109              | 15.4                      | 0.88                    | 0.86                   |
| C11-23                 | 10.4                          | 8.87                   | 96.9             | 18.4                      | 0.85                    | 0.77                   |
| C11-36                 | 10.0                          | 8.76                   | 104              | 15.3                      | 0.87                    | 0.83                   |
| C11-45                 | 9.76                          | 8.09                   | 110              | 14.4                      | 0.83                    | 0.87                   |
| C11-52                 | 9.82                          | 8.73                   | 107              | 14.8                      | 0.89                    | 0.85                   |
| <b>Average</b>         | 10.3                          | 8.95                   | 105              | 15.1                      | 0.87                    | 0.84                   |
| <b>SD</b>              | 0.60                          | 0.63                   | 3.67             | 1.57                      |                         |                        |
| <b>COV (%)</b>         | 5.82                          | 6.99                   | 3.49             | 10.4                      |                         |                        |

**Table 10. Continued. Summary of tensile tests at various temperatures for the crossply carbon-fiber composite,  $\pm 45^\circ$  fiber orientation**

| <b>Specimen Number</b> | <b>Virgin stiffness (GPa)</b> | <b>Stiffness (GPa)</b> | <b>UTS (MPa)</b> | <b>Failure Strain (%)</b> | <b>Stiffness factor</b> | <b>Strength factor</b> |
|------------------------|-------------------------------|------------------------|------------------|---------------------------|-------------------------|------------------------|
| <b>120°C</b>           |                               |                        |                  |                           |                         |                        |
| C11-9                  | 11.5                          | 4.16                   | 82.7             | 17.0                      | 0.36                    | 0.66                   |
| C11-15                 | 11.5                          | 4.07                   | 72.8             | 17.7                      | 0.36                    | 0.58                   |
| C11-24                 | 10.0                          | 3.99                   | 71.3             | 19.7                      | 0.40                    | 0.57                   |
| C11-37                 | 9.99                          | 4.24                   | 71.6             | 16.5                      | 0.42                    | 0.57                   |
| C11-46                 | 9.61                          | 3.85                   | 79.7             | 20.0                      | 0.40                    | 0.63                   |
| C11-53                 | 9.55                          | 3.54                   | 75.3             | 21.1                      | 0.37                    | 0.60                   |
| <b>Average</b>         | 10.3                          | 3.98                   | 75.5             | 18.7                      | 0.39                    | 0.60                   |
| <b>SD</b>              | 0.89                          | 0.25                   | 4.67             | 1.87                      |                         |                        |
| <b>COV (%)</b>         | 8.56                          | 6.41                   | 6.18             | 10.0                      |                         |                        |

**Table 11. Temperature multiplication factors for determining at-temperature tensile modulus and strength from room-temperature values for the crossply carbon-fiber composite, 0/90° fiber orientation**

| <b>Temperature (°C)</b> | <b>Stiffness factor</b> | <b>Strength factor</b> |
|-------------------------|-------------------------|------------------------|
| <b>-40</b>              | 1.00                    | 1.00                   |
| <b>23</b>               | 1.00                    | 1.00                   |
| <b>70</b>               | 0.98                    | 0.96                   |
| <b>120</b>              | 0.90                    | 0.82                   |

**Table 12. Temperature multiplication factors for determining at-temperature tensile modulus and strength from room-temperature values for the crossply carbon-fiber composite,  $\pm 45^\circ$  fiber orientation**

| <b>Temperature (°C)</b> | <b>Stiffness factor</b> | <b>Strength factor</b> |
|-------------------------|-------------------------|------------------------|
| <b>-40</b>              | 1.29                    | 1.29                   |
| <b>23</b>               | 1.00                    | 1.00                   |
| <b>70</b>               | 0.79                    | 0.79                   |
| <b>120</b>              | 0.55                    | 0.55                   |

**Table 13. Summary of Poisson's ratio measurements at different temperatures for the crossply carbon-fiber composite, 0/90° fiber orientation**

| Specimen number | Poisson's ratio |      |      |       |
|-----------------|-----------------|------|------|-------|
|                 | -40°C           | 23°C | 70°C | 120°C |
| C12-15          | 0.06            | 0.06 | 0.04 | 0.04  |
| C12-18          | 0.03            | 0.04 | 0.03 | 0.05  |
| C12-34          | 0.05            | 0.05 | 0.05 | 0.03  |
| <b>Average</b>  | 0.05            | 0.05 | 0.04 | 0.04  |

**Table 14. Summary of Poisson's ratio measurements at different temperatures for the crossply carbon-fiber composite, ±45° fiber orientation**

| Specimen number | Poisson's ratio |      |      |       |
|-----------------|-----------------|------|------|-------|
|                 | -40°C           | 23°C | 70°C | 120°C |
| C11-13          | 0.68            | 0.77 | 0.74 | 0.84  |
| C11-25          | 0.71            | 0.77 | 0.73 | 0.90  |
| C11-39          | 0.70            | 0.74 | 0.74 | 0.86  |
| <b>Average</b>  | 0.70            | 0.76 | 0.74 | 0.87  |

**Table 15. Effects of prior thermal cycling on mechanical properties of the crossply carbon-fiber composite, 0/90° fiber orientation**

| <b>Specimen number</b> | <b>Virgin stiffness (GPa)</b> | <b>Stiffness (GPa)</b> | <b>Strength (MPa)</b> | <b>Stiffness factor</b> | <b>Strength factor</b> |
|------------------------|-------------------------------|------------------------|-----------------------|-------------------------|------------------------|
| <b>Tension</b>         |                               |                        |                       |                         |                        |
| C52-14                 | 50.0                          | 46.1                   | 543                   | 0.92                    | 1.02                   |
| C52-16                 | 49.4                          | 47.1                   | 570                   | 0.95                    | 1.08                   |
| C52-18                 | 46.3                          | 45.6                   | 515                   | 0.98                    | 0.97                   |
| C52-20                 | 44.7                          | 43.7                   | 453                   | 0.98                    | 0.86                   |
| C52-22                 | 43.6                          | 45.3                   | 518                   | 1.04                    | 0.98                   |
| C52-23                 | 49.3                          | 47.3                   | 519                   | 0.96                    | 0.98                   |
| <b>Average</b>         | 47.2                          | 45.8                   | 520                   | 0.97                    | 0.93                   |
| <b>SD</b>              | 2.69                          | 1.31                   | 38.7                  |                         |                        |
| <b>COV (%)</b>         | 5.70                          | 2.87                   | 7.45                  |                         |                        |
| <b>Compression</b>     |                               |                        |                       |                         |                        |
| C25-5                  | -                             | 64.9                   | 344                   | 1.10                    | 1.04                   |
| C25-8                  | -                             | 56.5                   | 322                   | 0.96                    | 0.98                   |
| C25-10                 | -                             | 55.2                   | 339                   | 0.93                    | 1.03                   |
| C25-29                 | -                             | 60.5                   | 314                   | 1.02                    | 0.95                   |
| C25-34                 |                               | 60.8                   | 336                   | 1.03                    | 1.02                   |
| C25-38                 |                               | 58.3                   | 343                   | 0.99                    | 1.04                   |
| <b>Average</b>         | -                             | 59.4                   | 333                   | 1.00                    | 1.01                   |
| <b>SD</b>              | -                             | 3.48                   | 12.4                  |                         |                        |
| <b>COV (%)</b>         | -                             | 5.86                   | 3.72                  |                         |                        |



**Table 16. Effects of prior thermal cycling on mechanical properties of the crossply carbon-fiber composite,  $\pm 45^\circ$  fiber orientation**

| <b>Specimen number</b> | <b>Virgin stiffness (GPa)</b> | <b>Stiffness (GPa)</b> | <b>Strength (MPa)</b> | <b>Stiffness factor</b> | <b>Strength factor</b> |
|------------------------|-------------------------------|------------------------|-----------------------|-------------------------|------------------------|
| <b>Tension</b>         |                               |                        |                       |                         |                        |
| C52-2                  | 10.5                          | 10.1                   | 161                   | 0.96                    | 0.97                   |
| C52-4                  | 11.3                          | 9.31                   | 161                   | 0.82                    | 0.98                   |
| C52-6                  | 12.1                          | 10.5                   | 170                   | 0.87                    | 1.03                   |
| C52-8                  | 12.4                          | 10.8                   | 184                   | 0.87                    | 1.12                   |
| C52-10                 | 11.7                          | 8.48                   | 166                   | 0.72                    | 1.01                   |
| C52-12                 | 12.1                          | 9.93                   | 164                   | 0.82                    | 1.00                   |
| <b>Average</b>         | 11.7                          | 9.85                   | 168                   | 0.85                    | 1.02                   |
| <b>SD</b>              | 0.69                          | 0.84                   | 8.69                  |                         |                        |
| <b>COV (%)</b>         | 5.95                          | 8.58                   | 5.19                  |                         |                        |
| <b>Compression</b>     |                               |                        |                       |                         |                        |
| C26-12                 | -                             | 12.6                   | 172                   | 0.91                    | 1.05                   |
| C26-23                 | -                             | 13.6                   | 171                   | 0.98                    | 1.05                   |
| C26-35                 | -                             | 14.9                   | 173                   | 1.07                    | 1.06                   |
| C26-38                 | -                             | 13.0                   | 174                   | 0.94                    | 1.07                   |
| C26-45                 |                               | 14.7                   | 178                   | 1.06                    | 1.09                   |
| C26-70                 |                               | 14.1                   | 172                   | 1.02                    | 1.05                   |
| <b>Average</b>         | -                             | 13.8                   | 173                   | 1.00                    | 1.06                   |
| <b>SD</b>              | -                             | 0.92                   | 2.50                  |                         |                        |
| <b>COV (%)</b>         | -                             | 6.66                   | 1.44                  |                         |                        |

**Table 17. Effects of prior thermal cycling on apparent shear strength in short-beam shear of the crossply carbon-fiber composite, 0/90° fiber orientation\***

| <b>Specimen number</b>                              | <b>Apparent shear strength (MPa)</b> | <b>Strength factor</b> |
|---|--------------------------------------|------------------------|
| <b>Unexposed specimens</b>                          |                                      |                        |
| 1   | 88.9                                 | 1.00                   |
| 4   | 93.8                                 | 1.00                   |
| 15  | 86.2                                 | 1.00                   |
| 19  | 97.9                                 | 1.00                   |
| 28  | 93.8                                 | 1.00                   |
| 40  | 95.8                                 | 1.00                   |
| 44  | 88.9                                 | 1.00                   |
| 49  | 89.6                                 | 1.00                   |
| 53  | 92.4                                 | 1.00                   |
| 61  | 93.1                                 | 1.00                   |
| <b>Average</b>                                      | 92.0                                 | 1.00                   |
| <b>SD</b>   | 3.58                                 |                        |
| <b>COV (%)</b>                                      | 3.89                                 |                        |
| <b>Specimens subjected to prior thermal cycling</b> |                                      |                        |
| 21  | 82.7                                 | 0.90                   |
| 23  | 81.4                                 | 0.88                   |
| 26  | 83.4                                 | 0.90                   |
| 51  | 88.3                                 | 0.96                   |
| 63  | 88.3                                 | 0.96                   |
| 69  | 84.1                                 | 0.91                   |
| <b>Average</b>                                      | 84.7                                 | 0.92                   |
| <b>SD</b>   | 2.91                                 |                        |
| <b>COV (%)</b>                                      | 3.43                                 |                        |

\*All specimens machined from plaque C23.

**Table 18. Effects of prior thermal cycling on apparent shear strength in short-beam shear of the crossply carbon-fiber composite,  $\pm 45^\circ$  fiber orientation\***

| <b>Specimen number</b>                              | <b>Apparent shear strength (MPa)</b> | <b>Strength factor</b> |
|---|--------------------------------------|------------------------|
| <b>Unexposed specimens</b>                          |                                      |                        |
| 1   | 76.5                                 | 1.00                   |
| 4   | 73.1                                 | 1.00                   |
| 15  | 77.2                                 | 1.00                   |
| 19  | 74.5                                 | 1.00                   |
| 28  | 79.3                                 | 1.00                   |
| 40  | 75.8                                 | 1.00                   |
| 44  | 78.6                                 | 1.00                   |
| 49  | 76.5                                 | 1.00                   |
| 53  | 82.7                                 | 1.00                   |
| 61  | 77.2                                 | 1.00                   |
| <b>Average</b>                                      | 77.2                                 | 1.00                   |
| <b>SD</b>   | 2.67                                 |                        |
| <b>COV (%)</b>                                      | 3.46                                 |                        |
| <b>Specimens subjected to prior thermal cycling</b> |                                      |                        |
| 21  | 73.7                                 | 0.95                   |
| 23  | 75.9                                 | 0.98                   |
| 26  | 74.1                                 | 0.96                   |
| 51  | 75.8                                 | 0.98                   |
| 63  | 74.4                                 | 0.96                   |
| 69  | 78.4                                 | 1.02                   |
| <b>Average</b>                                      | 75.4                                 | 0.98                   |
| <b>SD</b>   | 1.73                                 |                        |
| <b>COV (%)</b>                                      | 2.29                                 |                        |

\*All specimens machined from plaque C23.

**Table 19. Effects of fluid environments on apparent shear strength in short-beam shear of the crossply carbon-fiber composite, 0/90° fiber orientation\***

| <b>Specimen number</b>         | <b>Apparent shear strength (MPa)</b> | <b>Strength factor</b> |
|--------------------------------|--------------------------------------|------------------------|
| <b>Distilled water</b>         |                                      |                        |
| 2                              | 85.5                                 | 0.93                   |
| 16                             | 89.6                                 | 0.97                   |
| 30                             | 82.7                                 | 0.90                   |
| 41                             | 89.6                                 | 0.97                   |
| 50                             | 88.3                                 | 0.96                   |
| 60                             | 88.9                                 | 0.96                   |
| <b>Average</b>                 | 87.4                                 | 0.95                   |
| <b>SD</b>                      | 2.77                                 |                        |
| <b>COV (%)</b>                 | 3.17                                 |                        |
| <b>Saltwater</b>               |                                      |                        |
| 3                              | 86.9                                 | 0.94                   |
| 17                             | 82.7                                 | 0.90                   |
| 31                             | 87.6                                 | 0.95                   |
| 42                             | 84.8                                 | 0.92                   |
| 48                             | 84.1                                 | 0.91                   |
| 59                             | 84.1                                 | 0.91                   |
| <b>Average</b>                 | 85.0                                 | 0.92                   |
| <b>SD</b>                      | 1.83                                 |                        |
| <b>COV (%)</b>                 | 2.16                                 |                        |
| <b>Windshield washer fluid</b> |                                      |                        |
| 18                             | 88.3                                 | 0.96                   |
| 25                             | 91.7                                 | 0.99                   |
| 32                             | 91.0                                 | 0.99                   |
| 43                             | 82.7                                 | 0.90                   |
| 47                             | 95.8                                 | 1.04                   |
| 58                             | 81.4                                 | 0.88                   |
| <b>Average</b>                 | 88.5                                 | 0.96                   |
| <b>SD</b>                      | 5.56                                 |                        |
| <b>COV (%)</b>                 | 6.29                                 |                        |

\*All specimens machined from plaque C23.

**Table 19. Continued. Effects of fluid environments on apparent shear strength in short-beam shear of the crossply carbon-fiber composite, 0/90° fiber orientation\***

| <b>Specimen number</b> | <b>Apparent shear strength (MPa)</b> | <b>Strength factor</b> |
|------------------------|--------------------------------------|------------------------|
| <b>Coolant</b>         |                                      |                        |
| 5                      | 93.1                                 | 1.01                   |
| 12                     | 75.8                                 | 0.82                   |
| 29                     | 96.5                                 | 1.04                   |
| 39                     | 88.3                                 | 0.96                   |
| 54                     | 82.0                                 | 0.89                   |
| 57                     | 86.2                                 | 0.93                   |
| <b>Average</b>         | 87.0                                 | 0.94                   |
| <b>SD</b>              | 7.47                                 |                        |
| <b>COV (%)</b>         | 8.59                                 |                        |
| <b>Motor oil</b>       |                                      |                        |
| 6                      | 82.7                                 | 0.90                   |
| 13                     | 91.7                                 | 0.99                   |
| 27                     | 85.5                                 | 0.93                   |
| 38                     | 95.1                                 | 1.03                   |
| 55                     | 91.0                                 | 0.99                   |
| 56                     | 89.6                                 | 0.97                   |
| <b>Average</b>         | 89.3                                 | 0.97                   |
| <b>SD</b>              | 4.48                                 |                        |
| <b>COV (%)</b>         | 5.02                                 |                        |
| <b>Gasoline</b>        |                                      |                        |
| 7                      | 95.1                                 | 1.03                   |
| 10                     | 93.1                                 | 1.01                   |
| 35                     | 90.3                                 | 0.98                   |
| 37                     | 91.0                                 | 0.99                   |
| 52                     | 91.7                                 | 0.99                   |
| 67                     | 95.1                                 | 1.03                   |
| <b>Average</b>         | 92.7                                 | 1.00                   |
| <b>SD</b>              | 2.08                                 |                        |
| <b>COV (%)</b>         | 2.24                                 |                        |
| <b>Brake fluid</b>     |                                      |                        |
| 8                      | 84.1                                 | 0.91                   |
| 11                     | 91.0                                 | 0.99                   |
| 34                     | 86.9                                 | 0.94                   |
| 36                     | 85.5                                 | 0.93                   |
| 62                     | 88.9                                 | 0.96                   |
| 64                     | 72.4                                 | 0.78                   |
| <b>Average</b>         | 84.8                                 | 0.92                   |
| <b>SD</b>              | 6.56                                 |                        |
| <b>COV (%)</b>         | 7.73                                 |                        |

\*All specimens machined from plaque C23.

**Table 19. Continued. Effects of fluid environments on apparent shear strength in short-beam shear of the crossply carbon-fiber composite, 0/90° fiber orientation\***

| <b>Specimen number</b>    | <b>Apparent shear strength (MPa)</b> | <b>Strength factor</b> |
|---------------------------|--------------------------------------|------------------------|
| <b>Transmission fluid</b> |                                      |                        |
| 9                         | 84.1                                 | 0.91                   |
| 14                        | 80.0                                 | 0.87                   |
| 33                        | 85.5                                 | 0.93                   |
| 45                        | 91.0                                 | 0.99                   |
| 46                        | 93.8                                 | 1.01                   |
| 65                        | 84.1                                 | 0.91                   |
| <b>Average</b>            | 86.4                                 | 0.94                   |
| <b>SD</b>                 | 5.06                                 |                        |
| <b>COV (%)</b>            | 5.86                                 |                        |
| <b>Battery acid</b>       |                                      |                        |
| 20                        | 85.5                                 | 0.93                   |
| 22                        | 85.5                                 | 0.93                   |
| 24                        | 91.7                                 | 0.99                   |
| 66                        | 91.0                                 | 0.99                   |
| 68                        | 95.8                                 | 1.04                   |
| 70                        | 95.1                                 | 1.03                   |
| <b>Average</b>            | 90.8                                 | 0.98                   |
| <b>SD</b>                 | 4.50                                 |                        |
| <b>COV (%)</b>            | 4.96                                 |                        |

\*All specimens machined from plaque C23.

**Table 20. Effects of fluid environments on apparent shear strength in short-beam shear of the crossply carbon-fiber composite,  $\pm 45^\circ$  fiber orientation\***

| <b>Specimen number</b>         | <b>Apparent shear strength (MPa)</b> | <b>Strength factor</b> |
|--------------------------------|--------------------------------------|------------------------|
| <b>Distilled water</b>         |                                      |                        |
| 2                              | 73.8                                 | 0.96                   |
| 16                             | 72.4                                 | 0.94                   |
| 30                             | 73.8                                 | 0.96                   |
| 41                             | 77.9                                 | 1.01                   |
| 50                             | 74.5                                 | 0.96                   |
| 60                             | 69.6                                 | 0.90                   |
| <b>Average</b>                 | 73.7                                 | 0.95                   |
| <b>SD</b>                      | 2.70                                 |                        |
| <b>COV (%)</b>                 | 3.67                                 |                        |
| <b>Saltwater</b>               |                                      |                        |
| 3                              | 78.6                                 | 1.02                   |
| 17                             | 75.2                                 | 0.97                   |
| 31                             | 69.6                                 | 0.90                   |
| 42                             | 71.7                                 | 0.93                   |
| 48                             | 80.0                                 | 1.04                   |
| 59                             | 71.0                                 | 0.92                   |
| <b>Average</b>                 | 74.3                                 | 0.96                   |
| <b>SD</b>                      | 4.26                                 |                        |
| <b>COV (%)</b>                 | 5.73                                 |                        |
| <b>Windshield washer fluid</b> |                                      |                        |
| 18                             | 71.7                                 | 0.93                   |
| 25                             | 79.3                                 | 1.03                   |
| 32                             | 69.6                                 | 0.90                   |
| 43                             | 71.0                                 | 0.92                   |
| 47                             | 68.9                                 | 0.89                   |
| 58                             | 71.0                                 | 0.92                   |
| <b>Average</b>                 | 71.9                                 | 0.93                   |
| <b>SD</b>                      | 3.74                                 |                        |
| <b>COV (%)</b>                 | 5.20                                 |                        |
| <b>Coolant</b>                 |                                      |                        |
| 5                              | 77.9                                 | 1.01                   |
| 12                             | 67.6                                 | 0.88                   |
| 29                             | 73.1                                 | 0.95                   |
| 39                             | 74.5                                 | 0.96                   |
| 54                             | 75.8                                 | 0.98                   |
| 57                             | 69.6                                 | 0.90                   |
| <b>Average</b>                 | 73.1                                 | 0.95                   |
| <b>SD</b>                      | 3.88                                 |                        |
| <b>COV (%)</b>                 | 5.30                                 |                        |

\*All specimens machined from plaque C23.

**Table 20. Continued. Effects of fluid environments on apparent shear strength in short-beam shear of the crossply carbon-fiber composite,  $\pm 45^\circ$  fiber orientation\***

| <b>Specimen number</b>    | <b>Apparent shear strength (MPa)</b> | <b>Strength factor</b> |
|---------------------------|--------------------------------------|------------------------|
| <b>Motor oil</b>          |                                      |                        |
| 6                         | 71.7                                 | 0.93                   |
| 13                        | 75.2                                 | 0.97                   |
| 27                        | 71.7                                 | 0.93                   |
| 38                        | 66.2                                 | 0.86                   |
| 55                        | 68.3                                 | 0.88                   |
| 56                        | 73.8                                 | 0.96                   |
| <b>Average</b>            | 71.1                                 | 0.92                   |
| <b>SD</b>                 | 3.36                                 |                        |
| <b>COV (%)</b>            | 4.73                                 |                        |
| <b>Gasoline</b>           |                                      |                        |
| 7                         | 77.9                                 | 1.01                   |
| 10                        | 75.8                                 | 0.98                   |
| 35                        | 73.1                                 | 0.95                   |
| 37                        | 80.0                                 | 1.04                   |
| 52                        | 78.6                                 | 1.02                   |
| 67                        | 73.8                                 | 0.96                   |
| <b>Average</b>            | 76.5                                 | 0.99                   |
| <b>SD</b>                 | 2.76                                 |                        |
| <b>COV (%)</b>            | 3.60                                 |                        |
| <b>Brake fluid</b>        |                                      |                        |
| 8                         | 74.5                                 | 0.96                   |
| 11                        | 66.9                                 | 0.87                   |
| 34                        | 68.9                                 | 0.89                   |
| 36                        | 73.1                                 | 0.95                   |
| 62                        | 66.9                                 | 0.87                   |
| 64                        | 73.1                                 | 0.95                   |
| <b>Average</b>            | 70.6                                 | 0.91                   |
| <b>SD</b>                 | 3.40                                 |                        |
| <b>COV (%)</b>            | 4.81                                 |                        |
| <b>Transmission fluid</b> |                                      |                        |
| 9                         | 66.0                                 | 0.85                   |
| 14                        | 68.5                                 | 0.89                   |
| 33                        | 76.5                                 | 0.99                   |
| 45                        | 77.9                                 | 1.01                   |
| 46                        | 71.0                                 | 0.92                   |
| 65                        | 73.1                                 | 0.95                   |
| <b>Average</b>            | 72.2                                 | 0.93                   |
| <b>SD</b>                 | 4.61                                 |                        |
| <b>COV (%)</b>            | 6.39                                 |                        |

\*All specimens machined from plaque C23.



**Table 20. Continued. Effects of fluid environments on apparent shear strength in short-beam shear of the crossply carbon-fiber composite,  $\pm 45^\circ$  fiber orientation\***

| <b>Specimen number</b> | <b>Apparent shear strength (MPa)</b> | <b>Strength factor</b> |
|------------------------|--------------------------------------|------------------------|
| <b>Battery acid</b>    |                                      |                        |
| 20                     | 71.2                                 | 0.92                   |
| 22                     | 64.9                                 | 0.84                   |
| 24                     | 68.0                                 | 0.88                   |
| 66                     | 69.4                                 | 0.90                   |
| 68                     | 68.1                                 | 0.88                   |
| 70                     | 67.3                                 | 0.87                   |
| <b>Average</b>         | 68.1                                 | 0.88                   |
| <b>SD</b>              | 2.10                                 |                        |
| <b>COV (%)</b>         | 3.09                                 |                        |

\*All specimens machined from plaque C23.

**Table 21. Effect of exposure in 23°C distilled water and in 70% RH air on tensile strength and stiffness of the crossply carbon-fiber composite, 0/90° fiber orientation**

| <b>Specimen number</b>         | <b>Virgin stiffness (GPa)</b> | <b>Stiffness (GPa)</b> | <b>UTS (MPa)</b> | <b>Change in stiffness (%)</b> | <b>Change in strength (%)</b> |
|--------------------------------|-------------------------------|------------------------|------------------|--------------------------------|-------------------------------|
| <b>Distilled water, 1000 h</b> |                               |                        |                  |                                |                               |
| C12-2                          | 47.5                          | 45.5                   | 396              | -4.21                          | -2.71                         |
| C12-9                          | 41.2                          | 37.0                   | 368              | -10.2                          | -9.64                         |
| C12-20                         | 39.4                          | 39.0                   | 384              | -1.22                          | -5.75                         |
| C21-2                          | 68.2                          | 62.1                   | 439              | -8.90                          | -1.09                         |
| C21-20                         | 64.3                          | 61.0                   | 432              | -5.14                          | -2.49                         |
| C21-29                         | 70.3                          | 65.5                   | 434              | -6.86                          | -2.02                         |
| <b>Average</b>                 | 55.2                          | 51.7                   | 409              | -6.09                          | -3.95                         |
| <b>SD</b>                      | 14.0                          | 12.7                   | 30.0             |                                |                               |
| <b>COV (%)</b>                 | 25.4                          | 24.5                   | 7.34             |                                |                               |
| <b>Distilled water, 4241 h</b> |                               |                        |                  |                                |                               |
| C12-4                          | 46.3                          | 43.9                   | 381              | -5.36                          | -6.50                         |
| C12-8                          | 44.9                          | 42.1                   | 364              | -6.14                          | -10.7                         |
| C12-35                         | 42.4                          | 39.2                   | 384              | -7.48                          | -5.69                         |
| C21-8                          | 61.4                          | 56.2                   | 423              | -8.53                          | -4.51                         |
| C21-18                         | 70.7                          | 63.6                   | 423              | -10.1                          | -4.53                         |
| C21-35                         | 67.8                          | 62.3                   | 415              | -8.14                          | -6.35                         |
| <b>Average</b>                 | 55.6                          | 51.2                   | 398              | -7.63                          | -6.38                         |
| <b>SD</b>                      | 12.5                          | 10.8                   | 25.4             |                                |                               |
| <b>COV (%)</b>                 | 22.6                          | 21.0                   | 6.38             |                                |                               |
| <b>70% RH, 3968 h</b>          |                               |                        |                  |                                |                               |
| C12-6                          | 43.6                          | 43.2                   | 436              | -1.11                          | 6.94                          |
| C12-13                         | 42.0                          | 41.9                   | 447              | -0.33                          | 9.81                          |
| C12-25                         | 41.9                          | 41.6                   | 444              | -0.49                          | 8.97                          |
| C21-6                          | 68.3                          | 67.8                   | 405              | -0.61                          | -8.71                         |
| C21-13                         | 65.2                          | 64.4                   | 408              | -1.3                           | -7.93                         |
| C21-25                         | 61.0                          | 60.5                   | 407              | -0.90                          | -8.24                         |
| <b>Average</b>                 | 53.7                          | 53.2                   | 424              | -0.78                          | 0.14                          |
| <b>SD</b>                      | 12.5                          | 12.3                   | 20.0             |                                |                               |
| <b>COV (%)</b>                 | 23.2                          | 23.1                   | 4.72             |                                |                               |

**Table 22. Effect of exposure in 23°C distilled water and in 70% RH air on tensile strength and stiffness of the crossply carbon-fiber composite,  $\pm 45^\circ$  fiber orientation**

| <b>Specimen number</b>         | <b>Virgin stiffness (GPa)</b> | <b>Stiffness (GPa)</b> | <b>UTS (MPa)</b> | <b>Change in stiffness (%)</b> | <b>Change in strength (%)</b> |
|--------------------------------|-------------------------------|------------------------|------------------|--------------------------------|-------------------------------|
| <b>Distilled water, 1000 h</b> |                               |                        |                  |                                |                               |
| C14-4                          | 12.2                          | 11.4                   | 132              | -6.21                          | 0.00                          |
| C14-14                         | 11.6                          | 11.2                   | 134              | -2.98                          | 1.04                          |
| C14-28                         | 11.2                          | 11.0                   | 127              | -2.45                          | -4.17                         |
| C14-35                         | 10.6                          | 9.79                   | 124              | -7.79                          | -6.25                         |
| C14-43                         | 11.4                          | 11.1                   | 125              | -2.42                          | -5.73                         |
| C14-55                         | 10.3                          | 10.1                   | 125              | -2.67                          | -5.73                         |
| <b>Average</b>                 | 11.2                          | 10.8                   | 128              | -4.09                          | -3.47                         |
| <b>SD</b>                      | 0.67                          | 0.67                   | 4.22             |                                |                               |
| <b>COV (%)</b>                 | 5.98                          | 6.27                   | 3.30             |                                |                               |
| <b>Distilled water, 4267 h</b> |                               |                        |                  |                                |                               |
| C14-1                          | 12.6                          | 12.1                   | 125              | -4.37                          | -5.21                         |
| C14-13                         | 11.8                          | 11.5                   | 132              | -2.34                          | -0.52                         |
| C14-25                         | 11.6                          | 11.2                   | 122              | -2.98                          | -7.81                         |
| C14-36                         | 10.4                          | 10.0                   | 118              | -3.97                          | -10.9                         |
| C14-40                         | 10.2                          | 9.79                   | 111              | -4.05                          | -16.1                         |
| C14-53                         | 11.3                          | 10.0                   | 120              | -11.6                          | -9.38                         |
| <b>Average</b>                 | 11.3                          | 10.8                   | 121              | -4.88                          | -8.33                         |
| <b>SD</b>                      | 0.90                          | 0.96                   | 7.00             |                                |                               |
| <b>COV (%)</b>                 | 7.95                          | 8.91                   | 5.77             |                                |                               |
| <b>70% RH, 4271 h</b>          |                               |                        |                  |                                |                               |
| C14-10                         | 12.0                          | 11.3                   | 121              | -5.75                          | -8.85                         |
| C14-12                         | 11.2                          | 11.3                   | 121              | 1.23                           | -8.33                         |
| C14-26                         | 11.1                          | 10.6                   | 123              | -4.35                          | -6.77                         |
| C14-37                         | 10.3                          | 10.5                   | 122              | 2.01                           | -7.81                         |
| C14-41                         | 10.5                          | 10.3                   | 127              | -1.32                          | -4.17                         |
| C14-51                         | 11.0                          | 10.3                   | 126              | -5.7                           | -4.69                         |
| <b>Average</b>                 | 11.0                          | 10.7                   | 123              | -2.30                          | -6.77                         |
| <b>SD</b>                      | 0.61                          | 0.46                   | 2.58             |                                |                               |
| <b>COV (%)</b>                 | 5.51                          | 4.25                   | 2.09             |                                |                               |

**Table 23. Effect of 1000-h distilled water exposure and 1000-h distilled water exposure followed by freezing on stiffness and strength of the crossply carbon-fiber composite, 0/90° fiber orientation**

| <b>Specimen number</b>                                | <b>Virgin stiffness (GPa)</b> | <b>Stiffness (GPa)</b> | <b>UTS (MPa)</b> | <b>Change in stiffness (%)</b> | <b>Change in strength (%)</b> |
|---|-------------------------------|------------------------|------------------|--------------------------------|-------------------------------|
| <b>1000 h in distilled water</b>                      |                               |                        |                  |                                |                               |
| C15-10  | 49.8                          | 48.5                   | 496              | -2.77                          | 5.11                          |
| C15-13  | 51.0                          | 48.0                   | 495              | -5.95                          | 4.82                          |
| C15-16  | 53.2                          | 50.3                   | 554              | -5.32                          | 17.4                          |
| C15-28  | 46.7                          | 44.1                   | 438              | -5.61                          | -7.30                         |
| C15-32  | 48.6                          | 45.6                   | 433              | -6.10                          | -8.32                         |
| C15-35  | 46.8                          | 44.5                   | 453              | -5.01                          | -4.09                         |
| <b>Average</b>  | 49.4                          | 46.8                   | 478              | -5.12                          | 1.27                          |
| <b>SD</b>   | 2.52                          | 2.49                   | 46.3             |                                |                               |
| <b>COV (%)</b>  | 5.10                          | 5.31                   | 9.68             |                                |                               |
| <b>1000 h in distilled water followed by freezing</b> |                               |                        |                  |                                |                               |
| C15-11  | 52.4                          | 47.7                   | 489              | -8.95                          | 3.50                          |
| C15-14  | 52.9                          | 50.5                   | 554              | -4.43                          | 17.4                          |
| C15-17  | 50.5                          | 51.9                   | 480              | 2.73                           | 1.61                          |
| C15-30  | 46.6                          | 44.5                   | 471              | -4.44                          | -0.29                         |
| C15-33  | 45.4                          | 42.7                   | 432              | -5.93                          | -8.61                         |
| C15-34  | 47.2                          | 45.9                   | 455              | -2.78                          | -3.65                         |
| <b>Average</b>  | 49.2                          | 47.2                   | 480              | -3.97                          | 1.65                          |
| <b>SD</b>   | 3.20                          | 3.55                   | 41.6             |                                |                               |
| <b>COV (%)</b>  | 6.51                          | 7.52                   | 8.66             |                                |                               |

**Table 24. Effect of 1000-h distilled water exposure and 1000-h distilled water exposure followed by freezing on stiffness and strength of the crossply carbon-fiber composite,  $\pm 45^\circ$  fiber orientation**

| <b>Specimen number</b>                                | <b>Virgin stiffness (GPa)</b> | <b>Stiffness (GPa)</b> | <b>UTS (MPa)</b> | <b>Change in stiffness (%)</b> | <b>Change in strength (%)</b> |
|---|-------------------------------|------------------------|------------------|--------------------------------|-------------------------------|
| <b>1000 h in distilled water</b>                      |                               |                        |                  |                                |                               |
| C17-18  | 8.83                          | 9.31                   | 101              | 5.47                           | -9.26                         |
| C17-21  | 9.79                          | 8.62                   | 98.6             | -12.0                          | -11.7                         |
| C17-24  | 10.0                          | 9.03                   | 102              | -9.66                          | -8.64                         |
| C17-47  | 8.55                          | 7.86                   | 95.8             | -8.06                          | -14.2                         |
| C17-50  | 11.0                          | 10.7                   | 124              | -2.52                          | 11.1                          |
| C17-53  | 11.1                          | 9.93                   | 132              | -10.6                          | 18.5                          |
| <b>Average</b>  | 9.87                          | 9.24                   | 109              | -6.22                          | -2.37                         |
| <b>SD</b>   | 1.06                          | 0.99                   | 15.3             |                                |                               |
| <b>COV (%)</b>  | 10.7                          | 10.7                   | 14.0             |                                |                               |
| <b>1000 h in distilled water followed by freezing</b> |                               |                        |                  |                                |                               |
| C17-19  | 9.65                          | 9.24                   | 112              | -4.29                          | 0.00                          |
| C17-20  | 9.58                          | 8.96                   | 106              | -6.47                          | -4.94                         |
| C17-23  | 9.72                          | 9.03                   | 108              | -7.09                          | -3.70                         |
| C17-46  | 8.14                          | 7.58                   | 101              | -6.78                          | -9.88                         |
| C17-49  | 8.96                          | 8.48                   | 110              | -5.38                          | -1.23                         |
| C17-52  | 8.62                          | 8.69                   | 112              | 0.80                           | 0.00                          |
| <b>Average</b>  | 9.11                          | 8.66                   | 108              | -4.87                          | -3.29                         |
| <b>SD</b>   | 0.65                          | 0.59                   | 4.24             |                                |                               |
| <b>COV (%)</b>  | 7.12                          | 6.84                   | 3.93             |                                |                               |

**Table 25. Effect of exposure in windshield washer fluid on tensile strength and stiffness of the crossply carbon-fiber composite, 0/90° fiber orientation**

| <b>Specimen number</b>        | <b>Virgin stiffness (GPa)</b> | <b>Stiffness (GPa)</b> | <b>UTS (MPa)</b> | <b>Stiffness factor</b> | <b>Strength factor</b> |
|-------------------------------|-------------------------------|------------------------|------------------|-------------------------|------------------------|
| <b>Exposure time = 50 h</b>   |                               |                        |                  |                         |                        |
| C12-17                        | 45.5                          | 45.0                   | 419              | 0.99                    | 1.03                   |
| C12-27                        | 36.2                          | 36.6                   | 392              | 1.01                    | 0.96                   |
| C21-4                         | 63.8                          | 63.4                   | 454              | 0.99                    | 1.02                   |
| C21-15                        | 62.5                          | 61.9                   | 443              | 0.99                    | 1.00                   |
| C21-27                        | 58.1                          | 57.0                   | 429              | 0.98                    | 0.97                   |
| <b>Average</b>                | 53.2                          | 52.8                   | 427              | 0.99                    | 1.00                   |
| <b>SD</b>                     | 12.0                          | 11.6                   | 23.8             |                         |                        |
| <b>COV (%)</b>                | 22.5                          | 21.9                   | 5.58             |                         |                        |
| <b>Exposure time = 100 h</b>  |                               |                        |                  |                         |                        |
| C12-24                        | 43.2                          | 43.0                   | 416              | 1.00                    | 1.02                   |
| C12-33                        | 39.5                          | 40.4                   | 390              | 1.02                    | 0.96                   |
| C21-17                        | 65.6                          | 61.8                   | 406              | 0.94                    | 0.92                   |
| C21-28                        | 56.4                          | 56.1                   | 461              | 1.00                    | 1.04                   |
| C21-32                        | 63.1                          | 63.6                   | 422              | 1.01                    | 0.95                   |
| <b>Average</b>                | 53.6                          | 53.0                   | 419              | 0.99                    | 0.98                   |
| <b>SD</b>                     | 11.7                          | 10.7                   | 26.5             |                         |                        |
| <b>COV (%)</b>                | 21.9                          | 20.2                   | 6.31             |                         |                        |
| <b>Exposure time = 1000 h</b> |                               |                        |                  |                         |                        |
| C19-2                         | 51.6                          | 51.2                   | 547              | 0.99                    | 1.15                   |
| C19-4                         | 51.7                          | 50.7                   | 561              | 0.98                    | 1.18                   |
| C19-5                         | 59.1                          | 57.6                   | 589              | 0.97                    | 1.24                   |
| C19-21                        | 49.8                          | 48.1                   | 519              | 0.97                    | 1.09                   |
| C19-22                        | 50.0                          | 48.7                   | 507              | 0.97                    | 1.07                   |
| C19-23                        | 51.8                          | 51.6                   | 540              | 1.00                    | 1.13                   |
| <b>Average</b>                | 52.3                          | 51.3                   | 544              | 0.98                    | 1.14                   |
| <b>SD</b>                     | 3.43                          | 3.38                   | 29.3             |                         |                        |
| <b>COV (%)</b>                | 6.56                          | 6.60                   | 5.38             |                         |                        |

**Table 26. Effect of exposure in windshield washer fluid on tensile strength and stiffness of the crossply carbon-fiber composite,  $\pm 45^\circ$  fiber orientation**

| <b>Specimen number</b>        | <b>Virgin stiffness (GPa)</b> | <b>Stiffness (GPa)</b> | <b>UTS (MPa)</b> | <b>Stiffness factor</b> | <b>Strength factor</b> |
|-------------------------------|-------------------------------|------------------------|------------------|-------------------------|------------------------|
| <b>Exposure time = 50 h</b>   |                               |                        |                  |                         |                        |
| C11-1                         | 12.2                          | 12.3                   | 126              | 1.01                    | 1.00                   |
| C11-35                        | 11.6                          | 11.5                   | 125              | 0.99                    | 0.99                   |
| C11-47                        | 10.3                          | 10.3                   | 125              | 1.00                    | 0.99                   |
| C11-49                        | 10.0                          | 9.72                   | 125              | 0.97                    | 0.99                   |
| C11-50                        | 10.9                          | 10.8                   | 124              | 0.99                    | 0.98                   |
| <b>Average</b>                | 11.0                          | 10.9                   | 125              | 0.99                    | 0.99                   |
| <b>SD</b>                     | 0.90                          | 1.00                   | 0.79             |                         |                        |
| <b>COV (%)</b>                | 8.18                          | 9.10                   | 0.63             |                         |                        |
| <b>Exposure time = 100 h</b>  |                               |                        |                  |                         |                        |
| C11-22                        | 11.7                          | 11.2                   | 122              | 0.95                    | 0.97                   |
| C11-38                        | 11.7                          | 11.1                   | 124              | 0.95                    | 0.98                   |
| C11-44                        | 10.3                          | 10.3                   | 125              | 0.99                    | 0.99                   |
| C11-48                        | 10.6                          | 9.93                   | 119              | 0.94                    | 0.95                   |
| C11-51                        | 10.9                          | 10.2                   | 125              | 0.94                    | 0.99                   |
| C11-58                        | 10.6                          | 10.4                   | 121              | 0.98                    | 0.96                   |
| <b>Average</b>                | 11.0                          | 10.5                   | 123              | 0.96                    | 0.97                   |
| <b>SD</b>                     | 0.60                          | 0.51                   | 2.47             |                         |                        |
| <b>COV (%)</b>                | 5.42                          | 4.81                   | 2.01             |                         |                        |
| <b>Exposure time = 1000 h</b> |                               |                        |                  |                         |                        |
| C57-4                         | 12.4                          | 10.5                   | 154              | 0.85                    | 0.97                   |
| C57-13                        | 11.1                          | 9.65                   | 157              | 0.87                    | 0.99                   |
| C57-26                        | 10.5                          | 9.58                   | 155              | 0.91                    | 0.97                   |
| C57-34                        | 10.5                          | 10.1                   | 158              | 0.97                    | 0.99                   |
| C57-41                        | 11.2                          | 9.86                   | 149              | 0.88                    | 0.94                   |
| C57-50                        | 10.1                          | 9.79                   | 154              | 0.97                    | 0.97                   |
| <b>Average</b>                | 11.0                          | 9.93                   | 155              | 0.91                    | 0.97                   |
| <b>SD</b>                     | 0.81                          | 0.36                   | 3.19             |                         |                        |
| <b>COV (%)</b>                | 7.37                          | 3.62                   | 2.06             |                         |                        |

**Table 27. Summary of room-temperature compressive tests for the crossply carbon-fiber composite**

| <b>Specimen number</b>         | <b>Compressive stiffness (GPa)</b> | <b>UCS (MPa)</b> | <b>Failure strain (%)</b> |
|--------------------------------|------------------------------------|------------------|---------------------------|
| <b>0/90° fiber orientation</b> |                                    |                  |                           |
| C4-C2                          | 50.9                               | -452             | -1.00                     |
| C4-C3                          | 51.6                               | -442             | -0.75                     |
| C4-C4                          | 56.1                               | -478             | -1.18                     |
| C4-C5                          | 57.5                               | -535             | -1.09                     |
| C4-C8                          | 43.8                               | -491             | -1.15                     |
| C4-C9                          | 43.9                               | -441             | -1.24                     |
| C5-C2                          | 50.7                               | -517             | -1.03                     |
| C5-C3                          | 48.8                               | -507             | -1.09                     |
| C5-C5                          | 53.5                               | -505             | -1.41                     |
| C5-C6                          | 44.7                               | -456             | -1.37                     |
| C5-C8                          | 53.1                               | -479             | -1.25                     |
| C5-C9                          | 50.8                               | -435             | -0.83                     |
| C25-2                          | 64.1                               | -355             | <sup>a</sup>              |
| C25-17                         | 58.1                               | -338             | <sup>a</sup>              |
| C25-32                         | 50.8                               | -324             | <sup>a</sup>              |
| C25-36                         | 67.0                               | -312             | <sup>a</sup>              |
| C25-41                         | 59.4                               | -336             | <sup>a</sup>              |
| C25-47                         | 55.1                               | -313             | <sup>a</sup>              |
| <b>Average</b>                 | 53.3                               | -429             | -1.12                     |
| <b>SD</b>                      | 6.39                               | 77.4             | 0.20                      |
| <b>COV (%)</b>                 | 12.0                               | -18.1            | -17.7                     |
| <b>±45° fiber orientation</b>  |                                    |                  |                           |
| C26-4                          | 15.6                               | 170              | 5.42                      |
| C26-14                         | 14.0                               | 163              | 8.01                      |
| C26-27                         | 14.2                               | 165              | 7.41                      |
| C26-41                         | 13.4                               | 151              | 8.37                      |
| C26-52                         | 13.2                               | 157              | 8.74                      |
| C26-61                         | 12.9                               | 170              | 5.57                      |
| <b>Average</b>                 | 13.9                               | 163              | 7.25                      |
| <b>SD</b>                      | 0.98                               | 7.47             | 1.43                      |
| <b>COV (%)</b>                 | 7.08                               | 4.59             | 19.7                      |

<sup>a</sup> No strain measurement



**Table 28. Compressive properties of the crossply carbon-fiber composite, 0/90° fiber orientation, at different temperatures**

| <b>Specimen number</b> | <b>Compressive stiffness (GPa)</b> | <b>UCS (MPa)</b> | <b>Failure strain (%)</b> |
|------------------------|------------------------------------|------------------|---------------------------|
| <b>50°C</b>            |                                    |                  |                           |
| C2-C1                  | 50.9                               | -370             | -0.78                     |
| C2-C4                  | 48.7                               | -342             | -0.71                     |
| C2-C7                  | 49.4                               | -411             | -0.63                     |
| C2-C9                  | 46.6                               | -392             | -0.70                     |
| C3-C1                  | 51.8                               | -381             | -0.79                     |
| C3-C2                  | 42.3                               | -419             | -0.69                     |
| C3-C3                  | 39.6                               | -362             | -0.66                     |
| C3-C7                  | 47.7                               | -247             | -0.74                     |
| <b>Average</b>         | 47.1                               | -365             | -0.71                     |
| <b>SD</b>              | 4.20                               | 54.4             | 0.06                      |
| <b>COV (%)</b>         | 8.92                               | 14.9             | 7.85                      |
| <b>120°C</b>           |                                    |                  |                           |
| C2-C3                  | 45.8                               | -162             | -0.25                     |
| C2-C5                  | 51.6                               | -222             | -0.41                     |
| C2-C8                  | 37.3                               | -171             | -0.52                     |
| C2-C10                 | 40.6                               | -193             | -0.50                     |
| C3-C4                  | 33.9                               | -230             | -0.71                     |
| C3-C6                  | 41.3                               | -177             | -0.39                     |
| C3-C8                  | 49.0                               | -176             | -0.29                     |
| C3-C9                  | 38.4                               | -185             | -0.54                     |
| <b>Average</b>         | 42.2                               | -190             | -0.45                     |
| <b>SD</b>              | 6.09                               | 24.6             | 0.15                      |
| <b>COV (%)</b>         | 14.4                               | 13.0             | 33.1                      |
| <b>-40°C</b>           |                                    |                  |                           |
| C2-C2                  | 51.9                               | -515             | -0.98                     |
| C2-C6                  | 42.5                               | -474             | -1.16                     |
| C3-C5                  | 46.4                               | -472             | -0.91                     |
| C3-C10                 | 42.1                               | -475             | -1.15                     |
| C4-C1                  | 42.5                               | -484             | -1.12                     |
| C4-C10                 | 34.7                               | -468             | -1.21                     |
| C5-C1                  | 51.6                               | -500             | -0.95                     |
| C5-C10                 | 41.0                               | -483             | -1.04                     |
| <b>Average</b>         | 43.5                               | -480             | -1.07                     |
| <b>SD</b>              | 6.21                               | 12.7             | 0.13                      |
| <b>COV (%)</b>         | 14.3                               | 2.64             | 12.2                      |

**Table 29. Compressive properties of the crossply carbon-fiber composite,  $\pm 45^\circ$  fiber orientation, at different temperatures**

| <b>Specimen number</b> | <b>Compressive stiffness (GPa)</b> | <b>UCS (MPa)</b> | <b>Failure strain (%)</b> |
|------------------------|------------------------------------|------------------|---------------------------|
| <b>70°C</b>            |                                    |                  |                           |
| C26-2                  | 11.8                               | 130              | 7.41                      |
| C26-15                 | 10.6                               | 121              | 9.68                      |
| C26-28                 | 9.79                               | 120              | 9.09                      |
| C26-42                 | 11.2                               | 127              | 6.23                      |
| C26-53                 | 10.3                               | 121              | 8.58                      |
| C26-62                 | 10.9                               | 105              | 9.48                      |
| <b>Average</b>         | 10.8                               | 121              | 8.41                      |
| <b>SD</b>              | 0.70                               | 8.61             | 1.34                      |
| <b>COV (%)</b>         | 6.47                               | 7.12             | 16.0                      |
| <b>120°C</b>           |                                    |                  |                           |
| C26-6                  | 6.32                               | 78.1             | 9.41                      |
| C26-16                 | 6.76                               | 76.5             | 8.36                      |
| C26-60                 | 6.18                               | 79.1             | 7.75                      |
| C26-43                 | 6.69                               | 76.5             | 9.55                      |
| C26-54                 | 5.67                               | 80.3             | 7.08                      |
| C26-63                 | 5.83                               | 78.0             | 8.14                      |
| <b>Average</b>         | 6.24                               | 78.1             | 8.38                      |
| <b>SD</b>              | 0.44                               | 1.47             | 0.96                      |
| <b>COV (%)</b>         | 7.06                               | 1.88             | 11.4                      |
| <b>-40°C</b>           |                                    |                  |                           |
| C26-7                  | 16.5                               | 209              | 2.63                      |
| C26-17                 | 17.8                               | 217              | 2.88                      |
| C26-31                 | 17.2                               | 213              | 3.46                      |
| C26-44                 | 16.8                               | 226              | 2.86                      |
| C26-51                 | 17.3                               | 219              | 3.04                      |
| C26-60                 | 18.3                               | 208              | 3.52                      |
| <b>Average</b>         | 17.3                               | 215              | 3.07                      |
| <b>SD</b>              | 0.65                               | 6.97             | 0.35                      |
| <b>COV (%)</b>         | 3.75                               | 3.23             | 11.6                      |

**Table 30. Temperature multiplication factors for determining at-temperature compressive modulus and strength from room-temperature values for the crossply carbon-fiber composite, 0/90° fiber orientation**

| <b>Temperature<br/>(°C)</b> | <b>Stiffness multiplication<br/>factor</b> | <b>Strength multiplication<br/>factor</b> |
|-----------------------------|--|---|
| <b>-40</b>                  | 1.05                                       | 1.10                                      |
| <b>23</b>                   | 1.00                                       | 1.00                                      |
| <b>70</b>                   | 0.93                                       | 0.78                                      |
| <b>120</b>                  | 0.80                                       | 0.41                                      |

**Table 31. Temperature multiplication factors for determining at-temperature compressive modulus and strength from room-temperature values for the crossply carbon-fiber composite, ±45° fiber orientation**

| <b>Temperature<br/>(°C)</b> | <b>Stiffness multiplication<br/>factor</b> | <b>Strength multiplication<br/>factor</b> |
|-----------------------------|--|---|
| <b>-40</b>                  | 1.32                                       | 1.32                                      |
| <b>23</b>                   | 1.00                                       | 1.00                                      |
| <b>70</b>                   | 0.76                                       | 0.76                                      |
| <b>120</b>                  | 0.50                                       | 0.50                                      |

**Table 32. Effects of 1000-h exposure in 23°C distilled water on room-temperature compressive properties of the crossply carbon-fiber composite**

| <b>Specimen number</b>         | <b>Compressive stiffness (GPa)</b> | <b>UCS (MPa)</b> | <b>Stiffness factor</b> | <b>Strength factor</b> |
|--------------------------------|------------------------------------|------------------|-------------------------|------------------------|
| <b>0/90° fiber orientation</b> |                                    |                  |                         |                        |
| C25-4                          | 54.7                               | 338              | 0.93                    | 1.02                   |
| C25-13                         | 56.7                               | 316              | 0.96                    | 0.96                   |
| C25-20                         | 58.0                               | 320              | 0.98                    | 0.97                   |
| C25-33                         | 54.4                               | 324              | 0.92                    | 0.98                   |
| C25-42                         | 57.4                               | 339              | 0.97                    | 1.03                   |
| C25-48                         | 52.9                               | 311              | 0.89                    | 0.94                   |
| <b>Average</b>                 | 55.7                               | 325              | 0.94                    | 0.98                   |
| <b>SD</b>                      | 1.99                               | 11.4             |                         |                        |
| <b>COV (%)</b>                 | 3.58                               | 3.52             |                         |                        |
| <b>±45° fiber orientation</b>  |                                    |                  |                         |                        |
| C26-1                          | 14.2                               | 164              | 1.03                    | 1.01                   |
| C26-10                         | 13.6                               | 158              | 0.98                    | 0.97                   |
| C26-26                         | 12.8                               | 162              | 0.92                    | 0.99                   |
| C26-32                         | 13.3                               | 150              | 0.96                    | 0.92                   |
| C26-50                         | 12.4                               | 158              | 0.89                    | 0.97                   |
| C26-75                         | 12.3                               | 165              | 0.89                    | 1.01                   |
| <b>Average</b>                 | 13.1                               | 159              | 0.95                    | 0.98                   |
| <b>SD</b>                      | 0.73                               | 5.56             |                         |                        |
| <b>COV (%)</b>                 | 5.58                               | 3.49             |                         |                        |

**Table 33. Effect of exposure in windshield washer fluid on compressive strength of the crossply carbon-fiber composite**

| <b>Specimen Number</b>                | <b>UCS (MPa)</b> | <b>Strength factor</b> |
|---------------------------------------|------------------|------------------------|
| <b><u>0/90° fiber orientation</u></b> |                  |                        |
| <b>Exposure time = 50 h</b>           |                  |                        |
| C25-3                                 | 305              | 0.92                   |
| C252-9                                | 333              | 1.01                   |
| C25-12                                | 313              | 0.95                   |
| C25-19                                | 323              | 0.98                   |
| C25-31                                | 326              | 0.99                   |
| C25-46                                | 329              | 1.00                   |
| <b>Average</b>                        | 321              | 0.97                   |
| <b>SD</b>                             | 10.7             |                        |
| <b>COV (%)</b>                        | 3.33             |                        |
| <b>Exposure time = 100 h</b>          |                  |                        |
| C25-1                                 | 308              | 0.94                   |
| C25-11                                | 299              | 0.91                   |
| C25-18                                | 282              | 0.86                   |
| C25-30                                | 308              | 0.94                   |
| C25-43                                | 298              | 0.90                   |
| C25-49                                | 324              | 0.98                   |
| <b>Average</b>                        | 303              | 0.92                   |
| <b>SD</b>                             | 14.0             |                        |
| <b>COV (%)</b>                        | 4.60             |                        |
| <b><u>±45° fiber orientation</u></b>  |                  |                        |
| <b>Exposure time = 50 h</b>           |                  |                        |
| C26-8                                 | 170              | 1.04                   |
| C26-25                                | 163              | 1.00                   |
| C26-33                                | 165              | 1.01                   |
| C26-48                                | 151              | 0.93                   |
| C26-55                                | 157              | 0.96                   |
| C26-74                                | 170              | 1.04                   |
| <b>Average</b>                        | 163              | 1.00                   |
| <b>SD</b>                             | 7.47             |                        |
| <b>COV (%)</b>                        | 4.59             |                        |
| <b>Exposure time = 100 h</b>          |                  |                        |
| C26-9                                 | 165              | 1.01                   |
| C26-24                                | 158              | 0.97                   |
| C26-34                                | 162              | 0.99                   |
| C26-46                                | 163              | 1.00                   |
| C26-58                                | 164              | 1.00                   |
| C26-71                                | 163              | 1.00                   |
| <b>Average</b>                        | 162              | 0.99                   |
| <b>SD</b>                             | 2.39             |                        |
| <b>COV (%)</b>                        | 1.47             |                        |

**Table 34. Summary of room-temperature shear tests for the crossply carbon-fiber composite**

| <b>Specimen number</b>         | <b>Shear modulus (GPa)</b> | <b>Shear strength (MPa)</b> | <b>Failure strain (%)</b> |
|--------------------------------|----------------------------|-----------------------------|---------------------------|
| <b>0/90° fiber orientation</b> |                            |                             |                           |
| C1-20                          | 2.92                       | 81.6                        | 12.8                      |
| C1-22                          | 2.74                       | 98.9                        | 11.4                      |
| C1-25                          | 3.10                       | 98.8                        | 11.8                      |
| C1-30                          | 2.49                       | 100                         | 11.3                      |
| C1-32                          | 2.56                       | 86.8                        | 12.4                      |
| C2-S3                          | 3.17                       | 89.9                        | 12.1                      |
| C2-S4                          | 3.31                       | 91.0                        | 12.1                      |
| C2-S5                          | 2.93                       | 87.9                        | 11.4                      |
| C2-S8                          | 2.86                       | 80.2                        | 11.1                      |
| C2-S9                          | 3.59                       | 103                         | 13.1                      |
| C2-S10                         | 3.55                       | 98.9                        | 11.5                      |
| C3-2                           | 2.70                       | 107                         | 12.7                      |
| C3-6                           | 2.79                       | 95.6                        | 10.8                      |
| C3-8                           | 2.68                       | 84.9                        | 11.9                      |
| C3-9                           | 2.99                       | 86.4                        | 12.0                      |
| C4-3                           | 3.03                       | 90.1                        | <sup>a</sup>              |
| C4-5                           | 3.33                       | 101                         | <sup>a</sup>              |
| C4-9                           | 2.71                       | 106                         | <sup>a</sup>              |
| C5-2                           | 2.90                       | 98.8                        | <sup>a</sup>              |
| C5-8                           | 3.18                       | 98.0                        | <sup>a</sup>              |
| C5-10                          | 2.74                       | 109                         | <sup>a</sup>              |
| <b>Average</b>                 | 2.96                       | 95.0                        | 11.9                      |
| <b>SD</b>                      | 0.30                       | 8.45                        | 0.67                      |
| <b>COV (%)</b>                 | 10.2                       | 8.90                        | 5.59                      |
| <b>±45° fiber orientation</b>  |                            |                             |                           |
| C21-S1                         | 23.9                       | 202                         | 1.06                      |
| C21-S4                         | 23.3                       | 206                         | 0.94                      |
| C21-S10                        | 24.6                       | 168                         | 0.68                      |
| C21-S16                        | 24.8                       | 207                         | 0.76                      |
| C21-S21                        | 23.8                       | 194                         | 1.12                      |
| C21-S27                        | 24.9                       | 167                         | 0.72                      |
| <b>Average</b>                 | 24.2                       | 191                         | 0.88                      |
| <b>SD</b>                      | 0.64                       | 18.7                        | 0.19                      |
| <b>COV (%)</b>                 | 2.65                       | 9.80                        | 21.2                      |

<sup>a</sup> No strain measurement

**Table 35. Shear properties of the crossply carbon-fiber composite, 0/90° fiber orientation, at different temperatures**

| <b>Specimen number</b> | <b>Shear modulus (GPa)</b> | <b>Shear strength (MPa)</b> | <b>Failure strain (%)</b> |
|------------------------|----------------------------|-----------------------------|---------------------------|
| <b>70°C</b>            |                            |                             |                           |
| C1-2                   | 2.21                       | 69.1                        | 12.7                      |
| C1-19                  | 2.25                       | 67.9                        | 11.7                      |
| C1-21                  | 2.16                       | 74.0                        | 11.7                      |
| C1-27                  | 1.95                       | 65.5                        | 11.9                      |
| C1-29                  | 1.92                       | 70.2                        | 12.7                      |
| C1-31                  | 2.19                       | 67.8                        | 12.6                      |
| <b>Average</b>         | 2.11                       | 69.1                        | 12.2                      |
| <b>SD</b>              | 0.14                       | 2.87                        | 0.51                      |
| <b>COV (%)</b>         | 6.72                       | 4.15                        | 4.13                      |
| <b>120°C</b>           |                            |                             |                           |
| C2-1                   | 0.56                       | 23.7                        | 10.6                      |
| C2-3                   | 0.58                       | 25.1                        | 11.1                      |
| C2-6                   | 0.59                       | 22.0                        | 12.0                      |
| C3-1                   | 0.61                       | 25.9                        | 11.3                      |
| C3-4                   | 0.65                       | 27.5                        | 12.0                      |
| C3-5                   | 0.62                       | 24.9                        | 10.5                      |
| <b>Average</b>         | 0.60                       | 24.9                        | 11.2                      |
| <b>SD</b>              | 0.03                       | 1.87                        | 0.66                      |
| <b>COV (%)</b>         | 5.20                       | 7.52                        | 5.85                      |
| <b>-40°C</b>           |                            |                             |                           |
| C1-18                  | 3.11                       | 111                         | 8.61                      |
| C1-24                  | 3.49                       | 107                         | 12.7                      |
| C1-28                  | 3.38                       | 116                         | 12.7                      |
| C1-33                  | 3.29                       | 107                         | 11.9                      |
| C1-34                  | 3.37                       | 114                         | 9.72                      |
| C1-35                  | 3.25                       | 110                         | 9.13                      |
| <b>Average</b>         | 3.31                       | 111                         | 10.8                      |
| <b>SD</b>              | 0.13                       | 3.76                        | 1.86                      |
| <b>COV (%)</b>         | 3.93                       | 3.39                        | 17.2                      |

**Table 36. Shear properties of the crossply carbon-fiber composite,  $\pm 45^\circ$  fiber orientation, at different temperatures**

| <b>Specimen number</b> | <b>Shear modulus (GPa)</b> | <b>Shear strength (MPa)</b> | <b>Failure strain (%)</b> |
|------------------------|----------------------------|-----------------------------|---------------------------|
| <b>70°C</b>            |                            |                             |                           |
| C21-2                  | 18.1                       | 123                         | 0.76                      |
| C21-5                  | 18.7                       | 117                         | 0.53                      |
| C21-11                 | 17.8                       | 103                         | 0.64                      |
| C21-17                 | 18.7                       | 118                         | 0.59                      |
| C21-23                 | 19.5                       | 102                         | 0.62                      |
| C21-26                 | 18.0                       | 103                         | 0.47                      |
| <b>Average</b>         | 18.5                       | 111                         | 0.60                      |
| <b>SD</b>              | 0.62                       | 9.33                        | 0.10                      |
| <b>COV (%)</b>         | 3.38                       | 8.42                        | 16.5                      |
| <b>120°C</b>           |                            |                             |                           |
| C21-6                  | 14.9                       | 87.6                        | 0.05                      |
| C21-9                  | 12.4                       | 85.7                        | 0.09                      |
| C21-14                 | 13.9                       | 71.0                        | 0.03                      |
| C21-19                 | 16.1                       | 88.9                        | 0.04                      |
| C21-20                 | 15.8                       | 90.8                        | 0.05                      |
| C21-24                 | 13.3                       | 82.0                        | 0.05                      |
| <b>Average</b>         | 14.4                       | 84.3                        | 0.05                      |
| <b>SD</b>              | 1.44                       | 7.18                        | 0.02                      |
| <b>COV (%)</b>         | 10.0                       | 8.51                        | 40.6                      |
| <b>-40°C</b>           |                            |                             |                           |
| C21-3                  | 29.2                       | 248                         | 1.10                      |
| C21-7                  | 28.4                       | 240                         | 1.24                      |
| C21-12                 | 29.2                       | 261                         | 1.19                      |
| C21-15                 | 34.3                       | 262                         | 1.40                      |
| C21-18                 | 31.3                       | 261                         | 1.27                      |
| C21-25                 | 29.0                       | 216                         | 0.90                      |
| <b>Average</b>         | 30.2                       | 248                         | 1.18                      |
| <b>SD</b>              | 2.20                       | 18.1                        | 0.17                      |
| <b>COV (%)</b>         | 7.27                       | 7.30                        | 14.4                      |



**Table 37. Temperature multiplication factors for determining at-temperature shear modulus and strength from room-temperature values for the crossply carbon-fiber composite, 0/90° fiber orientation**

| <b>Temperature<br/>(°C)</b> | <b>Stiffness multiplication<br/>factor</b> | <b>Strength multiplication<br/>factor</b> |
|-----------------------------|--|---|
| <b>-40</b>                  | 1.18                                       | 1.18                                      |
| <b>23</b>                   | 1.00                                       | 1.00                                      |
| <b>70</b>                   | 0.71                                       | 0.71                                      |
| <b>120</b>                  | 0.26                                       | 0.26                                      |

**Table 38. Temperature multiplication factors for determining at-temperature shear modulus and strength from room-temperature values for the crossply carbon-fiber composite, ±45° fiber orientation**

| <b>Temperature<br/>(°C)</b> | <b>Stiffness multiplication<br/>factor</b> | <b>Strength multiplication<br/>factor</b> |
|-----------------------------|--|---|
| <b>-40</b>                  | 1.26                                       | 1.35                                      |
| <b>23</b>                   | 1.00                                       | 1.00                                      |
| <b>70</b>                   | 0.79                                       | 0.70                                      |
| <b>120</b>                  | 0.60                                       | 0.46                                      |

**Table 39. Effects of 1000-h exposure in 23°C distilled water on room-temperature shear properties of the crossply carbon-fiber composite**

| <b>Specimen number</b>         | <b>Shear modulus (GPa)</b> | <b>Shear strength (MPa)</b> | <b>Stiffness factor</b> | <b>Strength factor</b> |
|--------------------------------|----------------------------|-----------------------------|-------------------------|------------------------|
| <b>0/90° fiber orientation</b> |                            |                             |                         |                        |
| C2-7                           | 2.83                       | 87.6                        | 1.03                    | 0.95                   |
| C3-3                           | 2.69                       | 88.3                        | 0.98                    | 0.94                   |
| C3-7                           | 2.59                       | 95.8                        | 0.94                    | 1.02                   |
| C3-10                          | 2.83                       | 88.9                        | 1.03                    | 0.95                   |
| C4-1                           | 2.96                       | 95.1                        | 0.98                    | 0.96                   |
| C5-1                           | 2.90                       | 104                         | 0.98                    | 1.02                   |
| <b>Average</b>                 | 2.80                       | 93.3                        | 0.99                    | 0.97                   |
| <b>SD</b>                      | 0.14                       | 6.39                        |                         |                        |
| <b>COV (%)</b>                 | 4.88                       | 6.85                        |                         |                        |
| <b>±45° fiber orientation</b>  |                            |                             |                         |                        |
| C22-6                          | 22.5                       | 193                         | 0.89                    | 0.93                   |
| C22-7                          | 24.0                       | 197                         | 0.95                    | 0.95                   |
| C22-11                         | 24.2                       | 208                         | 0.96                    | 1.00                   |
| C22-15                         | 22.7                       | 188                         | 0.90                    | 0.91                   |
| C22-17                         | 23.5                       | 207                         | 0.93                    | 1.00                   |
| C22-25                         | 24.2                       | 203                         | 0.96                    | 0.98                   |
| <b>Average</b>                 | 23.5                       | 199                         | 0.93                    | 0.96                   |
| <b>SD</b>                      | 0.77                       | 7.78                        |                         |                        |
| <b>COV (%)</b>                 | 3.29                       | 3.90                        |                         |                        |

**Table 40. Effect of exposure in windshield washer fluid on shear strength of the crossply carbon-fiber composite**

| <b>Specimen number</b>                | <b>Shear strength (MPa)</b> | <b>Strength factor</b> |
|---------------------------------------|-----------------------------|------------------------|
| <b><u>0/90° fiber orientation</u></b> |                             |                        |
| <b>Exposure time = 50 h</b>           |                             |                        |
| C4-7                                  | 99.2                        | 1.00                   |
| C4-8                                  | 101                         | 1.01                   |
| C4-10                                 | 97.7                        | 0.98                   |
| C5-4                                  | 98.6                        | 0.97                   |
| C5-6                                  | 97.2                        | 0.95                   |
| C5-9                                  | 98.6                        | 0.97                   |
| <b>Average</b>                        | 98.7                        | 0.98                   |
| <b>SD</b>                             | 1.21                        |                        |
| <b>COV (%)</b>                        | 1.22                        |                        |
| <b>Exposure time = 100 h</b>          |                             |                        |
| C4-2                                  | 98.6                        | 0.99                   |
| C4-4                                  | 96.5                        | 0.97                   |
| C4-6                                  | 95.8                        | 0.97                   |
| C5-3                                  | 96.2                        | 0.94                   |
| C5-5                                  | 101                         | 0.99                   |
| C5-7                                  | 97.2                        | 0.95                   |
| <b>Average</b>                        | 97.5                        | 0.97                   |
| <b>SD</b>                             | 1.83                        |                        |
| <b>COV (%)</b>                        | 1.88                        |                        |
| <b><u>±45° fiber orientation</u></b>  |                             |                        |
| <b>Exposure time = 50 h</b>           |                             |                        |
| C22-1                                 | 205                         | 0.99                   |
| C22-3                                 | 192                         | 0.93                   |
| C22-12                                | 204                         | 0.98                   |
| C22-18                                | 194                         | 0.93                   |
| C22-20                                | 192                         | 0.92                   |
| C22-26                                | 180                         | 0.87                   |
| <b>Average</b>                        | 194                         | 0.94                   |
| <b>SD</b>                             | 9.15                        |                        |
| <b>COV (%)</b>                        | 4.71                        |                        |
| <b>Exposure time = 100 h</b>          |                             |                        |
| C22-4                                 | 184                         | 0.88                   |
| C22-8                                 | 197                         | 0.95                   |
| C22-10                                | 194                         | 0.94                   |
| C22-21                                | 192                         | 0.92                   |
| C22-23                                | 199                         | 0.96                   |
| C22-28                                | 187                         | 0.90                   |
| <b>Average</b>                        | 192                         | 0.93                   |
| <b>SD</b>                             | 5.99                        |                        |
| <b>COV (%)</b>                        | 3.12                        |                        |

**Table 41. Uniaxial flexural properties of the crossply carbon-fiber composite at different temperatures**

| <b>Specimen number</b>                | <b>Modulus of Elasticity (GPa)</b> | <b>MOR (MPa)</b> |
|---------------------------------------|------------------------------------|------------------|
| <b><u>0/90° fiber orientation</u></b> |                                    |                  |
| <b>23°C</b>                           |                                    |                  |
| C27-3                                 | 26.4                               | 779              |
| C27-7                                 | 21.8                               | 772              |
| C27-11                                | 20.5                               | 738              |
| C27-16                                | 22.2                               | 841              |
| C27-29                                | 25.4                               | 793              |
| C27-36                                | 24.8                               | 855              |
| <b>Average</b>                        | 23.5                               | 796              |
| <b>SD</b>                             | 2.35                               | 44.2             |
| <b>COV (%)</b>                        | 10.0                               | 5.55             |
| <b>120°C</b>                          |                                    |                  |
| C27-15                                | 12.2                               | 477              |
| C27-21                                | 16.0                               | 556              |
| C27-23                                | 14.9                               | 515              |
| C27-24                                | 11.1                               | 422              |
| C27-27                                | 16.0                               | 436              |
| C27-31                                | 14.0                               | 508              |
| <b>Average</b>                        | 14.0                               | 486              |
| <b>SD</b>                             | 2.02                               | 50.8             |
| <b>COV (%)</b>                        | 14.4                               | 10.5             |
| <b><u>±45° fiber orientation</u></b>  |                                    |                  |
| <b>23°C</b>                           |                                    |                  |
| C27-1                                 | 2.96                               | 350              |
| C27-6                                 | 2.34                               | 279              |
| C27-13                                | 2.69                               | 316              |
| C27-19                                | 2.76                               | 327              |
| C27-24                                | 2.41                               | 288              |
| C27-35                                | 2.62                               | 309              |
| <b>Average</b>                        | 2.63                               | 311              |
| <b>SD</b>                             | 0.23                               | 25.8             |
| <b>COV (%)</b>                        | 8.68                               | 8.29             |
| <b>120°C</b>                          |                                    |                  |
| C27-5                                 | 0.76                               | 151              |
| C27-8                                 | 0.69                               | 144              |
| C27-16                                | 0.76                               | 155              |
| C27-29                                | 0.69                               | 147              |
| C27-30                                | 0.69                               | 142              |
| C27-34                                | 0.90                               | 181              |
| <b>Average</b>                        | 0.75                               | 153              |
| <b>SD</b>                             | 0.08                               | 14.5             |
| <b>COV (%)</b>                        | 10.8                               | 9.43             |

**Table 42. Effects of 1000-h exposure in 23°C distilled water on room-temperature uniaxial flexural properties of the crossply carbon-fiber composite**

| <b>Specimen number</b>                | <b>MOR (GPa)</b> | <b>MOR design factor</b> |
|---------------------------------------|------------------|--------------------------|
| <b><u>0/90° fiber orientation</u></b> |                  |                          |
| C27-6                                 | 765              | 0.96                     |
| C27-10                                | 724              | 0.91                     |
| C27-14                                | 765              | 0.96                     |
| C27-29                                | 800              | 1.00                     |
| C27-25                                | 696              | 0.87                     |
| C27-33                                | 827              | 1.04                     |
| <b>Average</b>                        | 763              | 0.96                     |
| <b>SD</b>                             | 47.9             |                          |
| <b>COV (%)</b>                        | 6.28             |                          |
| <b><u>±45° fiber orientation</u></b>  |                  |                          |
| C27-4                                 | 516              | 0.91                     |
| C27-10                                | 517              | 0.91                     |
| C27-11                                | 598              | 1.06                     |
| C27-18                                | 561              | 0.99                     |
| C27-23                                | 572              | 1.01                     |
| C27-33                                | 576              | 1.02                     |
| <b>Average</b>                        | 557              | 0.98                     |
| <b>SD</b>                             | 33.1             |                          |
| <b>COV (%)</b>                        | 5.95             |                          |

**Table 43. Effect of exposure in windshield washer fluid on uniaxial flexural properties of the crossply carbon-fiber composite**

| <b>Specimen number</b>                | <b>MOR (MPa)</b> | <b>MOR design factor</b> |
|---------------------------------------|------------------|--------------------------|
| <b><u>0/90° fiber orientation</u></b> |                  |                          |
| <b>Exposure time = 50 h</b>           |                  |                          |
| C27-4                                 | 779              | 0.97                     |
| C27-8                                 | 765              | 0.96                     |
| C27-12                                | 765              | 0.96                     |
| C27-17                                | 827              | 1.03                     |
| C27-28                                | 793              | 0.99                     |
| C27-35                                | 786              | 0.98                     |
| <b>Average</b>                        | 786              | 0.98                     |
| <b>SD</b>                             | 23.1             |                          |
| <b>COV (%)</b>                        | 2.94             |                          |
| <b>Exposure time = 100 h</b>          |                  |                          |
| C27-5                                 | 724              | 0.91                     |
| C27-9                                 | 807              | 1.01                     |
| C27-13                                | 779              | 0.97                     |
| C27-18                                | 779              | 0.97                     |
| C27-26                                | 752              | 0.94                     |
| C27-34                                | 820              | 1.03                     |
| <b>Average</b>                        | 777              | 0.97                     |
| <b>SD</b>                             | 35.3             |                          |
| <b>COV (%)</b>                        | 4.55             |                          |
| <b><u>±45° fiber orientation</u></b>  |                  |                          |
| <b>Exposure time = 50 h</b>           |                  |                          |
| C27-2                                 | 592              | 1.05                     |
| C27-7                                 | 532              | 0.94                     |
| C27-14                                | 568              | 1.00                     |
| C27-20                                | 560              | 0.99                     |
| C27-25                                | 546              | 0.96                     |
| C27-31                                | 552              | 0.98                     |
| <b>Average</b>                        | 558              | 0.99                     |
| <b>SD</b>                             | 20.5             |                          |
| <b>COV (%)</b>                        | 3.68             |                          |
| <b>Exposure time = 100 h</b>          |                  |                          |
| C27-3                                 | 565              | 1.00                     |
| C27-9                                 | 543              | 0.96                     |
| C27-15                                | 552              | 0.98                     |
| C27-17                                | 539              | 0.95                     |
| C27-22                                | 537              | 0.95                     |
| C27-32                                | 574              | 1.01                     |
| <b>Average</b>                        | 552              | 0.97                     |
| <b>SD</b>                             | 14.9             |                          |
| <b>COV (%)</b>                        | 2.69             |                          |

**Table 44. Biaxial flexural properties of the crossply carbon-fiber composite at different temperatures:  $\pm 45^\circ$  fiber orientation**

| <b>Specimen number</b> | <b>Maximum load (N)</b> | <b>Temperature factor</b> |
|------------------------|-------------------------|---------------------------|
| <b>23°C</b>            |                         |                           |
| C31-8                  | 12179                   | 1.00                      |
| C31-9                  | 13051                   | 1.00                      |
| C31-14                 | 12246                   | 1.00                      |
| C31-17                 | 12477                   | 1.00                      |
| C31-20                 | 12179                   | 1.00                      |
| C31-23                 | 12152                   | 1.00                      |
| <b>Average</b>         | 12381                   | 1.00                      |
| <b>SD</b>              | 374.6                   |                           |
| <b>COV (%)</b>         | 3.03                    |                           |
| <b>120°C</b>           |                         |                           |
| C31-6                  | 7033                    | 0.57                      |
| C31-7                  | 7362                    | 0.59                      |
| C31-16                 | 7277                    | 0.59                      |
| C31-19                 | 6530                    | 0.53                      |
| C31-22                 | 6183                    | 0.50                      |
| C31-25                 | 6214                    | 0.50                      |
| <b>Average</b>         | 6766                    | 0.55                      |
| <b>SD</b>              | 570.6                   |                           |
| <b>COV (%)</b>         | 8.43                    |                           |

**Table 45. Effects of environment on biaxial flexural properties of the crossply carbon-fiber composite:  $\pm 45^\circ$  fiber orientation**

| <b>Specimen number</b>                  | <b>Maximum load (N)</b> | <b>Design factor</b> |
|---|-------------------------|----------------------|
| <b>1000 h in 23°C distilled water</b>   |                         |                      |
| C31-1                                   | 12104                   | 0.98                 |
| C31-5                                   | 12419                   | 1.00                 |
| C31-11                                  | 12446                   | 1.01                 |
| C31-13                                  | 12250                   | 0.99                 |
| C31-21                                  | 11939                   | 0.96                 |
| C31-24                                  | 11863                   | 0.96                 |
| <b>Average</b>                          | 12170                   | 0.98                 |
| <b>SD</b>                               | 269.9                   |                      |
| <b>COV (%)</b>                          | 2.22                    |                      |
| <b>100 h in windshield washer fluid</b> |                         |                      |
| C31-3                                   | 11641                   | 0.94                 |
| C31-4                                   | 12393                   | 1.00                 |
| C31-12                                  | 12993                   | 1.05                 |
| C31-15                                  | 12815                   | 1.04                 |
| C31-18                                  | 12580                   | 1.02                 |
| C31-26                                  | 11650                   | 0.94                 |
| <b>Average</b>                          | 12345                   | 1.00                 |
| <b>SD</b>                               | 520.2                   |                      |
| <b>COV (%)</b>                          | 4.21                    |                      |



**Table 46. Summary of room-temperature stiffness values for the quasi-isotropic carbon-fiber composite**

| <b>Specimen number</b> | <b>Stiffness (GPa)</b> | <b>Specimen number</b> | <b>Stiffness (GPa)</b> | <b>Specimen number</b> | <b>Stiffness (GPa)</b> | <b>Specimen number</b> | <b>Stiffness (GPa)</b> |
|------------------------|------------------------|------------------------|------------------------|------------------------|------------------------|------------------------|------------------------|
| Q9-1                   | 32.1                   | Q10-43                 | 35.0                   | Q11-31                 | 34.0                   | Q12-20                 | 31.4                   |
| Q9-2                   | 27.6                   | Q10-44                 | 33.7                   | Q11-32                 | 32.8                   | Q12-21                 | 30.1                   |
| Q9-3                   | 26.0                   | Q10-45                 | 34.3                   | Q11-33                 | 28.7                   | Q12-22                 | 34.4                   |
| Q9-4                   | 34.4                   | Q10-46                 | 36.4                   | Q11-34                 | 29.5                   | Q12-23                 | 34.0                   |
| Q9-5                   | 30.8                   | Q10-47                 | 30.8                   | Q11-35                 | 34.8                   | Q12-24                 | 34.3                   |
| Q9-6                   | 32.6                   | Q10-48                 | 33.8                   | Q11-36                 | 32.7                   | Q12-25                 | 35.3                   |
| Q10-1                  | 32.8                   | Q10-49                 | 35.1                   | Q11-37                 | 32.2                   | Q12-26                 | 31.0                   |
| Q10-2                  | 32.1                   | Q10-50                 | 33.4                   | Q11-38                 | 32.8                   | Q12-27                 | 32.4                   |
| Q10-3                  | 31.9                   | Q10-51                 | 35.3                   | Q11-39                 | 29.3                   | Q12-28                 | 31.3                   |
| Q10-4                  | 33.1                   | Q10-52                 | 34.8                   | Q11-40                 | 31.9                   | Q12-29                 | 33.5                   |
| Q10-5                  | 30.2                   | Q10-53                 | 33.1                   | Q11-41                 | 31.6                   | Q12-30                 | 34.9                   |
| Q10-6                  | 30.0                   | Q10-54                 | 32.6                   | Q11-42                 | 31.6                   | Q12-31                 | 30.5                   |
| Q10-7                  | 32.4                   | Q10-55                 | 35.0                   | Q11-43                 | 34.5                   | Q12-32                 | 30.7                   |
| Q10-8                  | 30.8                   | Q10-56                 | 33.1                   | Q11-44                 | 32.0                   | Q12-33                 | 32.0                   |
| Q10-9                  | 31.3                   | Q10-57                 | 34.8                   | Q11-45                 | 34.1                   | Q12-34                 | 33.3                   |
| Q10-10                 | 28.7                   | Q10-58                 | 33.5                   | Q11-46                 | 34.8                   | Q12-35                 | 33.5                   |
| Q10-11                 | 30.3                   | Q11-1                  | 31.5                   | Q11-47                 | 33.1                   | Q12-36                 | 35.9                   |
| Q10-12                 | 31.6                   | Q11-2                  | 32.9                   | Q11-48                 | 35.6                   | Q12-37                 | 32.1                   |
| Q10-13                 | 31.1                   | Q11-3                  | 30.5                   | Q11-49                 | 32.7                   | Q12-38                 | 33.5                   |
| Q10-14                 | 29.4                   | Q11-4                  | 28.4                   | Q11-50                 | 35.3                   | Q12-39                 | 30.7                   |
| Q10-15                 | 30.6                   | Q11-5                  | 33.8                   | Q11-51                 | 31.4                   | Q12-40                 | 34.0                   |
| Q10-16                 | 30.0                   | Q11-6                  | 32.6                   | Q11-52                 | 29.6                   | Q12-41                 | 34.1                   |
| Q10-17                 | 29.7                   | Q11-7                  | 31.3                   | Q11-53                 | 32.5                   | Q12-42                 | 37.5                   |
| Q10-18                 | 28.6                   | Q11-8                  | 33.0                   | Q11-54                 | 33.6                   | Q12-43                 | 34.5                   |
| Q10-19                 | 29.4                   | Q11-9                  | 32.0                   | Q11-55                 | 36.5                   | Q12-44                 | 33.3                   |
| Q10-20                 | 30.7                   | Q11-10                 | 33.5                   | Q11-56                 | 34.5                   | Q12-45                 | 35.5                   |
| Q10-21                 | 30.9                   | Q11-11                 | 33.4                   | Q11-57                 | 32.6                   | Q12-46                 | 32.0                   |
| Q10-22                 | 34.9                   | Q11-12                 | 29.5                   | Q11-58                 | 35.3                   | Q12-47                 | 37.0                   |
| Q10-23                 | 31.7                   | Q11-13                 | 26.4                   | Q12-2                  | 33.0                   | Q12-48                 | 36.6                   |
| Q10-26                 | 32.4                   | Q11-14                 | 26.9                   | Q12-3                  | 30.8                   | Q12-49                 | 33.5                   |
| Q10-27                 | 30.8                   | Q11-15                 | 27.5                   | Q12-4                  | 35.2                   | Q12-50                 | 33.6                   |
| Q10-28                 | 34.4                   | Q11-16                 | 31.9                   | Q12-5                  | 33.1                   | Q12-51                 | 32.4                   |
| Q10-29                 | 31.8                   | Q11-17                 | 30.4                   | Q12-6                  | 31.6                   | Q12-52                 | 34.5                   |
| Q10-30                 | 32.2                   | Q11-18                 | 30.3                   | Q12-7                  | 32.3                   | Q12-53                 | 33.2                   |
| Q10-31                 | 33.7                   | Q11-19                 | 35.2                   | Q12-8                  | 30.6                   | Q12-54                 | 30.8                   |
| Q10-32                 | 30.8                   | Q11-20                 | 34.7                   | Q12-9                  | 33.1                   | Q12-55                 | 34.9                   |
| Q10-33                 | 31.3                   | Q11-21                 | 32.1                   | Q12-10                 | 28.7                   | Q12-56                 | 35.7                   |
| Q10-34                 | 30.7                   | Q11-22                 | 31.5                   | Q12-11                 | 31.1                   | Q12-57                 | 35.4                   |
| Q10-35                 | 31.5                   | Q11-23                 | 31.2                   | Q12-12                 | 30.7                   | Q13-1                  | 33.6                   |
| Q10-36                 | 33.4                   | Q11-24                 | 30.7                   | Q12-13                 | 32.5                   | Q13-2                  | 31.0                   |
| Q10-37                 | 28.8                   | Q11-25                 | 33.0                   | Q12-14                 | 31.9                   | Q13-3                  | 29.0                   |
| Q10-38                 | 31.3                   | Q11-26                 | 31.8                   | Q12-15                 | 30.0                   | Q13-4                  | 31.0                   |
| Q10-39                 | 35.0                   | Q11-27                 | 33.3                   | Q12-16                 | 30.2                   | Q13-5                  | 30.6                   |
| Q10-40                 | 33.5                   | Q11-28                 | 32.2                   | Q12-17                 | 29.7                   | Q13-6                  | 28.2                   |
| Q10-41                 | 36.0                   | Q11-29                 | 34.3                   | Q12-18                 | 28.8                   | Q13-7                  | 30.1                   |
| Q10-42                 | 34.6                   | Q11-30                 | 33.6                   | Q12-19                 | 30.5                   | Q13-8                  | 30.3                   |

**Table 46. Continued. Summary of room-temperature stiffness values for the quasi-isotropic carbon-fiber composite**

| <b>Specimen number</b> | <b>Stiffness (GPa)</b> | <b>Specimen number</b> | <b>Stiffness (GPa)</b> | <b>Specimen number</b> | <b>Stiffness (GPa)</b> | <b>Specimen number</b> | <b>Stiffness (GPa)</b> |
|------------------------|------------------------|------------------------|------------------------|------------------------|------------------------|------------------------|------------------------|
| Q13-9                  | 28.9                   | Q13-55                 | 33.8                   | Q14-43                 | 33.9                   | Q15-31                 | 32.8                   |
| Q13-10                 | 31.9                   | Q13-56                 | 34.4                   | Q14-44                 | 34.0                   | Q15-32                 | 29.8                   |
| Q13-11                 | 30.6                   | Q13-57                 | 35.0                   | Q14-45                 | 33.1                   | Q15-33                 | 32.8                   |
| Q13-12                 | 30.6                   | Q13-58                 | 32.5                   | Q14-46                 | 39.0                   | Q15-34                 | 32.4                   |
| Q13-13                 | 27.4                   | Q14-1                  | 35.4                   | Q14-47                 | 32.2                   | Q15-35                 | 31.4                   |
| Q13-14                 | 28.6                   | Q14-2                  | 34.8                   | Q14-48                 | 36.1                   | Q15-36                 | 32.3                   |
| Q13-15                 | 32.3                   | Q14-3                  | 31.4                   | Q14-49                 | 33.4                   | Q15-37                 | 36.0                   |
| Q13-16                 | 30.2                   | Q14-4                  | 32.3                   | Q14-50                 | 33.1                   | Q15-38                 | 31.8                   |
| Q13-17                 | 30.5                   | Q14-5                  | 33.0                   | Q14-51                 | 35.2                   | Q15-39                 | 31.6                   |
| Q13-18                 | 31.0                   | Q14-6                  | 33.2                   | Q14-52                 | 33.6                   | Q15-40                 | 31.5                   |
| Q13-19                 | 28.9                   | Q14-7                  | 30.9                   | Q14-53                 | 33.0                   | Q15-41                 | 32.9                   |
| Q13-20                 | 30.5                   | Q14-8                  | 33.2                   | Q14-54                 | 32.5                   | Q15-42                 | 32.6                   |
| Q13-21                 | 29.3                   | Q14-9                  | 32.7                   | Q14-55                 | 33.7                   | Q15-43                 | 32.6                   |
| Q13-22                 | 30.8                   | Q14-10                 | 30.0                   | Q14-56                 | 31.3                   | Q15-44                 | 32.6                   |
| Q13-23                 | 33.0                   | Q14-11                 | 29.3                   | Q14-57                 | 33.1                   | Q15-45                 | 32.3                   |
| Q13-24                 | 35.6                   | Q14-12                 | 31.5                   | Q14-58                 | 36.1                   | Q15-46                 | 30.8                   |
| Q13-25                 | 30.1                   | Q14-13                 | 30.6                   | Q15-1                  | 35.8                   | Q15-47                 | 30.8                   |
| Q13-26                 | 35.9                   | Q14-14                 | 31.9                   | Q15-2                  | 32.8                   | Q15-48                 | 32.4                   |
| Q13-27                 | 34.8                   | Q14-15                 | 33.8                   | Q15-3                  | 32.9                   | Q15-49                 | 31.8                   |
| Q13-28                 | 30.8                   | Q14-16                 | 28.4                   | Q15-4                  | 34.8                   | Q15-50                 | 31.4                   |
| Q13-29                 | 34.7                   | Q14-17                 | 31.3                   | Q15-5                  | 33.2                   | Q15-51                 | 28.8                   |
| Q13-30                 | 31.1                   | Q14-18                 | 32.7                   | Q15-6                  | 32.6                   | Q15-52                 | 29.4                   |
| Q13-31                 | 30.2                   | Q14-19                 | 29.0                   | Q15-7                  | 32.4                   | Q15-53                 | 31.6                   |
| Q13-32                 | 31.1                   | Q14-20                 | 33.9                   | Q15-8                  | 33.4                   | Q15-54                 | 30.7                   |
| Q13-33                 | 29.5                   | Q14-21                 | 34.5                   | Q15-9                  | 32.6                   | Q15-55                 | 31.4                   |
| Q13-34                 | 34.3                   | Q14-22                 | 33.2                   | Q15-10                 | 28.5                   | Q15-56                 | 32.3                   |
| Q13-35                 | 31.3                   | Q14-23                 | 29.2                   | Q15-11                 | 32.8                   | Q15-57                 | 31.0                   |
| Q13-36                 | 30.8                   | Q14-24                 | 32.2                   | Q15-12                 | 34.0                   | Q15-58                 | 32.0                   |
| Q13-37                 | 33.5                   | Q14-25                 | 35.8                   | Q15-13                 | 34.7                   | Q16-1                  | 31.3                   |
| Q13-38                 | 31.7                   | Q14-26                 | 33.5                   | Q15-14                 | 33.1                   | Q16-2                  | 32.8                   |
| Q13-39                 | 30.1                   | Q14-27                 | 32.7                   | Q15-15                 | 32.7                   | Q16-3                  | 31.3                   |
| Q13-40                 | 33.8                   | Q14-28                 | 35.3                   | Q15-16                 | 34.1                   | Q16-4                  | 32.7                   |
| Q13-41                 | 34.1                   | Q14-29                 | 31.6                   | Q15-17                 | 32.4                   | Q16-5                  | 32.4                   |
| Q13-42                 | 31.5                   | Q14-30                 | 32.3                   | Q15-18                 | 32.9                   | Q16-6                  | 33.3                   |
| Q13-43                 | 32.0                   | Q14-31                 | 32.7                   | Q15-19                 | 33.0                   | Q16-7                  | 33.1                   |
| Q13-44                 | 34.0                   | Q14-32                 | 34.4                   | Q15-20                 | 33.5                   | Q16-8                  | 33.6                   |
| Q13-45                 | 32.5                   | Q14-33                 | 33.2                   | Q15-21                 | 34.6                   | Q16-9                  | 32.4                   |
| Q13-46                 | 33.3                   | Q14-34                 | 29.9                   | Q15-22                 | 29.8                   | Q16-10                 | 30.9                   |
| Q13-47                 | 34.0                   | Q14-35                 | 31.3                   | Q15-23                 | 29.5                   | Q16-11                 | 31.9                   |
| Q13-48                 | 29.5                   | Q14-36                 | 30.1                   | Q15-24                 | 32.2                   | Q16-12                 | 32.8                   |
| Q13-49                 | 34.1                   | Q14-37                 | 31.7                   | Q15-25                 | 31.1                   | Q16-13                 | 31.1                   |
| Q13-50                 | 33.5                   | Q14-38                 | 34.0                   | Q15-26                 | 30.9                   | Q16-14                 | 29.6                   |
| Q13-51                 | 33.4                   | Q14-39                 | 36.2                   | Q15-27                 | 33.2                   | Q16-15                 | 31.1                   |
| Q13-52                 | 34.3                   | Q14-40                 | 32.9                   | Q15-28                 | 32.6                   | Q16-16                 | 31.3                   |
| Q13-53                 | 35.0                   | Q14-41                 | 33.6                   | Q15-29                 | 32.9                   | Q16-17                 | 33.1                   |
| Q13-54                 | 33.8                   | Q14-42                 | 34.6                   | Q15-30                 | 31.7                   | Q16-18                 | 32.9                   |

**Table 46. Continued. Summary of room-temperature stiffness values for the quasi-isotropic carbon-fiber composite**

| <b>Specimen number</b> | <b>Stiffness (GPa)</b> | <b>Specimen number</b> | <b>Stiffness (GPa)</b> | <b>Specimen number</b> | <b>Stiffness (GPa)</b> | <b>Specimen number</b> | <b>Stiffness (GPa)</b> |
|------------------------|------------------------|------------------------|------------------------|------------------------|------------------------|------------------------|------------------------|
| Q16-19                 | 35.5                   | Q16-42                 | 34.0                   | Q19-1L                 | 30.7                   | Q24-4                  | 32.1                   |
| Q16-20                 | 31.8                   | Q16-43                 | 29.1                   | Q19-2L                 | 35.2                   | Q25-1                  | 33.3                   |
| Q16-21                 | 32.7                   | Q16-44                 | 31.5                   | Q19-1T                 | 34.4                   | Q25-2                  | 35.0                   |
| Q16-22                 | 31.4                   | Q16-45                 | 33.0                   | Q19-2T                 | 38.9                   | Q25-3                  | 33.0                   |
| Q16-23                 | 34.1                   | Q16-46                 | 30.7                   | Q20A                   | 32.0                   | Q25-4                  | 33.2                   |
| Q16-24                 | 30.6                   | Q16-47                 | 31.4                   | Q20B                   | 33.0                   | Q26-1                  | 32.3                   |
| Q16-25                 | 33.8                   | Q16-48                 | 29.1                   | Q20C                   | 35.3                   | Q26-2                  | 34.9                   |
| Q16-26                 | 32.4                   | Q16-49                 | 31.6                   | Q20D                   | 36.1                   | Q26-3                  | 35.4                   |
| Q16-27                 | 31.8                   | Q16-50                 | 29.6                   | Q21-1                  | 34.0                   | Q26-4                  | 33.4                   |
| Q16-28                 | 31.7                   | Q16-51                 | 30.7                   | Q21-2                  | 30.7                   | Q27-1                  | 31.6                   |
| Q16-29                 | 29.8                   | Q16-52                 | 31.0                   | Q21-3                  | 34.2                   | Q27-2                  | 30.4                   |
| Q16-30                 | 32.4                   | Q16-53                 | 32.0                   | Q21-4                  | 34.5                   | Q27-3                  | 32.3                   |
| Q16-31                 | 32.7                   | Q16-54                 | 32.8                   | Q22-1                  | 33.2                   | Q27-4                  | 31.6                   |
| Q16-32                 | 30.4                   | Q16-55                 | 33.0                   | Q22-2                  | 34.4                   | Q28-1                  | 34.5                   |
| Q16-33                 | 32.2                   | Q16-56                 | 31.1                   | Q22-3                  | 39.0                   | Q28-2                  | 33.9                   |
| Q16-34                 | 28.6                   | Q16-57                 | 31.9                   | Q22-4                  | 38.1                   | Q28-3                  | 34.3                   |
| Q16-35                 | 33.8                   | Q16-58                 | 30.5                   | Q23-1                  | 33.0                   | Q28-4                  | 29.9                   |
| Q16-36                 | 30.5                   | Q18-1                  | 33.2                   | Q23-2                  | 31.5                   |                        |                        |
| Q16-37                 | 34.9                   | Q18-2                  | 31.5                   | Q23-3                  | 33.8                   | <b>Average</b>         | 32.4                   |
| Q16-38                 | 32.0                   | Q18-3                  | 34.8                   | Q23-4                  | 34.7                   | <b>SD</b>              | 2.04                   |
| Q16-39                 | 37.1                   | Q18-4                  | 35.5                   | Q24-1                  | 32.3                   | <b>COV(%)</b>          | 6.28                   |
| Q16-40                 | 32.0                   | Q18-5                  | 35.0                   | Q24-2                  | 31.4                   |                        |                        |
| Q16-41                 | 30.4                   | Q18-6                  | 35.3                   | Q24-3                  | 31.0                   |                        |                        |

**Table 47. Summary of room-temperature tensile properties for the quasi-isotropic carbon-fiber composite**

| <b>Specimen number</b> | <b>UTS (MPa)</b> | <b>Failure strain (%)</b> | <b>Specimen number</b> | <b>UTS (MPa)</b> | <b>Failure strain (%)</b> |
|------------------------|------------------|---------------------------|------------------------|------------------|---------------------------|
| Q9-1                   | 261              | 0.90                      | Q19-1L                 | 328              | 1.07                      |
| Q9-2                   | 298              | 1.06                      | Q19-2L                 | 340              | 0.92                      |
| Q9-3                   | 286              | 1.11                      | Q19-1T                 | 362              | 1.07                      |
| Q9-4                   | 335              | 0.99                      | Q19-2T                 | 354              | 0.89                      |
| Q9-5                   | 308              | 1.01                      | Q20A                   | 346              | 1.11                      |
| Q9-6                   | 308              | 0.95                      | Q20B                   | 322              | 0.98                      |
| Q10-5                  | 331              | 1.12                      | Q20C                   | 379              | 1.08                      |
| Q10-16                 | 346              | 1.02                      | Q20D                   | 372              | 1.04                      |
| Q10-43                 | 295              | 0.91                      | Q21-1                  | 339              | 0.98                      |
| Q10-54                 | 328              | 1.00                      | Q21-2                  | 351              | 1.14                      |
| Q11-5                  | 403              | 1.05                      | Q21-3                  | 366              | 1.05                      |
| Q11-16                 | 362              | 1.07                      | Q21-4                  | 380              | 1.09                      |
| Q11-22                 | 362              | 1.00                      | Q22-1                  | 341              | 1.03                      |
| Q11-36                 | 362              | 0.99                      | Q22-2                  | 306              | 0.88                      |
| Q11-43                 | 317              | 1.05                      | Q22-3                  | 380              | 0.95                      |
| Q11-54                 | 341              | 0.99                      | Q22-4                  | 397              | 1.04                      |
| Q12-5                  | 411              | 1.20                      | Q23-1                  | 299              | 0.90                      |
| Q12-16                 | 312              | 0.99                      | Q23-2                  | 351              | 1.13                      |
| Q12-22                 | 338              | 0.99                      | Q23-3                  | 331              | 0.97                      |
| Q12-36                 | 407              | 1.13                      | Q23-4                  | 296              | 0.84                      |
| Q12-43                 | 281              | 0.96                      | Q24-1                  | 341              | 1.04                      |
| Q12-54                 | 337              | 0.99                      | Q24-2                  | 346              | 1.13                      |
| Q13-5                  | 310              | 0.98                      | Q24-3                  | 314              | 0.99                      |
| Q13-16                 | 333              | 1.09                      | Q24-4                  | 350              | 1.07                      |
| Q13-22                 | 327              | 0.96                      | Q25-1                  | 292              | 0.88                      |
| Q13-36                 | 341              | 1.04                      | Q25-2                  | 336              | 0.97                      |
| Q13-43                 | 306              | 1.10                      | Q25-3                  | 351              | 1.07                      |
| Q13-54                 | 358              | 1.05                      | Q25-4                  | 337              | 1.02                      |
| Q14-5                  | 372              | 1.06                      | Q26-1                  | 326              | 1.05                      |
| Q14-16                 | 281              | -                         | Q26-2                  | 332              | 0.94                      |
| Q14-43                 | 332              | 0.99                      | Q26-3                  | 336              | 0.97                      |
| Q14-54                 | 325              | 0.98                      | Q26-4                  | 324              | 0.97                      |
| Q15-5                  | 317              | 1.00                      | Q27-1                  | 323              | 1.02                      |
| Q15-16                 | 354              | 1.04                      | Q27-2                  | 307              | 0.99                      |
| Q15-43                 | 371              | 1.14                      | Q27-3                  | 318              | 0.97                      |
| Q15-54                 | 334              | 1.07                      | Q27-4                  | 320              | 1.00                      |
| Q16-5                  | 344              | 1.07                      | Q28-1                  | 340              | 0.98                      |
| Q16-16                 | 332              | 1.07                      | Q28-2                  | 334              | 1.00                      |
| Q16-43                 | 313              | 1.05                      | Q28-3                  | 367              | 1.04                      |
| Q16-54                 | 343              | 0.98                      | Q28-4                  | 276              | 0.92                      |
| Q18-1                  | 330              | 1.00                      |                        |                  |                           |
| Q18-2                  | 340              | 1.07                      | <b>Average</b>         | 336              | 1.02                      |
| Q18-3                  | 314              | 0.88                      | <b>SD</b>              | 29.1             | 0.07                      |
| Q18-4                  | 353              | 0.98                      | <b>COV(%)</b>          | 8.66             | 6.80                      |
| Q18-5                  | 365              | 1.04                      |                        |                  |                           |
| Q18-6                  | 352              | 1.03                      |                        |                  |                           |

**Table 48. Summary of plaque average tensile properties for the quasi-isotropic carbon-fiber composite**

| <b>Plaque number</b>   | <b>Number of stiffness tests</b> | <b>E<sub>avg</sub> (GPa)</b> | <b>E<sub>max</sub> (GPa)</b> | <b>E<sub>min</sub> (GPa)</b> | <b>Number of tensile tests</b> | <b>UTS<sub>avg</sub> (MPa)</b> | <b>UTS<sub>max</sub> (MPa)</b> | <b>UTS<sub>min</sub> (MPa)</b> | <b>ε<sub>f avg</sub> (%)</b> |
|------------------------|----------------------------------|------------------------------|------------------------------|------------------------------|--------------------------------|--------------------------------|--------------------------------|--------------------------------|------------------------------|
| Q9                     | 6                                | 30.6                         | 34.4                         | 27.6                         | 6                              | 299                            | 335                            | 261                            | 1.00                         |
| Q10                    | 58                               | 32.3                         | 36.4                         | 28.6                         | 4                              | 325                            | 346                            | 295                            | 1.01                         |
| Q11                    | 58                               | 32.2                         | 36.5                         | 26.4                         | 6                              | 358                            | 403                            | 317                            | 1.02                         |
| Q12                    | 56                               | 32.8                         | 37.5                         | 28.7                         | 6                              | 348                            | 411                            | 281                            | 1.04                         |
| Q13                    | 58                               | 31.9                         | 35.9                         | 27.4                         | 6                              | 329                            | 358                            | 306                            | 1.04                         |
| Q14                    | 58                               | 32.9                         | 39.0                         | 28.4                         | 4                              | 328                            | 372                            | 281                            | 1.01                         |
| Q15                    | 58                               | 32.2                         | 36.0                         | 28.5                         | 4                              | 344                            | 354                            | 317                            | 1.06                         |
| Q16                    | 58                               | 31.9                         | 37.1                         | 28.6                         | 4                              | 333                            | 344                            | 313                            | 1.04                         |
| Q18                    | 6                                | 34.2                         | 35.5                         | 31.5                         | 6                              | 342                            | 365                            | 314                            | 1.00                         |
| Q19                    | 4                                | 34.8                         | 38.9                         | 30.7                         | 4                              | 346                            | 362                            | 328                            | 0.99                         |
| Q20                    | 4                                | 34.1                         | 36.1                         | 32.0                         | 4                              | 355                            | 379                            | 322                            | 1.05                         |
| Q21                    | 4                                | 33.3                         | 34.5                         | 30.7                         | 4                              | 359                            | 380                            | 339                            | 1.07                         |
| Q22                    | 4                                | 36.2                         | 39.0                         | 33.2                         | 4                              | 356                            | 397                            | 306                            | 0.98                         |
| Q23                    | 4                                | 33.2                         | 34.7                         | 31.5                         | 4                              | 319                            | 351                            | 296                            | 0.96                         |
| Q24                    | 4                                | 31.7                         | 32.3                         | 31.0                         | 4                              | 338                            | 350                            | 314                            | 1.06                         |
| Q25                    | 4                                | 33.6                         | 35.0                         | 33.0                         | 4                              | 329                            | 351                            | 292                            | 0.99                         |
| Q26                    | 4                                | 34.0                         | 35.4                         | 32.3                         | 4                              | 330                            | 336                            | 324                            | 0.98                         |
| Q27                    | 4                                | 31.5                         | 32.3                         | 30.4                         | 4                              | 317                            | 323                            | 307                            | 1.00                         |
| Q28                    | 4                                | 33.2                         | 34.5                         | 29.9                         | 4                              | 329                            | 367                            | 276                            | 0.99                         |
| <b>Number of tests</b> | 456                              |                              |                              |                              | 86                             |                                |                                |                                |                              |
| <b>Average</b>         |                                  | 32.4                         |                              |                              |                                | 336                            |                                |                                |                              |
| <b>SD</b>              |                                  | 2.04                         |                              |                              |                                | 29.1                           |                                |                                |                              |
| <b>COV %</b>           |                                  | 6.28                         |                              |                              |                                | 8.66                           |                                |                                |                              |
| <b>MAX</b>             |                                  | 39.0                         |                              |                              |                                | 411                            |                                |                                |                              |
| <b>MIN</b>             |                                  | 26.0                         |                              |                              |                                | 261                            |                                |                                |                              |

**Table 49. Summary of tensile tests at various strain rates for the quasi-isotropic carbon-fiber composite**

| <b>Specimen number</b>                                   | <b>Virgin stiffness (GPa)</b> | <b>Stiffness (GPa)</b> | <b>UTS (MPa)</b> | <b>Failure strain (%)</b> |
|--|-------------------------------|------------------------|------------------|---------------------------|
| <b>Strain rate = <math>10^{-6} \text{ s}^{-1}</math></b> |                               |                        |                  |                           |
| Q13-3  | 29.0                          | 27.4                   | 307              | 1.15                      |
| Q13-14   | 28.6                          | 28.3                   | 309              | 1.10                      |
| Q13-28   | 30.8                          | 29.6                   | 318              | 1.06                      |
| Q13-49   | 34.1                          | 32.8                   | 343              | 1.03                      |
| <b>Average</b>   | 30.6                          | 29.5                   | 319              | 1.09                      |
| <b>SD</b>  | 2.51                          | 2.36                   | 16.5             | 0.05                      |
| <b>COV (%)</b>   | 8.18                          | 8.00                   | 5.18             | 4.79                      |
| <b>Strain rate = <math>10^{-4} \text{ s}^{-1}</math></b> |                               |                        |                  |                           |
| Q13-2  | 31.0                          | 32.3                   | 312              | 1.01                      |
| Q13-13   | 27.4                          | 28.4                   | 300              | 1.07                      |
| Q13-27   | 34.8                          | 33.9                   | 305              | 0.89                      |
| Q13-51   | 33.4                          | 33.3                   | 358              | 1.07                      |
| <b>Average</b>   | 31.7                          | 32.0                   | 319              | 1.01                      |
| <b>SD</b>  | 3.24                          | 2.47                   | 26.6             | 0.08                      |
| <b>COV (%)</b>   | 10.2                          | 7.73                   | 8.35             | 8.40                      |
| <b>Strain rate = <math>10^{-2} \text{ s}^{-1}</math></b> |                               |                        |                  |                           |
| Q13-1  | 33.6                          | 30.9                   | 322              | 1.07                      |
| Q13-12   | 30.6                          | 31.1                   | 296              | 0.93                      |
| Q13-26   | 35.9                          | 35.9                   | 308              | 0.87                      |
| Q13-50   | 33.5                          | 31.9                   | 317              | 0.99                      |
| <b>Average</b>   | 33.4                          | 32.5                   | 311              | 0.97                      |
| <b>SD</b>  | 2.17                          | 2.34                   | 11.4             | 0.09                      |
| <b>COV (%)</b>   | 6.50                          | 7.21                   | 3.67             | 8.85                      |
| <b>Strain rate = <math>10 \text{ s}^{-1}</math></b>      |                               |                        |                  |                           |
| Q13-4  | 31.0                          | 22.6                   | 292              | 0.96                      |
| Q13-15   | 32.3                          | 25.2                   | 259              | 0.83                      |
| Q13-29   | 34.7                          | 24.7                   | 319              | 0.95                      |
| Q13-53   | 35.0                          | 25.9                   | 294              | 0.83                      |
| <b>Average</b>   | 33.3                          | 24.6                   | 291              | 0.89                      |
| <b>SD</b>  | 1.93                          | 1.42                   | 24.6             | 0.07                      |
| <b>COV (%)</b>   | 5.79                          | 5.78                   | 8.46             | 8.10                      |

**Table 50. Summary of tensile tests at various temperatures for the quasi-isotropic carbon-fiber composite**

| <b>Specimen number</b> | <b>Virgin stiffness (GPa)</b> | <b>Stiffness (GPa)</b> | <b>UTS (MPa)</b> | <b>Failure strain (%)</b> | <b>Stiffness factor</b> | <b>Strength factor</b> |
|------------------------|-------------------------------|------------------------|------------------|---------------------------|-------------------------|------------------------|
| <b>-40°C</b>           |                               |                        |                  |                           |                         |                        |
| Q11-4                  | 28.4                          | 29.4                   | 270              | 0.92                      | 1.04                    | 0.78                   |
| Q11-15                 | 27.5                          | 28.3                   | 280              | 0.98                      | 1.03                    | 0.81                   |
| Q11-21                 | 32.1                          | 35.1                   | 307              | 0.87                      | 1.09                    | 0.89                   |
| Q11-35                 | 34.8                          | 34.9                   | 337              | 0.97                      | 1.00                    | 0.97                   |
| Q11-42                 | 31.6                          | 34.5                   | 281              | 0.83                      | 1.09                    | 0.81                   |
| Q11-53                 | 32.5                          | 33.4                   | 303              | 0.91                      | 1.03                    | 0.88                   |
| <b>Average</b>         | 31.2                          | 32.6                   | 296              | 0.91                      | 1.05                    | 0.86                   |
| <b>SD</b>              | 2.73                          | 2.98                   | 24.5             | 0.06                      |                         |                        |
| <b>COV (%)</b>         | 8.85                          | 9.15                   | 8.28             | 6.30                      |                         |                        |
| <b>-10°C</b>           |                               |                        |                  |                           |                         |                        |
| Q11-10                 | 33.5                          | 34.3                   | 370              | 1.05                      | 1.02                    | 1.07                   |
| Q11-14                 | 26.9                          | 27.5                   | 266              | 0.98                      | 1.02                    | 0.77                   |
| Q11-26                 | 31.8                          | 32.8                   | 309              | 0.92                      | 1.03                    | 0.89                   |
| Q11-34                 | 29.5                          | 29.9                   | 293              | 0.97                      | 1.01                    | 0.85                   |
| Q11-40                 | 31.9                          | 32.3                   | 329              | 1.01                      | 1.01                    | 0.95                   |
| <b>Average</b>         | 30.7                          | 31.4                   | 313              | 0.99                      | 1.02                    | 0.91                   |
| <b>SD</b>              | 2.57                          | 2.68                   | 39.1             | 0.05                      |                         |                        |
| <b>COV (%)</b>         | 8.36                          | 8.53                   | 12.5             | 4.90                      |                         |                        |
| <b>23°C</b>            |                               |                        |                  |                           |                         |                        |
| Q11-5                  | 33.8                          | 33.8                   | 403              | 1.05                      | 1.00                    | 1.00                   |
| Q11-16                 | 31.9                          | 31.9                   | 362              | 1.07                      | 1.00                    | 1.00                   |
| Q11-22                 | 33.2                          | 33.2                   | 362              | 1.00                      | 1.00                    | 1.00                   |
| Q11-36                 | 30.1                          | 30.1                   | 362              | 0.99                      | 1.00                    | 1.00                   |
| Q11-43                 | 34.5                          | 34.5                   | 317              | 1.05                      | 1.00                    | 1.00                   |
| Q11-54                 | 33.6                          | 33.6                   | 341              | 0.99                      | 1.00                    | 1.00                   |
| <b>Average</b>         | 32.9                          | 32.9                   | 358              | 1.03                      | 1.00                    | 1.00                   |
| <b>SD</b>              | 1.60                          | 1.60                   | 28.4             | 0.04                      |                         |                        |
| <b>COV (%)</b>         | 4.87                          | 4.87                   | 7.95             | 3.48                      |                         |                        |
| <b>50°C</b>            |                               |                        |                  |                           |                         |                        |
| Q11-9                  | 32.0                          | 32.0                   | 301              | 0.93                      | 1.00                    | 0.87                   |
| Q11-13                 | 26.4                          | 27.2                   | 277              | 1.00                      | 1.03                    | 0.80                   |
| Q11-25                 | 33.0                          | 34.0                   | 336              | 0.99                      | 1.03                    | 0.97                   |
| Q11-33                 | 28.7                          | 28.5                   | 231              | 0.81                      | 0.99                    | 0.67                   |
| Q11-39                 | 29.3                          | 30.3                   | 326              | 1.06                      | 1.03                    | 0.94                   |
| Q11-49                 | 32.7                          | 33.5                   | 336              | 1.01                      | 1.02                    | 0.97                   |
| <b>Average</b>         | 30.4                          | 30.9                   | 301              | 0.97                      | 1.02                    | 0.87                   |
| <b>SD</b>              | 2.63                          | 2.73                   | 41.4             | 0.09                      |                         |                        |
| <b>COV (%)</b>         | 8.68                          | 8.84                   | 13.7             | 9.03                      |                         |                        |

**Table 50. Continued. Summary of tensile tests at various temperatures for the quasi-isotropic carbon-fiber composite**

| <b>Specimen number</b> | <b>Virgin stiffness (GPa)</b> | <b>Stiffness (GPa)</b> | <b>UTS (MPa)</b> | <b>Failure strain (%)</b> | <b>Stiffness factor</b> | <b>Strength factor</b> |
|------------------------|-------------------------------|------------------------|------------------|---------------------------|-------------------------|------------------------|
| <b>70°C</b>            |                               |                        |                  |                           |                         |                        |
| Q11-6                  | 32.6                          | 31.9                   | 331              | 1.04                      | 0.98                    | 0.96                   |
| Q11-17                 | 30.4                          | 29.4                   | 318              | 1.08                      | 0.97                    | 0.92                   |
| Q11-23                 | 31.2                          | 30.5                   | 307              | 0.97                      | 0.98                    | 0.89                   |
| Q11-37                 | 32.2                          | 30.8                   | 332              | 1.07                      | 0.96                    | 0.96                   |
| Q11-44                 | 32.0                          | 31.2                   | 308              | 1.03                      | 0.97                    | 0.89                   |
| Q11-55                 | 36.5                          | 33.2                   | 364              | 1.10                      | 0.91                    | 1.05                   |
| <b>Average</b>         | 32.5                          | 31.2                   | 327              | 1.05                      | 0.96                    | 0.95                   |
| <b>SD</b>              | 2.12                          | 1.29                   | 21.2             | 0.05                      |                         |                        |
| <b>COV (%)</b>         | 6.52                          | 4.15                   | 6.50             | 4.41                      |                         |                        |
| <b>120°C</b>           |                               |                        |                  |                           |                         |                        |
| Q11-7                  | 31.3                          | 28.5                   | 304              | 1.00                      | 0.91                    | 0.88                   |
| Q11-18                 | 30.3                          | 28.3                   | 260              | 0.98                      | 0.93                    | 0.75                   |
| Q11-24                 | 30.7                          | 27.7                   | 263              | 0.97                      | 0.90                    | 0.76                   |
| Q11-38                 | 32.8                          | 29.1                   | 302              | 1.03                      | 0.89                    | 0.87                   |
| Q11-45                 | 34.1                          | 31.0                   | 290              | 0.98                      | 0.91                    | 0.84                   |
| Q11-56                 | 34.5                          | 31.8                   | 309              | 1.04                      | 0.92                    | 0.89                   |
| <b>Average</b>         | 32.3                          | 29.4                   | 288              | 1.00                      | 0.91                    | 0.83                   |
| <b>SD</b>              | 1.78                          | 1.63                   | 21.5             | 0.03                      |                         |                        |
| <b>COV (%)</b>         | 5.52                          | 5.55                   | 7.46             | 2.90                      |                         |                        |

**Table 51. Temperature multiplication factors for determining at-temperature tensile modulus and strength from room-temperature values for the quasi-isotropic carbon-fiber composite**

| <b>Temperature (°C)</b> | <b>Stiffness multiplication factor</b> | <b>Strength multiplication factor</b> |
|-------------------------|--|---------------------------------------|
| <b>-40</b>              | 1.04                                   | 0.87                                  |
| <b>-10</b>              | 1.02                                   | 0.96                                  |
| <b>23</b>               | 1.00                                   | 1.00                                  |
| <b>50</b>               | 0.98                                   | 0.99                                  |
| <b>70</b>               | 0.96                                   | 0.97                                  |
| <b>120</b>              | 0.92                                   | 0.81                                  |



**Table 52. Summary of Poisson's ratio measurements at different temperatures for the quasi-isotropic carbon-fiber composite**

| Specimen number | Poisson's ratio |      |      |       |
|-----------------|-----------------|------|------|-------|
|                 | -40°C           | 23°C | 70°C | 120°C |
| Q13-8           | 0.28            | 0.28 | 0.29 | 0.31  |
| Q13-24          | 0.33            | 0.33 | 0.32 | 0.33  |
| Q13-32          | 0.31            | 0.32 | 0.31 | 0.35  |
| Q13-45          | 0.33            | 0.33 | 0.34 | 0.35  |
| Q13-57          | 0.31            | 0.32 | 0.31 | 0.35  |
| <b>Average</b>  | 0.31            | 0.32 | 0.31 | 0.34  |
| <b>SD</b>       | 0.02            | 0.02 | 0.02 | 0.02  |
| <b>COV (%)</b>  | 6.57            | 6.56 | 5.79 | 5.29  |

**Table 53. Effects of prior thermal cycling on mechanical properties of the quasi-isotropic carbon-fiber composite**

| Specimen number    | Virgin stiffness (GPa) | Stiffness (GPa) | Strength (MPa) | Stiffness factor | Strength factor |
|--------------------|------------------------|-----------------|----------------|------------------|-----------------|
| <b>Tension</b>     |                        |                 |                |                  |                 |
| Q13-7              | 30.1                   | 30.1            | 284            | 1.00             | 0.86            |
| Q13-18             | 31.0                   | 30.2            | 306            | 0.97             | 0.93            |
| Q13-21             | 29.3                   | 29.4            | 305            | 1.00             | 0.93            |
| Q13-33             | 29.5                   | 29.6            | 308            | 1.00             | 0.94            |
| Q13-42             | 31.5                   | 31.4            | 306            | 1.00             | 0.93            |
| Q13-56             | 34.4                   | 34.7            | 334            | 1.01             | 1.01            |
| <b>Average</b>     | 31.0                   | 30.9            | 307            | 1.00             | 0.93            |
| <b>SD</b>          | 1.88                   | 1.99            | 15.9           |                  |                 |
| <b>COV (%)</b>     | 6.08                   | 6.43            | 5.18           |                  |                 |
| <b>Compression</b> |                        |                 |                |                  |                 |
| Q18-7              | -                      | 29.2            | 246            | 0.93             | 1.11            |
| Q18-18             | -                      | 28.0            | 281            | 0.89             | 1.27            |
| Q18-21             | -                      | 29.7            | 279            | 0.95             | 1.26            |
| Q18-51             | -                      | 34.7            | 254            | 1.11             | 1.15            |
| <b>Average</b>     | -                      | 30.4            | 265            | 0.97             | 1.20            |
| <b>SD</b>          | -                      | 2.95            | 17.6           |                  |                 |
| <b>COV (%)</b>     | -                      | 9.72            | 6.66           |                  |                 |
| <b>Shear</b>       |                        |                 |                |                  |                 |
| Q18-7              | -                      | 9.38            | 224            | 0.77             | 0.99            |
| Q18-20             | -                      | 9.10            | 229            | 0.75             | 1.01            |
| Q18-21             | -                      | 8.89            | 212            | 0.73             | 0.94            |
| Q18-34             | -                      | 9.38            | 210            | 0.77             | 0.93            |
| <b>Average</b>     | -                      | 9.19            | 219            | 0.76             | 0.97            |
| <b>SD</b>          | -                      | 0.24            | 9.22           |                  |                 |
| <b>COV (%)</b>     | -                      | 2.59            | 4.21           |                  |                 |

**Table 54. Effect of exposure in 23°C distilled water on tensile strength and stiffness of the quasi-isotropic carbon-fiber composite**

| <b>Specimen number</b>        | <b>Virgin stiffness (GPa)</b> | <b>Stiffness (GPa)</b> | <b>UTS (MPa)</b> | <b>Change in stiffness (%)</b> | <b>Change in strength (%)</b> |
|-------------------------------|-------------------------------|------------------------|------------------|--------------------------------|-------------------------------|
| <b>Exposure Time = 500 h</b>  |                               |                        |                  |                                |                               |
| Q12-4                         | 35.2                          | 36.4                   | 374              | 1.03                           | 7.54                          |
| Q12-17                        | 29.7                          | 29.0                   | 303              | 0.98                           | -12.9                         |
| Q12-21                        | 30.1                          | 33.0                   | 330              | 1.10                           | -4.96                         |
| Q12-33                        | 32.0                          | 32.2                   | 292              | 1.01                           | -16.1                         |
| Q12-42                        | 37.5                          | 38.5                   | 355              | 1.03                           | 2.18                          |
| Q12-48                        | 36.6                          | 37.2                   | 414              | 1.02                           | 19.2                          |
| <b>Average</b>                | 33.5                          | 34.4                   | 345              | 1.03                           | -0.84                         |
| <b>SD</b>                     | 3.37                          | 3.59                   | 45.8             |                                |                               |
| <b>COV (%)</b>                | 10.1                          | 10.5                   | 13.3             |                                |                               |
| <b>Exposure Time = 1000 h</b> |                               |                        |                  |                                |                               |
| Q12-12                        | 30.7                          | 32.3                   | 346              | 1.05                           | -0.34                         |
| Q12-23                        | 34.0                          | 35.2                   | 373              | 1.04                           | 7.36                          |
| Q12-34                        | 33.3                          | 32.6                   | 352              | 0.98                           | 1.39                          |
| Q12-44                        | 33.3                          | 32.5                   | 341              | 0.98                           | -1.83                         |
| Q12-50                        | 33.5                          | 33.6                   | 327              | 1.00                           | -6.02                         |
| <b>Average</b>                | 33.0                          | 33.2                   | 348              | 1.01                           | 0.11                          |
| <b>SD</b>                     | 1.30                          | 1.21                   | 16.8             |                                |                               |
| <b>COV (%)</b>                | 3.93                          | 3.63                   | 4.84             |                                |                               |
| <b>Exposure Time = 1506 h</b> |                               |                        |                  |                                |                               |
| Q12-7                         | 32.3                          | 32.4                   | 305              | 1.00                           | -12.1                         |
| Q12-13                        | 32.5                          | 33.0                   | 359              | 1.02                           | 3.37                          |
| Q12-24                        | 34.3                          | 33.8                   | 346              | 0.99                           | -0.40                         |
| Q12-35                        | 33.5                          | 34.3                   | 365              | 1.02                           | 4.96                          |
| Q12-51                        | 33.6                          | 34.1                   | 354              | 1.01                           | 1.79                          |
| <b>Average</b>                | 33.2                          | 33.5                   | 346              | 1.01                           | -0.48                         |
| <b>SD</b>                     | 0.83                          | 0.80                   | 23.8             |                                |                               |
| <b>COV (%)</b>                | 2.50                          | 2.38                   | 6.90             |                                |                               |
| <b>Exposure Time = 1990 h</b> |                               |                        |                  |                                |                               |
| Q12-8                         | 30.6                          | 31.5                   | 354              | 1.03                           | 1.79                          |
| Q12-14                        | 31.9                          | 32.4                   | 321              | 1.02                           | -7.54                         |
| Q12-25                        | 35.3                          | 36.0                   | 364              | 1.02                           | 4.76                          |
| Q12-37                        | 32.1                          | 33.0                   | 354              | 1.03                           | 1.79                          |
| Q12-46                        | 32.0                          | 34.1                   | 325              | 1.07                           | -6.35                         |
| Q12-52                        | 32.4                          | 33.6                   | 350              | 1.04                           | 0.60                          |
| <b>Average</b>                | 32.4                          | 33.4                   | 345              | 1.03                           | -0.83                         |
| <b>SD</b>                     | 1.56                          | 1.55                   | 17.5             |                                |                               |
| <b>COV (%)</b>                | 4.81                          | 4.64                   | 5.06             |                                |                               |

**Table 54. Continued. Effect of exposure in 23°C distilled water on tensile strength and stiffness of the quasi-isotropic carbon-fiber composite**

| <b>Specimen number</b>        | <b>Virgin stiffness (GPa)</b> | <b>Stiffness (GPa)</b> | <b>UTS (MPa)</b> | <b>Change in stiffness (%)</b> | <b>Change in strength (%)</b> |
|-------------------------------|-------------------------------|------------------------|------------------|--------------------------------|-------------------------------|
| <b>Exposure Time = 4818 h</b> |                               |                        |                  |                                |                               |
| Q12-9                         | 33.1                          | 31.2                   | 321              | 0.94                           | -7.74                         |
| Q12-15                        | 30.0                          | 30.4                   | 300              | 1.01                           | -13.7                         |
| Q12-26                        | 31.0                          | 31.6                   | 330              | 1.02                           | -4.96                         |
| Q12-38                        | 33.5                          | 34.6                   | 361              | 1.03                           | 3.77                          |
| Q12-47                        | 37.0                          | 37.0                   | 360              | 1.00                           | 3.57                          |
| Q12-53                        | 34.5                          | 34.1                   | 345              | 0.99                           | -0.79                         |
| <b>Average</b>                | 33.2                          | 33.2                   | 336              | 1.00                           | -3.31                         |
| <b>SD</b>                     | 2.50                          | 2.51                   | 23.8             |                                |                               |
| <b>COV (%)</b>                | 7.54                          | 7.58                   | 7.09             |                                |                               |

**Table 55. Effect of exposure in 70% relative humidity air on tensile strength and stiffness of the quasi-isotropic carbon-fiber composite**

| <b>Specimen number</b>        | <b>Virgin stiffness (GPa)</b> | <b>Stiffness (GPa)</b> | <b>UTS (MPa)</b> | <b>Failure strain (%)</b> | <b>Change in stiffness (%)</b> | <b>Change in strength (%)</b> |
|-------------------------------|-------------------------------|------------------------|------------------|---------------------------|--------------------------------|-------------------------------|
| <b>Exposure Time = 1000 h</b> |                               |                        |                  |                           |                                |                               |
| Q12-10                        | 28.7                          | 28.6                   | 266              | 0.93                      | 1.00                           | -23.4                         |
| Q12-18                        | 32.6                          | 33.0                   | 330              | 1.01                      | 1.01                           | -4.97                         |
| Q12-27                        | 32.4                          | 32.9                   | 345              | 1.11                      | 1.02                           | -0.78                         |
| Q12-30                        | 34.9                          | 35.0                   | 378              | 1.10                      | 1.00                           | 8.69                          |
| Q12-39                        | 33.3                          | 33.4                   | 343              | 1.05                      | 1.00                           | -1.21                         |
| Q12-55                        | 30.8                          | 31.3                   | 341              | 1.09                      | 1.02                           | -2.00                         |
| <b>Average</b>                | 32.1                          | 32.4                   | 334              | 1.05                      | 1.01                           | -3.95                         |
| <b>SD</b>                     | 2.14                          | 2.19                   | 37.0             | 0.07                      |                                |                               |
| <b>COV (%)</b>                | 6.66                          | 6.77                   | 11.1             | 6.57                      |                                |                               |
| <b>Exposure Time = 1990 h</b> |                               |                        |                  |                           |                                |                               |
| Q12-2                         | 33.0                          | 32.5                   | 326              | 0.99                      | 0.98                           | -6.15                         |
| Q12-19                        | 30.5                          | 30.3                   | 338              | 1.12                      | 0.99                           | -2.78                         |
| Q12-28                        | 31.3                          | 31.9                   | 326              | 1.01                      | 1.02                           | -6.15                         |
| Q12-31                        | 30.5                          | 29.6                   | 312              | 1.15                      | 0.97                           | -10.1                         |
| Q12-40                        | 34.0                          | 34.3                   | 303              | 0.88                      | 1.01                           | -12.9                         |
| Q12-56                        | 34.9                          | 34.5                   | 361              | 1.05                      | 0.99                           | 3.77                          |
| <b>Average</b>                | 32.4                          | 32.2                   | 328              | 1.03                      | 0.99                           | -5.72                         |
| <b>SD</b>                     | 1.88                          | 2.01                   | 20.4             | 0.10                      |                                |                               |
| <b>COV (%)</b>                | 5.80                          | 6.25                   | 6.2              | 9.42                      |                                |                               |
| <b>Exposure Time = 4818 h</b> |                               |                        |                  |                           |                                |                               |
| Q12-11                        | 31.1                          | 32.3                   | 365              | 1.12                      | 1.04                           | 5.16                          |
| Q12-20                        | 31.4                          | 31.6                   | 309              | 0.97                      | 1.01                           | -11.1                         |
| Q12-29                        | 33.5                          | 34.3                   | 327              | 0.94                      | 1.02                           | -5.95                         |
| Q12-32                        | 30.7                          | 30.3                   | 316              | 1.06                      | 0.99                           | -9.13                         |
| Q12-41                        | 34.1                          | 34.9                   | 370              | 1.08                      | 1.02                           | 6.55                          |
| Q12-57                        | 35.7                          | 35.3                   | 361              | 1.02                      | 0.99                           | 3.77                          |
| <b>Average</b>                | 32.8                          | 33.1                   | 341              | 1.03                      | 1.01                           | -1.79                         |
| <b>SD</b>                     | 1.99                          | 2.01                   | 27.1             | 0.07                      |                                |                               |
| <b>COV (%)</b>                | 6.08                          | 6.08                   | 7.9              | 6.61                      |                                |                               |

**Table 56. Effects of 100-h exposure in windshield washer fluid on tensile stiffness and strength of the quasi-isotropic carbon-fiber composite**

| <b>Specimen number</b> | <b>Virgin stiffness (GPa)</b> | <b>Stiffness (GPa)</b> | <b>UTS (MPa)</b> | <b>Stiffness factor</b> | <b>Strength factor</b> |
|------------------------|-------------------------------|------------------------|------------------|-------------------------|------------------------|
| Q13-6                  | 28.2                          | 29.2                   | 299              | 1.04                    | 0.91                   |
| Q13-17                 | 30.5                          | 29.7                   | 319              | 0.97                    | 0.97                   |
| Q13-23                 | 33.0                          | 33.6                   | 329              | 1.02                    | 1.00                   |
| Q13-37                 | 33.5                          | 32.3                   | 365              | 0.96                    | 1.11                   |
| Q13-44                 | 34.0                          | 34.7                   | 347              | 1.02                    | 1.05                   |
| Q13-55                 | 33.8                          | 34.9                   | 325              | 1.03                    | 0.99                   |
| <b>Average</b>         | 32.2                          | 32.4                   | 331              | 1.01                    | 1.01                   |
| <b>SD</b>              | 2.32                          | 2.47                   | 22.9             |                         |                        |
| <b>COV (%)</b>         | 7.23                          | 7.63                   | 6.92             |                         |                        |

**Table 57. Summary of room-temperature compressive tests for the quasi-isotropic carbon-fiber composite**

| <b>Specimen number</b> | <b>Compressive stiffness (GPa)</b> | <b>UCS (MPa)</b> | <b>Failure strain (%)</b> |
|------------------------|------------------------------------|------------------|---------------------------|
| Q18-4                  | 29.6                               | 197              | 0.63                      |
| Q18-7                  | 30.3                               | 252              | 0.81                      |
| Q18-10                 | 32.1                               | 197              | 0.63                      |
| Q18-17                 | 33.0                               | 236              | 0.74                      |
| Q18-29                 | 33.4                               | 220              | 0.63                      |
| Q18-32                 | 38.0                               | 223              | 0.65                      |
| Q18-39                 | 27.0                               | 243              | 1.13                      |
| Q18-46                 | 28.8                               | 230              | <sup>a</sup>              |
| Q18-48                 | 31.0                               | 214              | 0.79                      |
| Q21-1                  | 32.2                               | 196              | 0.64                      |
| Q21-2                  | 29.1                               | 232              | 0.78                      |
| Q21-3                  | 37.2                               | 183              | 0.79                      |
| Q22-1                  | 29.5                               | 239              | 0.81                      |
| Q22-2                  | 31.2                               | 234              | 0.77                      |
| Q22-3                  | 34.5                               | 190              | 0.62                      |
| Q22-4                  | 33.1                               | 252              | 0.70                      |
| Q23-1                  | 32.2                               | 225              | 0.70                      |
| Q23-2                  | 30.5                               | 215              | 0.66                      |
| Q23-3                  | 29.6                               | 208              | 0.71                      |
| Q23-4                  | 29.5                               | <sup>a</sup>     | <sup>a</sup>              |
| Q24-1                  | 29.8                               | 237              | 0.84                      |
| Q24-2                  | 32.5                               | 257              | 0.83                      |
| Q24-3                  | 27.4                               | 182              | 0.79                      |
| Q24-4                  | 38.0                               | 244              | 0.69                      |
| Q25-1                  | 31.7                               | 253              | 0.76                      |
| Q25-2                  | 30.0                               | 225              | 0.73                      |
| Q25-3                  | 35.1                               | 252              | 0.63                      |
| Q25-4                  | 32.7                               | 183              | 0.54                      |
| Q26-1                  | <sup>a</sup>                       | 231              | <sup>a</sup>              |
| Q26-2                  | <sup>a</sup>                       | 230              | <sup>a</sup>              |
| Q26-3                  | 39.0                               | 252              | 0.69                      |
| Q26-4                  | 41.0                               | 243              | 0.56                      |
| Q27-1                  | 31.1                               | 246              | 0.62                      |
| Q27-2                  | 32.5                               | 237              | 0.63                      |
| Q27-3                  | <sup>a</sup>                       | 223              | <sup>a</sup>              |
| Q27-4                  | 33.4                               | 241              | 0.71                      |
| Q28-1                  | 27.0                               | 227              | 1.04                      |
| Q28-2                  | 32.6                               | 197              | 0.59                      |
| Q28-3                  | 29.2                               | 219              | 0.71                      |
| Q28-4                  | <sup>a</sup>                       | 212              | <sup>a</sup>              |
| <b>Average</b>         | 32.1                               | 225              | 0.72                      |
| <b>SD</b>              | 3.34                               | 21.6             | 0.12                      |
| <b>COV (%)</b>         | 10.4                               | 9.62             | 16.9                      |

<sup>a</sup> No strain measurement

**Table 58. Compressive properties of the quasi-isotropic carbon-fiber composite at different temperatures**

| Specimen number | Compressive stiffness<br>(GPa) | UCS (MPa) | Failure strain<br>(%) |
|-----------------|--------------------------------|-----------|-----------------------|
| <b>70°C</b>     |                                |           |                       |
| Q18-2           | 30.5                           | 203       | 0.64                  |
| Q18-5           | 29.9                           | 160       | 0.64                  |
| Q18-12          | <sup>a</sup>                   | 203       |                       |
| Q18-28          | 30.2                           | 203       | 0.65                  |
| Q18-41          | 29.5                           | 215       | 0.60                  |
| <b>Average</b>  | 30.0                           | 192       | 0.63                  |
| <b>SD</b>       | 0.43                           | 21.2      | 0.02                  |
| <b>COV (%)</b>  | 1.40                           | 11.0      | 3.51                  |
| <b>120°C</b>    |                                |           |                       |
| Q18-3           | 28.4                           | 136       | 0.49                  |
| Q18-13          | 22.8                           | 106       | 0.55                  |
| Q18-30          | <sup>a</sup>                   | 124       | <sup>a</sup>          |
| Q18-34          | 27.4                           | 130       | 0.55                  |
| Q18-42          | 28.5                           | 128       | 0.46                  |
| <b>Average</b>  | 26.8                           | 124       | 0.51                  |
| <b>SD</b>       | 2.70                           | 11.4      | 0.04                  |
| <b>COV (%)</b>  | 10.1                           | 9.17      | 8.78                  |
| <b>-40°C</b>    |                                |           |                       |
| Q18-8           | 28.1                           | 226       | 0.89                  |
| Q18-11          | 32.0                           | 252       | 0.88                  |
| Q18-27          | 32.3                           | 237       | 0.64                  |
| Q18-31          | 30.7                           | 203       | 0.71                  |
| Q18-45          | 33.9                           | 238       | 0.52                  |
| <b>Average</b>  | 30.8                           | 230       | 0.78                  |
| <b>SD</b>       | 2.17                           | 18.3      | 0.16                  |
| <b>COV (%)</b>  | 7.04                           | 7.96      | 20.3                  |

<sup>a</sup> No strain measurement

**Table 59. Temperature multiplication factors for determining at-temperature compressive stiffness and strength from room-temperature values for the quasi-isotropic carbon-fiber composite**

| Temperature<br>(°C) | Stiffness multiplication<br>factor | Strength multiplication<br>factor |
|---------------------|------------------------------------|-----------------------------------|
| <b>-40</b>          | 1.02                               | 1.02                              |
| <b>23</b>           | 1.00                               | 1.00                              |
| <b>70</b>           | 0.95                               | 0.86                              |
| <b>120</b>          | 0.85                               | 0.58                              |

**Table 60. Effects of 1000-h exposure in 23°C distilled water on room-temperature compressive properties of the quasi-isotropic carbon-fiber composite**

| Specimen number | Compressive stiffness (GPa) | UCS (MPa) | Stiffness factor | Strength factor |
|-----------------|-----------------------------|-----------|------------------|-----------------|
| Q18-6           | 31.3                        | 206       | 1.00             | 0.93            |
| Q18-16          | 28.8                        | 212       | 0.92             | 0.96            |
| Q18-20          | 35.8                        | 180       | 1.14             | 0.82            |
| Q18-37          | <sup>a</sup>                | 219       | <sup>a</sup>     | 0.99            |
| Q18-44          | 26.1                        | 216       | 0.83             | 0.98            |
| Q18-50          | 28.6                        | 211       | 0.91             | 0.96            |
| <b>Average</b>  | 30.1                        | 207       | 0.96             | 0.94            |
| <b>SD</b>       | 3.67                        | 14.1      |                  |                 |
| <b>COV (%)</b>  | 12.2                        | 6.81      |                  |                 |

<sup>a</sup> No strain measurement

**Table 61. Effects of 100-h exposure in windshield washer fluid on room-temperature compressive strength of the quasi-isotropic carbon-fiber composite**

| Specimen number | UCS (MPa) | Strength design factor |
|-----------------|-----------|------------------------|
| Q18-15          | 228       | 1.03                   |
| Q18-19          | 226       | 1.02                   |
| Q18-33          | 223       | 1.01                   |
| Q18-38          | 207       | 0.94                   |
| Q18-43          | 211       | 0.95                   |
| Q18-49          | 210       | 0.95                   |
| <b>Average</b>  | 218       | 0.98                   |
| <b>SD</b>       | 9.18      |                        |
| <b>COV (%)</b>  | 4.20      |                        |

**Table 62. Summary of in-air room-temperature shear properties of the quasi-isotropic carbon-fiber composite**

| Specimen number | Shear modulus (GPa) | Shear strength (MPa) | Failure strain (%) |
|-----------------|---------------------|----------------------|--------------------|
| Q18-1           | 10.9                | 217                  | 2.48               |
| Q18-3           | 12.2                | 235                  | 2.51               |
| Q18-26          | 13.0                | 238                  | 2.01               |
| Q18-29          | 12.2                | 212                  | 2.33               |
| Q18-30          | 13.9                | 244                  | 2.13               |
| Q18-39          | 11.2                | 238                  | 2.43               |
| Q18-11          | <sup>a</sup>        | 211                  | <sup>a</sup>       |
| Q18-14          | <sup>a</sup>        | 212                  | <sup>a</sup>       |
| <b>Average</b>  | 12.2                | 226                  | 2.32               |
| <b>SD</b>       | 1.11                | 14.1                 | 0.20               |
| <b>COV (%)</b>  | 9.11                | 6.24                 | 8.77               |

<sup>a</sup> No strain measurement



**Table 63. Shear properties of the quasi-isotropic carbon-fiber composite at different temperatures**

| <b>Specimen number</b> | <b>Shear Modulus (GPa)</b> | <b>Shear strength (MPa)</b> | <b>Failure strain (%)</b> |
|------------------------|----------------------------|-----------------------------|---------------------------|
| <b>70°C</b>            |                            |                             |                           |
| Q18-13                 | 11.9                       | 178                         | 1.75                      |
| Q18-16                 | 11.5                       | 200                         | 2.18                      |
| Q18-25                 | 11.9                       | 182                         | 2.04                      |
| Q18-28                 | 11.9                       | 197                         | 1.97                      |
| Q18-40                 | 12.1                       | 202                         | 2.32                      |
| <b>Average</b>         | 11.9                       | 192                         | 2.05                      |
| <b>SD</b>              | 0.22                       | 11.0                        | 0.22                      |
| <b>COV (%)</b>         | 1.85                       | 5.74                        | 10.5                      |
| <b>120°C</b>           |                            |                             |                           |
| Q18-10                 | 10.7                       | 138                         | 1.65                      |
| Q18-17                 | 11.3                       | 125                         | 1.82                      |
| Q18-24                 | 10.8                       | 133                         | 1.43                      |
| Q18-31                 | 11.2                       | 136                         | 1.24                      |
| Q18-37                 | 10.8                       | 127                         | 1.30                      |
| <b>Average</b>         | 11.0                       | 132                         | 1.49                      |
| <b>SD</b>              | 0.27                       | 5.63                        | 0.24                      |
| <b>COV (%)</b>         | 2.47                       | 4.27                        | 16.3                      |
| <b>-40°C</b>           |                            |                             |                           |
| Q18-2                  | 12.4                       | 235                         | 2.22                      |
| Q18-15                 | 12.1                       | 271                         | 2.61                      |
| Q18-27                 | 11.9                       | 232                         | 2.16                      |
| Q18-38                 | 12.5                       | 249                         | 2.31                      |
| <b>Average</b>         | 12.2                       | 247                         | 2.33                      |
| <b>SD</b>              | 0.28                       | 17.8                        | 0.20                      |
| <b>COV (%)</b>         | 2.25                       | 7.21                        | 8.59                      |

**Table 64. Temperature multiplication factors for determining at-temperature shear modulus and strength from room-temperature values for the quasi-isotropic carbon-fiber composite**

| <b>Temperature (°C)</b> | <b>Stiffness multiplication factor</b> | <b>Strength multiplication factor</b> |
|-------------------------|--|---------------------------------------|
| <b>-40</b>              | 0.99                                   | 1.06                                  |
| <b>23</b>               | 1.00                                   | 1.00                                  |
| <b>70</b>               | 0.97                                   | 0.85                                  |
| <b>120</b>              | 0.89                                   | 0.59                                  |

**Table 65. Effects of 1000-h exposure in 23°C distilled water on room-temperature shear properties of the quasi-isotropic carbon-fiber composite**

| <b>Specimen number</b> | <b>Shear modulus (GPa)</b> | <b>Shear strength (MPa)</b> | <b>Stiffness factor</b> | <b>Strength factor</b> |
|------------------------|----------------------------|-----------------------------|-------------------------|------------------------|
| Q18-5                  | 13.1                       | 226                         | 1.07                    | 1.00                   |
| Q18-8                  | 13.1                       | 244                         | 1.07                    | 1.08                   |
| Q18-18                 | 10.3                       | 190                         | 0.84                    | 0.84                   |
| Q18-22                 | 13.0                       | 238                         | 1.06                    | 1.05                   |
| Q18-33                 | 11.0                       | 209                         | 0.90                    | 0.93                   |
| Q18-35                 | <sup>a</sup>               | 227                         | <sup>a</sup>            | 1.00                   |
| <b>Average</b>         | 12.1                       | 223                         | 0.99                    | 0.98                   |
| <b>SD</b>              | 1.34                       | 19.9                        |                         |                        |
| <b>COV (%)</b>         | 11.1                       | 8.92                        |                         |                        |

<sup>a</sup> No strain measurement

**Table 66. Effects of 100-h exposure in windshield washer fluid on room-temperature shear strength of the quasi-isotropic carbon-fiber composite**

| <b>Specimen number</b> | <b>Shear strength (MPa)</b> | <b>Strength design factor</b> |
|------------------------|-----------------------------|-------------------------------|
| Q18-6                  | 237                         | 1.05                          |
| Q18-9                  | 231                         | 1.02                          |
| Q18-19                 | 218                         | 0.97                          |
| Q18-23                 | 224                         | 0.99                          |
| Q18-32                 | 221                         | 0.98                          |
| Q18-36                 | 197                         | 0.87                          |
| <b>Average</b>         | 222                         | 1.01                          |
| <b>SD</b>              | 13.7                        |                               |
| <b>COV (%)</b>         | 6.19                        |                               |

**Table 67. Uniaxial flexural properties of the quasi-isotropic carbon-fiber composite at different temperatures**

| <b>T beams</b>         |                  |                           | <b>L beams</b>         |                  |                           |
|------------------------|------------------|---------------------------|------------------------|------------------|---------------------------|
| <b>Specimen number</b> | <b>MOR (MPa)</b> | <b>Temperature factor</b> | <b>Specimen number</b> | <b>MOR (MPa)</b> | <b>Temperature factor</b> |
| <b>-40°C</b>           |                  |                           | <b>-40°C</b>           |                  |                           |
| Q19-5T                 | 531              | 0.85                      | Q19-1L                 | 601              | 1.02                      |
| Q19-7T                 | 669              | 1.08                      | Q19-8L                 | 548              | 0.93                      |
| Q19-16T                | 585              | 0.94                      | Q19-14L                | 565              | 0.96                      |
| Q19-19T                | 497              | 0.80                      | Q19-19L                | 628              | 1.06                      |
| Q19-26T                | 717              | 1.15                      | Q19-25L                | 612              | 1.04                      |
| Q19-34T                | 692              | 1.11                      | Q19-32L                | 627              | 1.06                      |
| <b>Average</b>         | 615              | 0.99                      | <b>Average</b>         | 597              | 1.01                      |
| <b>SD</b>              | 90.7             |                           | <b>SD</b>              | 33.2             |                           |
| <b>COV (%)</b>         | 14.7             |                           | <b>COV (%)</b>         | 5.57             |                           |
| <b>23°C</b>            |                  |                           | <b>23°C</b>            |                  |                           |
| Q19-3T                 | 571              | 1.00                      | Q19-3L                 | 567              | 1.00                      |
| Q19-9T                 | 610              | 1.00                      | Q19-10L                | 590              | 1.00                      |
| Q19-15T                | 643              | 1.00                      | Q19-16L                | 614              | 1.00                      |
| Q19-20T                | 620              | 1.00                      | Q19-21L                | 576              | 1.00                      |
| Q19-29T                | 681              | 1.00                      | Q19-27L                | 500              | 1.00                      |
| Q19-31T                | 609              | 1.00                      | Q19-34L                | 699              | 1.00                      |
| <b>Average</b>         | 622              | 1.00                      | <b>Average</b>         | 591              | 1.00                      |
| <b>SD</b>              | 37.0             |                           | <b>SD</b>              | 65.2             |                           |
| <b>COV (%)</b>         | 5.94             |                           | <b>COV (%)</b>         | 11.0             |                           |
| <b>70°C</b>            |                  |                           | <b>70°C</b>            |                  |                           |
| Q19-6T                 | 500              | 0.80                      | Q19-2L                 | 426              | 0.72                      |
| Q19-10T                | 534              | 0.86                      | Q19-9L                 | 410              | 0.69                      |
| Q19-13T                | 593              | 0.95                      | Q19-15L                | 379              | 0.64                      |
| Q19-21T                | 526              | 0.85                      | Q19-20L                | 427              | 0.72                      |
| Q19-30T                | 538              | 0.86                      | Q19-26L                | 475              | 0.80                      |
| Q19-32T                | 505              | 0.81                      | Q19-33L                | 485              | 0.82                      |
| <b>Average</b>         | 533              | 0.86                      | <b>Average</b>         | 434              | 0.73                      |
| <b>SD</b>              | 33.3             |                           | <b>SD</b>              | 40.0             |                           |
| <b>COV (%)</b>         | 6.25             |                           | <b>COV (%)</b>         | 9.22             |                           |
| <b>120°C</b>           |                  |                           | <b>120°C</b>           |                  |                           |
| Q19-4T                 | 245              | 0.39                      | Q19-4L                 | 278              | 0.47                      |
| Q19-8T                 | 265              | 0.43                      | Q19-11L                | 255              | 0.43                      |
| Q19-14T                | 338              | 0.54                      | Q19-17L                | 257              | 0.43                      |
| Q19-22T                | 372              | 0.60                      | Q19-22L                | 265              | 0.45                      |
| Q19-25T                | 399              | 0.64                      | Q19-28L                | 271              | 0.46                      |
| Q19-33T                | 281              | 0.45                      | Q19-35L                | 237              | 0.40                      |
| <b>Average</b>         | 317              | 0.51                      | <b>Average</b>         | 261              | 0.44                      |
| <b>SD</b>              | 62.2             |                           | <b>SD</b>              | 14.4             |                           |
| <b>COV (%)</b>         | 19.7             |                           | <b>COV (%)</b>         | 5.51             |                           |

**Table 68. Effects of 1000-h exposure in 23°C distilled water on uniaxial flexural properties of the quasi-isotropic carbon-fiber composite**

| <b>Specimen number</b> | <b>MOR (MPa)</b> | <b>Strength factor</b> |
|------------------------|------------------|------------------------|
| <b>T beams</b>         |                  |                        |
| Q19-1T                 | 589              | 0.95                   |
| Q19-12T                | 592              | 0.95                   |
| Q19-17T                | 637              | 1.02                   |
| Q19-24T                | 541              | 0.87                   |
| Q19-27T                | 546              | 0.88                   |
| Q19-35T                | 647              | 1.04                   |
| <b>Average</b>         | 592              | 0.95                   |
| <b>SD</b>              | 44.2             |                        |
| <b>COV (%)</b>         | 7.47             |                        |
| <b>L beams</b>         |                  |                        |
| Q19-5L                 | 537              | 0.91                   |
| Q19-7L                 | 497              | 0.84                   |
| Q19-12L                | 560              | 0.95                   |
| Q19-23L                | 523              | 0.88                   |
| Q19-29L                | 576              | 0.97                   |
| Q19-31L                | 621              | 1.05                   |
| <b>Average</b>         | 552              | 0.93                   |
| <b>SD</b>              | 43.6             |                        |
| <b>COV (%)</b>         | 7.89             |                        |

**Table 69. Effects of 100-h exposure in windshield washer fluid on uniaxial flexural properties of the quasi-isotropic carbon-fiber composite**

| <b>Specimen number</b> | <b>MOR (MPa)</b> | <b>Strength factor</b> |
|------------------------|------------------|------------------------|
| <b>T beams</b>         |                  |                        |
| Q19-2T                 | 607              | 0.98                   |
| Q19-11T                | 614              | 0.99                   |
| Q19-18T                | 672              | 1.08                   |
| Q19-23T                | 632              | 1.02                   |
| Q19-28T                | 664              | 1.07                   |
| Q19-36T                | 597              | 0.96                   |
| <b>Average</b>         | 631              | 1.01                   |
| <b>SD</b>              | 31.0             |                        |
| <b>COV (%)</b>         | 4.91             |                        |
| <b>L beams</b>         |                  |                        |
| Q19-6L                 | 589              | 1.00                   |
| Q19-13L                | 558              | 0.94                   |
| Q19-18L                | 502              | 0.85                   |
| Q19-24L                | 608              | 1.03                   |
| Q19-30L                | 491              | 0.83                   |
| Q19-36L                | 566              | 0.96                   |
| <b>Average</b>         | 552              | 0.93                   |
| <b>SD</b>              | 46.8             |                        |
| <b>COV (%)</b>         | 8.48             |                        |

**Table 70. Biaxial flexural properties of the quasi-isotropic carbon-fiber composite at different temperatures**

| <b>Specimen number</b> | <b>Maximum load (N)</b> | <b>Temperature factor</b> |
|------------------------|-------------------------|---------------------------|
| <b>23°C</b>            |                         |                           |
| Q19-1                  | 9643                    | 1.00                      |
| Q19-3                  | 10267                   | 1.00                      |
| Q19-6                  | 9390                    | 1.00                      |
| Q19-7                  | 10211                   | 1.00                      |
| Q19-17                 | 9329                    | 1.00                      |
| Q19-23                 | 9599                    | 1.00                      |
| <b>Average</b>         | 9740                    | 1.00                      |
| <b>SD</b>              | 405                     |                           |
| <b>COV (%)</b>         | 4.16                    |                           |
| <b>120°C</b>           |                         |                           |
| Q19-9                  | 3739                    | 0.38                      |
| Q19-11                 | 4126                    | 0.42                      |
| Q19-13                 | 4370                    | 0.45                      |
| Q19-18                 | 4421                    | 0.45                      |
| Q19-19                 | 5051                    | 0.52                      |
| Q19-24                 | 4196                    | 0.43                      |
| <b>Average</b>         | 4317                    | 0.44                      |
| <b>SD</b>              | 433                     |                           |
| <b>COV (%)</b>         | 10.0                    |                           |

**Table 71. Effects of environment on biaxial flexural properties of the quasi-isotropic carbon-fiber composite**

| <b>Specimen number</b>                  | <b>Maximum load (N)</b> | <b>Design factor</b> |
|---|-------------------------|----------------------|
| <b>1000 h in 23°C distilled water</b>   |                         |                      |
| Q19-5                                   | 9831                    | 1.01                 |
| Q19-10                                  | 8856                    | 0.91                 |
| Q19-12                                  | 8732                    | 0.90                 |
| Q19-14                                  | 8687                    | 0.89                 |
| Q19-16                                  | 8972                    | 0.92                 |
| <b>Average</b>                          | 9016                    | 0.93                 |
| <b>SD</b>                               | 469                     |                      |
| <b>COV (%)</b>                          | 5.20                    |                      |
| <b>100 h in windshield washer fluid</b> |                         |                      |
| Q19-2                                   | 10113                   | 1.04                 |
| Q19-4                                   | 9117                    | 0.94                 |
| Q19-8                                   | 9956                    | 1.02                 |
| Q19-15                                  | 9656                    | 0.99                 |
| Q19-20                                  | 9168                    | 0.94                 |
| Q19-22                                  | 9521                    | 0.98                 |
| <b>Average</b>                          | 9588                    | 0.98                 |
| <b>SD</b>                               | 404                     |                      |
| <b>COV (%)</b>                          | 4.22                    |                      |

# INTERNAL DISTRIBUTION

- |                   |                                |
|-------------------|--------------------------------|
| 1. R. G. Boeman   | 17. M. B. Ruggles-Wrenn        |
| 2. J. G. Hansen   | 18. P. A. Sklad                |
| 3. A. Ionita      | 19. C. D. Warren               |
| 4. E. Lara-Curzio | 20-21. Y. J. Weitsman          |
| 5-14 D. J. Naus   | 22. R. E. Ziegler              |
| 15. R. E. Norris  | 23. ORNL Laboratory Records-RC |
| 16. M. H. Rawlins |                                |

# EXTERNAL DISTRIBUTION

24. M. Abdallah, Hexcel Carbon Fibers, Research and Technology, P.O. Box 18748, Salt Lake City, UT 84118-0748
25. M. M. Fisher, American Plastics Council, 1300 Wilson Boulevard, Suite 800, Arlington, VA 22209
26. R. B. Freeman, The Budd Company, 1515 Atlantic Boulevard, Auburn Hills, MI 48326
27. R. Gjerde, Textron Automotive Company, 100 Brady Road, Americus, GA 31709
- 28-57. L. Berger, Automotive Composite Consortium, General Motors, 30500 Mound Road, Mail Code 480-106-710, Box 9055, Warren, MI 48090-9055
58. J. M. Henshaw, Department of Mechanical Engineering, The University of Tulsa, 600 S. College Avenue, Tulsa, OK 74104-3189
59. G. A. Holmes, National Institute of Standards and Technology, Bldg. 224, Room B116, Mail Stop: Room B108, Gaithersburg, MD 20899
60. D. Kossak, Cambridge Industries, 29333 Stephenson Highway, Madison Heights, MI 48071
61. F. G. Krautz, Vetrotex Certainteed, 4515 Allendale Road, Wichita Falls, TX 76310-2199
62. G. R. Miesel, Ashland Chemical Company, 900 Wilshire Drive, Suite 100, Troy, MI 48084
63. E. Ostwald, Dow Automotive, 1600 Harmon Road, Auburn Hills, MI 48326
64. S. R. Reeve, National Composite Center, 2000 Composite Drive, Kettering, OH 45420
65. C. R. Schultheisz, National Institute of Standards and Technology, Building 224, Room A209, Gaithersburg, MD 20899
66. T. D. Seagrave, Bayer Corporation, 100 Bayer Road, Pittsburgh, PA 15205
67. D. R. Secrist, Fortafil Fibers, Inc., 121 Cardiff Valley Road, Rockwood, TN 37854
68. D. Stewart, Stewart Automotive Research, LLC, 1260 Shotwell Street, Houston, TX 77020
69. S. J. Winckler, Cyclics Corporation, 747 Pierce Road, Clifton Park, NY 12065
- 70-73. J. A. Carpenter, U.S. Department of Energy, 1000 Independence Avenue, SW, Washington, DC 20585
74. S. Diamond, U.S. Department of Energy, 1000 Independence Avenue, SW, Washington, DC 20585